Spin Fluctuations in the Stacked-Triangular Antiferromagnet YMnO₃[†]

B. Roessli¹, S. N. Gvasaliya^{1,2}, E. Pomjakushina^{1,3}, and K. Conder³

¹ Laboratory for Neutron Scattering ETHZ and Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland

² Ioffe Physical Technical Institute, St. Petersburg, 194021 Russia

³ Laboratory for Development and Methods, Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland

Received February 24, 2005

The spectrum of spin fluctuations in the stacked-triangular antiferromagnet YMnO₃ was studied above the Néel temperature using both unpolarized and polarized inelastic neutron scattering. We find an in-plane and an out-of-plane excitation. The in-plane mode has two components just above T_N : a resolution-limited central peak and a Debye-like contribution. The quasi-elastic fluctuations have a line width that increases with q as Dq^z and the dynamical exponent $z = 2.3$. The out-of-plane fluctuations have a gap at the magnetic zone center and do not show any appreciable q dependence at small wave vectors. © 2005 Pleiades Publishing, Inc.

PACS numbers: 75.40.-s, 78.70.Nx

1. INTRODUCTION

YMnO₃ belongs to the family of RMnO₃ (R = Rare-earth) manganite ferroelectric compounds that crystallize in the hexagonal space group $P6_3cm$ below the paraelectric–ferroelectric phase transition (~ 900 K). In YMnO₃, the Mn³⁺ ions form triangular layers well separated from each other by Y layers. Because, in the ferroelectric phase, the lattice is distorted, the Mn ions are slightly trimerized. The large separation between adjacent layers suggests that YMnO₃ forms a good candidate for a geometrically frustrated 2-Dimensional (2D) antiferromagnet.

The magnetic structure of hexagonal YMnO₃ was first investigated by Bertaut and Mercier [1] and reinvestigated later in more details by Munoz *et al.* [2]. Below $T_N \sim 70$ K, the $S = 2$ magnetic moment of Mn ions are arranged in a 120° magnetic structure with the triangular layers at $z = 0$ and $z = 1/2$ being antiferromagnetically coupled. At saturation, the magnetic moment is $\mu = 2.9\mu_B$; i.e., it is significantly reduced from the expected $4\mu_B$ of Mn³⁺ spins, which was taken as evidence that, even in the ordered phase, strong spin fluctuations are present as a consequence of geometrical frustration [3]. Analysis of the spin-wave spectrum has confirmed the 2D character of the magnetic exchange interactions in YMnO₃ [4] with the ratio of the intra- to interplane exchange interactions being on the order $\sim 2 \times 10^2$. Whereas well-defined excitations are observed below the ordering temperature, a broad inelastic signal, as well as short-range correlations between the Mn magnetic moments within the triangular layers, persists well above T_N [3].

In this work, we investigate the q and temperature dependence of the spin excitations in YMnO₃ close to the Néel temperature. We were motivated by the fact that the nature of the phase transition of frustrated magnets is still not completely understood and that the critical properties of stacked triangular antiferromagnets have received special attention since Kawamura [5] proposed that the critical exponents in these systems form a new universality class. Experimental confirmation of the new class of (chiral) exponents was found in CsMnBr₃ by unpolarized [6] and polarized neutron scattering [7] measurements as well as in Ho [8]. Second, an anomaly in the dielectric constant ϵ with the electric field applied in the ab plane was found in YMnO₃ [9] at T_N . The nature of the coupling between the electric and magnetic properties in hexagonal manganites is a subject of intense debate [10]. Clearly, it is required to characterise the behavior of the magnetic fluctuations in the vicinity of T_N to understand the possible relationship with the magneto-dielectric effect in YMnO₃ [11].

2. EXPERIMENTAL

Polycrystalline YMnO₃ was prepared using a solid state reaction. The starting materials of Y₂O₃ and MnO₂ with 99.99% purity were mixed and grounded and then treated at 1000–1200°C in air for at least 70 h with several intermediate grindings. The phase purity of the compound was checked with a conventional x-ray diffractometer (SIEMENS D500). The powder was hydrostatically pressed in the form of rods (8 mm in diameter and ~ 60 mm in length). The rods were subsequently sintered at 1300°C for 30 h. The crystal growth was carried out using an optical floating zone furnace (FZ-T-

[†] This article was submitted by the authors in English.

Fig. 1. Temperature dependence of the intensity of the (1 0 0) magnetic Bragg peak. The line is a fit to the data with a power law.

10000-H-IV-VP-PC, Crystal System Corp., Japan) with four 1000 W halogen lamps as a heat source. The growth rate was 1.5 mm/h and both rods (the feeding and seeding rod) were rotated at about 20 rpm in opposite directions to ensure the liquid homogeneity. A mixture of argon with 2% oxygen at 5.5 bar was applied during the growing. The crystal has the shape of a rod 6 mm in diameter and 2 cm in height and a mosaic spread better than 1° .

The measurements were performed at triple-axis TASP located on the cold source of the neutron spallation source SINQ. The sample was mounted inside an He-flow cryostat with the crystallographic axis a^* and c^* in the scattering plane. The spectrometer was operated with the energy of the scattered neutrons kept fixed at $k_f = 1.47 \text{ \AA}^{-1}$ for measurements with unpolarized neutrons. 80' Soller collimators were installed in the incident beam and before the analyzer and the detector. With that configuration the energy resolution at zero energy transfer is $180 \text{ \mu eV}$. To reduce both the background and contamination by higher wavelength neutrons a cold Be filter was installed in the scattered beam. The inelastic polarized neutron measurements were performed at $k_f = 1.51 \text{ \AA}^{-1}$ along $(1 \pm q, 0, 0.1)$ and at different temperatures above T_N . To perform longitudinal-polarization analysis, remanent supermirror benders [12] were inserted after the monochromator and before the analyzer. The orientation of the polarization was chosen perpendicular to the scattering plane. Because magnetic fluctuations with a polarization factor parallel to the neutron spin occur in the nonspin flip channel, the nonspin flip data (NSF) contains the in-plane fluctuations, and, in the spin-flip channel (SF), only out-of-plane fluctuations are present, as will be shown below.

3. RESULTS AND DISCUSSION

Figure 1 shows the intensity of the (1 0 0) magnetic Bragg reflection as a function of the temperature, which mirrors the square of the staggered magnetization. The transition temperature, as determined by taking the derivative of the magnetization curve [13], is $T_N = 72.1 \pm 0.05 \text{ K}$. The intensity of the Bragg peak follows the power law $I \propto |(T/T_N - 1)|^{2\beta}$ with $\beta = 0.187(2)$. This value is lower than that reported for the case of typical stacked-triangular antiferromagnet RbNiCl_3 ($\beta = 0.28$), CsNiCl_3 ($\beta = 0.28$), and CsMnBr_3 ($0.21 < \beta < 0.25$) and close to the critical exponent obtained in VCl_2 ($\beta = 0.20$) [5, 14]. Typical 2D XY-antiferromagnets ($\text{BaNi}_2(\text{PO}_4)_2$) or ferromagnets (Rb_2CrCl_4 , K_2CuF_4) have a magnetization exponent that corresponds to the expected theoretical value $\beta = 0.23$ [15]. We note that $\beta = 0.19$ in the 3D triangular Ising antiferromagnet [16].

Figure 2a shows elastic scans along the $[1 0 l]$ direction as a function of temperature. Close to the Néel temperature, correlations between adjacent hexagonal planes give rise to broad magnetic scattering along c^* that eventually appears to condense into the magnetic Bragg peak at T_N . From Fig. 2b, we see that this diffuse scattering is static on the time scale of our experiment and corresponds to slow fluctuations of in-plane character, as will be shown below. With increasing temperature, these correlations disappear and only scattering across the $[1 0 l]$ direction show a peak in the neutron cross section. Hence, well above T_N , correlations persist only between the Mn moments located in the hexagonal plane, as shown in Fig. 3. Here, we describe the line shape of the diffuse intensity by a Lorentzian profile convoluted with the resolution function of the spectrometer:

$$\chi_c(\mathbf{Q}) = \frac{\chi_0}{\pi} \frac{\kappa_{\parallel}^2}{(\mathbf{q}_{\parallel} - \mathbf{Q}_0) + \kappa_{\parallel}^2} \frac{\kappa_{\perp}^2}{(\mathbf{q}_{\perp} - \mathbf{Q}_0)^2 + \kappa_{\perp}^2} \delta(\omega), \quad (1)$$

where $\mathbf{Q}_0$ is the position of the magnetic rod in reciprocal space, $\parallel$ and $\perp$ denote the direction along and perpendicular to the magnetic rod, and $\kappa_{\parallel}$ denotes the inverse of the correlation length ξ between Mn spins in the hexagonal plane. Close to the Néel temperature, the temperature dependence of ξ behaves similar to $\xi(T) = 0.038(\pm 0.005)(T - T_N)^{\nu}$ with $\nu = 0.57(\pm 0.06)$ as shown in Fig. 3b. We now turn to the behavior of the paramagnetic fluctuations in YMnO_3 . Figure 4 shows typical energy scans performed at $\mathbf{Q} = (1 - q, 0, -3.8)$ and $T = 73.6 \text{ K}$. The inelastic cross-section for an unpolarized neutron beam is given by

$$\frac{d^2\sigma}{d\Omega d\omega} \propto \sum_{\alpha\beta} (\delta_{\alpha\beta} - \hat{Q}_{\alpha}\hat{Q}_{\beta}) S^{\alpha\beta}(\mathbf{Q}, \omega), \quad (2)$$

where $\delta_{\alpha\beta}$ is the Kronecker symbol; α, β are the Cartesian coordinates x, y, z , $(\mathbf{Q}, \omega)$ that denote the momen-

Fig. 2. (a) Elastic scans along $(1, 0, l)$ that show the increase of diffuse magnetic scattering in YMnO_3 when the temperature approaches T_N . (b) Inelastic scan that shows the presence of the central peak in YMnO_3 . The insert shows the difference between scans measured at $(1, 0, -3.8)$ and $(1, 0, -3.5)$ that emphasizes the resolution-limited component.

tum and energy transfers from the neutron to the sample; and $\hat{Q} = \mathbf{Q}/|\mathbf{Q}|$. The first term in Eq. (2) is a selection rule that implies that only spin components perpendicular to the scattering vector contribute to the neutron scattering cross section. Hence, for scattering vectors with large l components such as $\mathbf{Q} = (1 \pm q, 0, -3.8)$, the inelastic spectrum contains essentially paramagnetic fluctuations with in-plane character ($\parallel$). In addition, close to the Néel temperature, inelastic scans through the magnetic rod show the resolution-limited central peak described by Eq. (1) as shown in Fig. 2. Thus, to analyze the data shown in Fig. 4, we modeled the inelastic intensity $I(\mathbf{Q}, \omega)$ in the following way:

$$I(\mathbf{Q}, \omega) = (S_{\text{para}}^{\parallel}(\mathbf{Q}, \omega) + S_{\text{inc}}(\omega) + S\chi_c(\mathbf{Q})) \otimes R(\mathbf{Q}, \omega) + Bck, \quad (3)$$

where $S_{\text{inc}} = A\delta(\omega)$ refers to the resolution-limited incoherent scattering that was measured at high temperature

Fig. 3. (a) Neutron diffuse intensity in YMnO_3 . The background was measured at $T = 300$ K and has been subtracted. (b) Temperature dependence of the inverse of the correlation length. The line is a fit to the data with a power law.

and S is a scale factor. The neutron scattering function $S_{\text{para}}^{\parallel}(\mathbf{Q}, \omega)$, which is related to the imaginary part of the dynamical susceptibility through $\pi(g\mu_B)^2 S_{\text{para}}^{\parallel}(\mathbf{Q}, \omega) = F^2(Q)(1 - \exp(-\hbar\omega/k_B T))^{-1} \Im\chi''(\mathbf{Q}, \omega)$, describes the line shape of the paramagnetic scattering as a function of momentum ($\mathbf{Q}$) and energy ($\hbar\omega$) transfer, respectively; $F(Q)$ is the magnetic form factor of Mn. In Eq. (3), the symbol $\otimes$ stands for the convolution with the spectrometer resolution function $R(\mathbf{Q}, \omega)$ [17] and Bck denotes the background level. We find that a Debye-like quasi-elastic line shape for the imaginary part of the dynamical susceptibility

$$\Im\chi''(\mathbf{Q}_0 + \mathbf{q}, \omega) = \omega\chi(\mathbf{Q}_0 + \mathbf{q}) \frac{\Gamma(\mathbf{q})}{\omega^2 + \Gamma(\mathbf{q})^2} \quad (4)$$

reproduces the data adequately. $\chi(\mathbf{q})$ is the static susceptibility as in Eq. (1) taken relative to the antiferromagnetic zone center ($\mathbf{Q}_0 = (1, 0, 0)$), and $\Gamma(\mathbf{q})$ is the damping of the paramagnetic fluctuations. Figure 4

Fig. 4. Constant q -scans in YMnO_3 at $T = 73.6$ K and 79.8 K that show the in-plane fluctuations, as explained in the text. The lines are the result of fit to the data using Eq. (3).

shows the results of fits to the data at $T = 73.6$ K from which we extract that the damping of the in-plane fluctuations $\Gamma(\mathbf{q})$ evolves similar to $\Gamma(0, T) + (1450 \pm 90)q^z$ (meV) with $\Gamma(0, 73.6 \text{ K}) = 0.23 \pm 0.07$ (meV), and $z = 2.26 \pm 0.07$. In contrast with data taken around $(1 \pm q, 0, 3.8)$, the inelastic spectra around $(1 \pm q, 0, 0.1)$ cannot be fitted with Eq. (4). This is an indication that the spectrum of paramagnetic fluctuations in YMnO_3 consists of 2 modes, an in-plane ($\parallel$) as well as an out-of-plane component ($\perp$). To separate the $\parallel$ from the $\perp$ fluctuations, it is necessary to use polarization analysis. A typical inelastic spectrum measured with polarization analysis is shown in Fig. 5 that reveals an out-of-plane excitation in the spin-flip channel. In contrast with the

Fig. 5. Constant q -scans in YMnO_3 at $T = 73.6$ K that show the in-plane fluctuations in the non-spin flip (NSF) and the out-of-plane component in the spin-flip channel (SF), respectively. The lines are the result of fit to the data as described in the text.

$\parallel$ fluctuations, the $\perp$ component is inelastic and is best described by a damped-harmonic oscillator function

$$S_{DHO}^{\perp} \propto \frac{\omega}{1 - \exp(-\omega/T)} \frac{\gamma_q}{(\omega^2 - \Omega_q^2)^2 + \omega^2 \gamma_q^2}, \quad (5)$$

where Ω_q is the renormalized frequency and γ_q the damping of the excitation. Within the precision of the measurements, we find that $\Omega_q = 3.9 \pm 0.3$ (meV) and $\gamma_q = 2 \pm 0.5$ (meV) in the range of momentum values reached in the present experiment ($q \leq 0.1$).

The analysis of the data in the non-spin-flip channel yields the same q dependence for the $\parallel$ fluctuations that was obtained with the unpolarized set up. The results are summarized in the table. The mean value for the dynamical exponent of the $\parallel$ fluctuations in YMnO_3 yields $z \sim 2.3$ and does not agree with the theoretical dynamical exponent $z = 1$ for the classical 2D triangular antiferromagnet [18]. Also, the value obtained in YMnO_3 is quite different from the dynamical exponents $z = 1.5$ expected for the 3D Heisenberg antiferromagnet and measured, e.g., in RbMnF_3 [19] and CsMnBr_3 [20]. Finally, we show the temperature dependence of $\Gamma(0, T)$ in Fig. 6, which increases almost linearly above T_N , $\Gamma(0, T) = 0.4 + 0.07(T - T_N)^{1.1 \pm 0.2}$.

Parameter values for the damping ($\Gamma(\mathbf{q}) = \gamma q^z$ (meV)) and the critical exponent (z) of the $\parallel$ -fluctuation in YMnO_3

	$T(\text{K})$	γ	$\Delta\gamma$	z	Δz
Unpol.	73.6	1450	90	2.26	0.07
	79.8	1283	272	2.29	0.16
Pol.	74	1306	277	2.53	0.25
	78	1028	313	2.40	0.4

Fig. 6. Temperature dependence of the damping of the paramagnetic fluctuations with in-plane polarization as measured with polarized neutrons. The line is a fit to the data as explained in the text.

4. CONCLUSIONS

To conclude, using both unpolarized and polarized inelastic neutron scattering, we showed that there are two magnetic excitations in the paramagnetic regime of YMnO_3 that have in-plane and out-of-plane polarization, respectively. The in-plane mode has a resolution-limited central peak and a quasi-elastic component with a line width that increases as a function of momentum transfer q similar to $\propto q^z$ with the dynamical exponent $z = 2.3$. The presence of two time scales in the spectrum of in-plane fluctuations might be the signature for the coexistence of 2D and 3D fluctuations in the vicinity of T_N [21]. The out-of-plane fluctuations are inelastic at the magnetic zone center and do not show any q dependence for small wave vectors.

This work was performed at the Neutron Spallation Source SINQ, Paul Scherrer Institut, Switzerland and was partly supported by the NCCR MaNEP project.

REFERENCES

1. B. Bertaut and M. Mercier, Phys. Lett. **5**, 27 (1963).

2. A. Munoz, J. A. Alonso, M. J. Martínez-Lope, *et al.*, Phys. Rev. B **62**, 9498 (2000).
3. Junghwan Park, J.-G. Park, Gun Sang Jeon, *et al.*, Phys. Rev. B **68**, 104426 (2003).
4. T. J. Sato, S. H. Lee, T. Katsufuji, *et al.*, Phys. Rev. B **68**, 014432 (2003).
5. For a recent review see H. Kawamura, J. Phys.: Condens. Matter **10**, 4707 (1998).
6. T. E. Mason, B. D. Gaulin, and M. F. Collins, Phys. Rev. B **39**, 586 (1989).
7. V. P. Plakhty *et al.*, Europhys. Lett. **48**, 215 (1999); Phys. Rev. Lett. **85**, 3942 (2000).
8. V. P. Plakhty, W. Schweika, Th. Brückel, *et al.*, Phys. Rev. B **64**, 100402 (2001).
9. Z. J. Huang *et al.*, Phys. Rev. B **56**, 2623 (1997); T. Katsufuji *et al.*, Phys. Rev. B **64**, 104419 (2001).
10. T. Kimura *et al.*, Nature **426**, 55 (2003); D. V. Efremov *et al.*, Nat. Mater. **3**, 853 (2004); B. Lorenz *et al.*, Phys. Rev. Lett. **92**, 087204 (2004).
11. G. Laws, A. P. Ramirez, C. M. Varma, *et al.*, Phys. Rev. Lett. **91**, 257208 (2003).
12. F. Semadeni, B. Roessli, and P. Böni, Physica B (Amsterdam) **297**, 152 (2001).
13. A. D. Bruce, J. Phys. C **14**, 193 (1982).
14. M. F. Collins and O. A. Petranko, Can. J. Phys. **75**, 605 (1997).
15. S. T. Bramwell and P. C. W. Holdsworth, J. Phys.: Condens. Matter **5**, L53 (1993).
16. O. Heinonen and R. G. Petschek, Phys. Rev. B **40**, 9052 (1989).
17. M. Popovich, Acta Crystallogr. A **31**, 507 (1975).
18. Kwangsik Nho and D. P. Landau, Phys. Rev. B **66**, 174403 (2002).
19. R. Coldea, R. A. Cowley, T. G. Perring, *et al.*, Phys. Rev. B **57**, 5281 (1998).
20. T. E. Mason, Y. S. Yang, M. F. Collins, *et al.*, J. Magn. Magn. Mater. **104–107**, 197 (1992).
21. L. P. Regnault, C. Lartigue, J. F. Legrand, *et al.*, Physica B (Amsterdam) **156–157**, 298 (1989); A. R. Völkel, A. R. Bishop, F. G. Mertens, *et al.*, J. Phys.: Condens. Matter **4**, 9411 (1992).