Dynamics of the two-dimensional $S = \frac{1}{2}$ dimer system $(\text{C}_5\text{H}_6\text{N}_2\text{F})_2\text{CuCl}_4$

Tao Hong,¹ S. N. Gvasaliya,^{5,*} S. Herringer,² M. M. Turnbull,² C. P. Landee,² L.-P. Regnault,³
M. Boehm,⁴ and A. Zheludev⁵

¹Neutron Scattering Science Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee 37831-6393, USA

²Carlson School of Chemistry and Department of Physics, Clark University, Worcester, Massachusetts 01610, USA

³CEA-Grenoble, INAC-SPSMS-MDN, 17 rue des Martyrs, F-38054 Grenoble Cedex 9, France

⁴Institut Laue-Langevin, Boîte Postale 156, F-38042 Grenoble, France

⁵Neutron Scattering and Magnetism, Laboratorium für Festkörperphysik, ETH Zürich, Zürich CH-8093, Switzerland

(Received 6 October 2010; published 4 February 2011)

Inelastic neutron scattering was used to study a quantum $S = 1/2$ antiferromagnetic Heisenberg system—Bis(2-amino-5-fluoropyridinium) Tetrachlorocuprate(II). The magnetic excitation spectrum is shown to be dominated by long-lived excitations with an energy gap of $\Delta = 1.07(3)$ meV. The measured dispersion relation is consistent with a simple two-dimensional square lattice of weakly coupled spin dimers. Comparing the data to a random phase approximation treatment of this model gives the intradimer and interdimer exchange constants $J = 1.45(2)$ meV and $J' = 0.31(3)$ meV, respectively.

DOI: [10.1103/PhysRevB.83.052401](https://doi.org/10.1103/PhysRevB.83.052401)

PACS number(s): 75.10.Jm, 75.50.Ee

Quantum spin liquids, where strong zero-point fluctuations destroy magnetic long-range order even at $T = 0$, have been a subject of intense studies for over two decades. Of particular interest are two-dimensional (2D) systems of this type. In addition to their relevance to layered superconducting cuprates,^{1,2} they are of interest in the context of field-induced quantum phase transitions,^{3,4} where, to date, most experimental work was performed on either spin chains^{5,6} and ladders,^{7–10} or three-dimensional (3D) systems.^{11,12} Several 2D spin liquids including $\text{BaCuSi}_2\text{O}_6$,¹³ $\text{SrCu}_2(\text{BO}_3)_2$,¹⁴ and PHCC ¹⁵ have been studied in great detail, but show rather complex behavior due to geometrically frustrated interactions.

Recently, a new quantum antiferromagnet Bis(2-amino-5-fluoropyridinium) Tetrachlorocuprate(II) (5FAP- CuCl_4 , for short) was discovered and characterized by bulk measurements.¹⁶ The ground state is a spin liquid. The energy gap Δ to the lowest excited (triplet) state was determined to be $0.97(4)$ meV from high-field magnetization data. 5FAP- $\text{CuCl}_4[(\text{C}_5\text{H}_6\text{N}_2\text{F})_2\text{CuCl}_4]$ crystallizes in a monoclinic space group $P2_1/c$ with lattice constants $a = 6.926(7)$ Å, $b = 21.73(2)$ Å, $c = 10.911(10)$ Å, and $\beta = 100.19(2)^\circ$. There are four inequivalent Cu atoms per unit cell as shown in Fig. 1(a). In view of the crystal structure, 5FAP- CuCl_4 consists of CuCl_4^{2-} anion layers separated by organic cations. Those CuCl_4^{2-} anions form zigzag layers which are stacked along the crystallographic a axis as shown in Fig. 1(b). Figure 1(c) shows the arrangement of CuCl_4^{2-} anions and organic cations viewing from the a axis. The yellow and purple lines indicate the most plausible superexchange interactions that could be carried across Cu-Cl-Cl-Cu bonds. The former involves the shortest Cl-Cl contact with a separation of 3.66 Å, while for the latter the relevant Cl-Cl distance is 4.07 Å. One can expect interlayer coupling along the a axis to be exponentially weaker due to a much larger Cl-Cl separation 5.07 Å. Even with this in mind, it is not obvious which in-plane interactions are the most relevant. To better understand the spin Hamiltonian for 5FAP- CuCl_4 , this Brief Report

details our inelastic neutron scattering (INS) measurements of magnetic excitations and their dispersion relation. We show that 5FAP- CuCl_4 can be adequately described by a minimal model that is equivalent to a square lattice of weakly interacting antiferromagnetic $S = 1/2$ dimers with no geometric frustration.

Small-size fully deuterated single-crystalline samples of 5FAP- CuCl_4 were prepared by the procedure described in Ref. 16. About 20 single crystals (~ 0.3 g total) were co-aligned with a mosaic about 4° and used for INS measurements on the cold-neutron triple-axis spectrometer IN14 at Institut Laue-Langevin. Another assembly consisting of 20 single crystals (~ 0.5 g) with a total 5° mosaic was used for measurements on the TASP¹⁷ spectrometer at SINQ, Paul Scherrer Institute. Horizontal beam divergences were given by ^{58}Ni guide-60'-open-open at IN14 and by $10'/\text{\AA}$ -open-open-open at TASP. Both experiments were performed with the scattered wave vector k_f fixed at $1.5 \text{ \AA}^{-1}$ and cooled Be filter, placed after the sample was used to remove higher-order beam contamination. The sample was oriented horizontally in a $(0,k,l)$ reciprocal lattice plane and cooled in a standard He-4 cryostat.

The data were collected in a series of constant- q scans at $T = 1.5$ K along the high symmetry directions in the $(0,k,l)$ reciprocal plane. The inset of Fig. 2(a) shows the raw data of a typical scan performed at $\mathbf{q} = (0,0,-1.5)$, where a sharp resolution-limited peak due to a magnetic excitation is clearly visible. The background (shown as a solid line) was determined by fitting the data over the range where no magnetic excitations are apparent to a term linear in energy, plus a resolution-limited Gaussian peak at zero energy transfer. The latter accounted for incoherent elastic scattering. Background-subtracted data at several wave vectors are shown in Fig. 3. At certain wave vectors the observed signal has a distinct double-peak structure as shown in Figs. 3(c) and 3(d). Solid lines in Fig. 3 are fits to Gaussian profiles of fixed widths, determined by instrumental resolution, as calculated using the Cooper-Nathans approximation.¹⁸ Excitation energies

FIG. 1. (Color online) (a) Outline of a unit cell in 5FAP-CuCl₄. (b) View from the *c* axis, showing the zigzag layer structure. Only Cu and Cl atoms are shown, the organic cations have been removed for clarity. (c) View from the *a* axis, showing the arrangement of CuCl₄²⁻ anions and organic cations. Different color lines stand for the different magnetic interactions. Color coding is as follows: magenta-Cu, green-Cl, black-C, red-H, blue-F, and cyan-N.

(dispersion relation) obtained from such fits are summarized in Fig. 2. The spectrum appears to consist of two equivalent branches, an “optic” one and an “acoustic” one, although the former is not visible at the majority of the wave vectors studied.

The most comprehensive method of determining the relevant exchange parameters in a gapped system with weakly dispersive excitations is based on the application of the first-moment sum rule for the magnetic dynamic structure factor.¹⁹ This procedure involves quantitative measurements of inelastic intensities as a function of wave vector and was successfully applied to the rather complex interaction geometry in CuHpCl.¹¹ Due to technical complications, associated with the sample fracturing upon cooling, and the data being collected in several disjoint experiments, in the present study we adopted a simpler approach. Only the measured excitation energies were analyzed. A parametrized model was refined to reproduce the experimental dispersion relations. The proposed minimal model is

FIG. 2. Dispersion of magnetic excitations measured in 5FAP-CuCl₄ at *T* = 1.5 K as a function of *k* and *l*. The solid (dashed) line is a fit to the acoustic (optical) magnon dispersion mode as discussed in the text. Inset: Constant-*q* = (0, 0, -1.5) scan as a function of the transferred energy $\hbar\omega$ at *T* = 1.5 K. The solid line is a Gaussian and a linear term fit to account for the background contribution.

visualized in Fig. 4, which shows the exchange constants in a single layer of magnetic Cu²⁺ ions. The dimers are formed by the stronger antiferromagnetic bonds *J*, which ensures a spin-singlet ground state and an energy gap. The dispersion of singlet-triplet dimer excitations is due to the weaker interdimer exchange constant *J'*. Topologically, this spin network can be viewed as a square lattice of *S* = 1/2 dimers. Nevertheless, its actual realization in the crystal has two dimers per crystallographic unit cell. This leads to a folding of the Brillouin zone and the appearance of two excitation branches. As shown below, this minimal model seems to be fully consistent with the experimental observations.

We can treat the weak interdimer coupling *J'* at the random phase approximation (RPA) level.²⁰ This method has been applied to numerous spin systems, including Cs₃Cr₂Br₉,²¹ BaCuSi₂O₆,²² BaCuSi₂O₇,²³ Ba₃Mn₂O₈,²⁴ and Ba₃Cr₂O₈.²⁵ In application to 5FAP-CuCl₄, we can treat two decoupled dimers in a unit cell as the basic spin cluster (tetramer). These tetramers will then form a Bravais lattice. With four sites in each tetramer, their bare susceptibilities are written as a 4 × 4 matrix, the indexes enumerating the four spins in

each unit:

$$\chi_0(\omega) = \frac{J}{2J^2 - 2(\hbar\omega)^2} R(T) \begin{pmatrix} 1 & -1 & 0 & 0 \\ -1 & 1 & 0 & 0 \\ 0 & 0 & 1 & -1 \\ 0 & 0 & -1 & 1 \end{pmatrix}. \quad (1)$$

Here $R(T) = \frac{1 - e^{-J/(k_B T)}}{1 + 3e^{-J/(k_B T)}}$ is the difference in population of the excited and ground states of the dimers. The weak interaction J' couples adjacent tetramers, but also dimers within each tetramer. Its effect is taken into account within the RPA. The corresponding RPA equation is written as

$$\chi^{\text{RPA}}(\mathbf{q}, \omega) = \chi_0(\omega) [1 - \chi_0(\omega) J'(\mathbf{q})]^{-1}. \quad (2)$$

Here $J'(\mathbf{q})$ is the Fourier transform of exchange interactions due to J' . It is also written as a 4×4 matrix:

$$J'(\mathbf{q}) = J' \begin{pmatrix} 0 & 0 & 0 & e^{-i2\pi(k+l)} + e^{-i2\pi k} \\ 0 & 0 & 1 + e^{-i2\pi l} & 0 \\ 0 & 1 + e^{i2\pi l} & 0 & 0 \\ e^{i2\pi(k+l)} + e^{i2\pi k} & 0 & 0 & 0 \end{pmatrix}. \quad (3)$$

The dispersion relation is then readily obtained from the location of poles in $\chi^{\text{RPA}}(\mathbf{q}, \omega)$:

$$(\hbar\omega_{\mathbf{q}})^2 = J^2 \mp J J' R(T) [\cos \pi(k+l) + \cos \pi(k-l)]. \quad (4)$$

The solid and dashed lines in Fig. 2 are fits of this dispersion relation to the experimental data. Good agreement is obtained with $J = 1.45(2)$ meV and $J' = 0.31(3)$ meV.

In summary, the spin dynamics of 5FAP-CuCl₄ is dominated by long-lived magnons with a bandwidth of 0.70(4) meV.

FIG. 3. Representative background-subtracted INS data for 5FAP-CuCl₄ at $T = 1.5$ K. The solid lines are fits Gaussian profiles of instrumental width. The shaded area in (a) is excluded due to a contamination by “accidental Bragg” spurious scattering.

This value is smaller than gap energy $\Delta = 1.07(3)$ meV, but still substantial. A minimal model, topologically equivalent to a square lattice of weakly interacting dimers, adequately describes the measured dispersion curves. However, since only excitation energies, and not intensities, were systematically measured, one cannot fully exclude a more complex, perhaps partially frustrated, coupling geometry. Future work will focus on the high-field study of quantum phase transition and critical phenomena in 5FAP-CuCl₄.

One of the authors (AZ) would like to thank B. Normand for discussions. The work at ORNL was partially funded by the Division of Scientific User Facilities, Office of Basic Energy Sciences - Materials Science, Department of Energy.

FIG. 4. (Color online) Minimal model for magnetic interactions in 5FAP-CuCl₄, shown in projection onto the (b, c) plane. Dimer singlets are formed by antiferromagnetic exchange J . Dispersion of singlet-triplet excitations is due to interdimer interaction J' .

*Previous address: Laboratory for Neutron Scattering, Paul Scherrer Institut, Villigen PSI, CH-5232, Switzerland.

- ¹P. W. Anderson, *Science* **235**, 1196 (1987).
- ²P. A. Lee, N. Nagaosa, and X.-G. Wen, *Rev. Mod. Phys.* **78**, 17 (2006).
- ³S. Sachdev, *Quantum Phase Transitions* (Cambridge University Press, Cambridge, 1999).
- ⁴T. Giamarchi, Ch. Rüegg, and O. Tchernyshyov, *Nature Phys.* **4**, 198 (2008).
- ⁵M. B. Stone, D. H. Reich, C. Broholm, K. Lefmann, C. Rischel, C. P. Landee, and M. M. Turnbull, *Phys. Rev. Lett.* **91**, 037205 (2003).
- ⁶T. Hong, R. Custelcean, B. C. Sales, B. Roessli, D. K. Singh, and A. Zheludev, *Phys. Rev. B* **80**, 132404 (2009).
- ⁷B. C. Watson, V. N. Kotov, M. W. Meisel, D. W. Hall, G. E. Granroth, W. T. Montfrooij, S. E. Nagler, D. A. Jensen, R. Backov, M. A. Petruska, G. E. Fanucci, and D. R. Talham, *Phys. Rev. Lett.* **86**, 5168 (2001); B. Thielemann, Ch. Rüegg, H. M. Ronnow, A. M. Läuchli, J.-S. Caux, B. Normand, D. Biner, K. W. Krämer, H.-U. Güdel, J. Stahn, K. Habicht, K. Kiefer, M. Boehm, D. F. McMorrow, and J. Mesot, *ibid.* **102**, 107204 (2009).
- ⁸T. Hong, M. Kenzelmann, M. M. Turnbull, C. P. Landee, B. D. Lewis, K. P. Schmidt, G. S. Uhrig, Y. Qiu, C. Broholm, and D. Reich, *Phys. Rev. B* **74**, 094434 (2006).
- ⁹T. Masuda, A. Zheludev, H. Manaka, L.-P. Regnault, J.-H. Chung, and Y. Qiu, *Phys. Rev. Lett.* **96**, 047210 (2006); V. O. Garlea, A. Zheludev, T. Masuda, H. Manaka, L.-P. Regnault, E. Ressouche, B. Grenier, J.-H. Chung, Y. Qiu, K. Habicht, K. Kiefer, and M. Boehm, *ibid.* **98**, 167202 (2007); T. Hong, A. Zheludev, H. Manaka, and L.-P. Regnault, *Phys. Rev. B* **81**, 060410(R) (2010).
- ¹⁰T. Hong, Y. H. Kim, C. Hotta, Y. Takano, G. Tremelling, M. M. Turnbull, C. P. Landee, H.-J. Kang, N. B. Christensen, K. Lefmann, K. P. Schmidt, G. S. Uhrig, and C. Broholm, *Phys. Rev. Lett.* **105**, 137207 (2010).
- ¹¹M. B. Stone, Y. Chen, J. Rittner, H. Yardimci, D. H. Reich, C. Broholm, D. V. Ferraris, and T. Lectka, *Phys. Rev. B* **65**, 064423 (2002).
- ¹²Ch. Rüegg, N. Cavadini, A. Furrer, H.-U. Güdel, K. Krämer, H. Mutka, A. Wildes, K. Habicht, and P. Vorderwisch, *Nature (London)* **423**, 62 (2003).
- ¹³S. E. Sebastian, N. Harrison, C. D. Batista, L. Balicas, M. Jaime, P. A. Sharma, N. Kawashima, and I. R. Fisher, *Nature (London)* **441**, 617 (2006); Ch. Rüegg, D. F. McMorrow, B. Normand, H. M. Ronnow, S. E. Sebastian, I. R. Fisher, C. D. Batista, S. N. Gvasaliya, Ch. Niedermayer, and J. Stahn, *Phys. Rev. Lett.* **98**, 017202 (2007).
- ¹⁴B. D. Gaulin, S. H. Lee, S. Haravifard, J. P. Castellan, A. J. Berlinsky, H. A. Dabkowska, Y. Qiu, and J. R. D. Copley, *Phys. Rev. Lett.* **93**, 267202 (2004).
- ¹⁵M. B. Stone, I. Zaliznyak, D. H. Reich, and C. Broholm, *Phys. Rev. B* **64**, 144405 (2001); M. B. Stone, I. A. Zaliznyak, T. Hong, C. L. Broholm, and D. H. Reich, *Nature (London)* **440**, 187 (2006); M. B. Stone, C. Broholm, D. H. Reich, P. Schiffer, O. Tchernyshyov, P. Vorderwisch, and N. Harrison, *New J. Phys.* **9**, 31 (2007).
- ¹⁶L. Li, M. M. Turnbull, C. P. Landee, J. Jornet, M. Deumal, J. J. Novoa, and J. L. Wikaira, *Inorg. Chem.* **46**, 11254 (2007).
- ¹⁷F. Semadeni, B. Roessli, and P. Boeni, *Physica B* **297**, 152 (2001).
- ¹⁸M. J. Cooper and R. Nathans, *Acta Crystallogr.* **23**, 357 (1967).
- ¹⁹P. C. Hohenberg and W. F. Brinkman, *Phys. Rev. B* **10**, 128 (1974).
- ²⁰S. B. Haley and P. Erdős, *Phys. Rev. B* **5**, 1106 (1972).
- ²¹B. Leuenberger, A. Stebler, H. U. Güdel, A. Furrer, R. Feile, and J. K. Kjems, *Phys. Rev. B* **30**, 6300 (1984).
- ²²Y. Sasago, K. Uchinokura, A. Zheludev, and G. Shirane, *Phys. Rev. B* **55**, 8357 (1997).
- ²³A. Zheludev, M. Kenzelmann, S. Raymond, T. Masuda, K. Uchinokura, and S.-H. Lee, *Phys. Rev. B* **65**, 014402 (2001).
- ²⁴M. B. Stone, M. D. Lumsden, Y. Qiu, E. C. Samulon, C. D. Batista, and I. R. Fisher, *Phys. Rev. B* **77**, 134406 (2008).
- ²⁵M. Kofu, J.-H. Kim, S. Ji, S.-H. Lee, H. Ueda, Y. Qiu, H.-J. Kang, M. A. Green, and Y. Ueda, *Phys. Rev. Lett.* **102**, 037206 (2009).