The Hydration of β - and α' -H-Dicalcium Silicates: An X-ray Spectromicroscopic Study

Jiaqi Li[†], Guoqing Geng^{†, §*}, Wenxin Zhang[†], Young-Sang Yu[‡], David A. Shapiro[‡], and Paulo J.M. Monteiro[†]

[†]Department of Civil and Environmental Engineering, University of California, Berkeley, 725 Davis Hall, UC Berkeley, California, 94720 United States

[§]Laboratory for Waste Management, OHLD/004, Paul Scherrer Institut, 5232 Villigen PSI, Switzerland

[‡]Advanced Light Source, Lawrence Berkeley National Laboratory, Building 2, 0437 Berkeley, California, 94720, United States

*Corresponding author: guoqing_geng@berkeley.edu

KEYWORDS. Portland cement; dicalcium silicate; low carbon cement; silicate chain polymerization; calcium silicate hydrate; calcium coordination; morphology

ABSTRACT

Dicalcium silicate (C_2S) is an important clinker mineral in Portland and belite-calcium sulfoaluminate cement. However, there is still a lack of information on the local degree of silicate polymerization and calcium coordination in C_2S hydration products. This study aimed to

fill this gap by characterizing the hydration of two C_2S polymorphs, the β - and α'_H types, using scanning transmission X-ray microscopy coupled with ptychographic imaging. The results showed that the coordination of the Ca species in β - and α'_H - C_2S had a distorted, cubic-like symmetry, whereas the Ca coordination of calcium silicate hydrate (C-S-H), the main hydration product, was structurally similar to that of tobermorite. The outer hydration product (Op) of both polymorphs exhibited an increasing degree of silicate polymerization over time. The inner hydration product (Ip) of β - C_2S polymerized slower than Op; however, the degree of silicate polymerization of both Ip and Op in the α'_H - C_2S hydration system was comparable. The polymerization degree of Op was inhibited by adjacent β - C_2S particles, whereas in α'_H - C_2S , the polymerization degree was more homogenous. Ptychographic imaging shows that the Op of α'_H - C_2S exhibits coarser fibrils than the Op of β - C_2S , and a clear Op-Ip interface of hydrated β - C_2S is observed.

INTRODUCTION

Concrete is the second most consumed material after water ¹. Its strength comes from the hydration of cement. The production of conventional Portland cement (PC) accounts for 8-9% of global CO₂ emission and 2-3% of energy consumption ². The major compounds of PC clinker are tricalcium silicate (Ca_3SiO_5 , also termed C_3S in cement chemistry notation), dicalcium silicate (Ca_2SiO_4 , also termed C_2S ; or belite as impure C_2S), tricalcium aluminate ($Ca_3Al_2O_6$), and tetracalcium aluminoferrite (Ca_2AlFeO_5). Among them, C_3S is the most abundant phase, but it has the highest environmental impact due to the high calcination temperatures and heavy CO₂ emission from decomposing limestone. The cement industry is under increasing pressure to reduce CO₂ emissions and energy consumption. Production of C_2S -rich PC at the expense of the

typically more abundant C_3S is one way to lower the environmental impact of PC manufacturing³. For example, belite-calcium sulfoaluminate (BCSA) cement is a very promising alternative to PC because the calcination temperature of BCSA is 200 °C lower than PC⁴. BCSA cement (also belite-rich) manufacturing is capable of reducing CO₂ emission and energy consumption by 30% and 20%, respectively⁵.

The main binding phase of hardened PC pastes and concretes is a calcium silicate hydrate (C-S-H) gel. The structure and properties of C-S-H govern the mechanical properties and durability of PC-based materials^{6 7}. The well-accepted molecular models of C-S-H (Figure 1) are created by modifying a tobermorite structure⁸ with defected dreierketten-type silicate chains, which are composed of bridging and pairing tetrahedra, flanked on CaO₇ sheets to form the calcium silicate basal layer. The neighboring basal layers are separated by zeolitic calcium ions and water⁹. The structures of synthetic nanocrystalline C-S-Hs have been extensively studied at the atomic, molecular, and nano scales. However, the atomic and molecular structures (e.g., Ca and Si coordination) of hydration product C-S-H have been inadequately studied due to their poor ordering along the *c*-axis. Understanding the structure and properties of C-S-H is essential for optimizing the properties of sustainable cement-based materials.

Figure 1. Schematic representation of the nanostructures of C-S-H. The Brown circles represent Ca species in the Ca-O sheet, and blue triangles are silicate units in paired and bridging sites. The grey diamonds and yellow squares represent sites which can be occupied by cations that charge-neutralize the structure as a whole (e.g., Ca^{2+} and/or K^+).

The hydration of C_2S is similar to the intensively studied hydration of C_3S ; both yield C-S-H gel and portlandite ($Ca(OH)_2$) as hydration products¹⁰. β - C_2S is the most common polymorph of C_2S in cements. Using the original surface of the unreacted particle as a reference, C-S-H exhibits a distinct morphology in the outer and inner regions. The inner product (Ip) C-S-H from β - C_2S hydration is spherulite-like on the nano-scale¹¹, while the outer product (Op) C-S-H is fibrillar¹² and contributes to the binding properties. Apart from the apparent morphological

difference due to the available space for stacking ¹¹, there is no significant difference in composition between the Ip and Op ¹². The reactivity of β -C₂S is lower than C₃S, but the β -C₂S hydration is significant for the long-term performance of PC concrete ¹³. The β -C₂S hydration has been investigated by nuclear magnetic resonance (NMR) ^{14 15 16 17}, electron microscopy ^{18 19 20}, and other spectroscopies ^{21 22 23 24}. However, these techniques are not capable of locally probing the polymerization degree of the silicate chain of the Ip or Op. e.g., NMR, Raman spectroscopy, and infrared spectroscopy can provide chemical environmental Si of C-S-H, but are not capable of providing adequate spatial data ^{25 26 27}. Scanning electron microscopy provides high-resolution images, whereas the polymerization degree of C-S-H cannot be evaluated ²⁸. The potential artifacts generated by the harsh vacuum and high energy electron beam are also not completely understood ^{29 30 31}. Recently, α' -C₂S, another polymorph of C₂S, has increasingly gained research and industrial interests due to its higher hydration reactivity compared to β -C₂S ³². However, the current understanding of the micro-chemistry (e.g., local coordination environment and silicate polymerization) during its hydration is limited ³³. Understanding the hydration of C₂S polymorphs and the structure of their hydration products C-S-H is essential for optimizing the properties of sustainable cement and concrete and for lowering the CO₂ emission and energy use in the construction industry.

Scanning transmission X-ray microscopy (STXM) is a powerful technique for characterizing the micro-chemistry of composite materials with a heterogeneous microstructure. It simultaneously provides morphological information and X-ray absorption near-edge structure (XANES) spectra of the elements of interest ^{34 35}, with a spatial resolution of up to 10 nm and a spectral resolution of 0.1 eV ³⁶. C-S-H gel is vulnerable to electron beam damage ³⁷, and the soft X-ray used in STXM (< 2000 eV) is more likely to preserve the morphology of C-S-H ³⁸. The application of

STXM in cement research started in recent years^{39 40 41 42 43 38 44 45}; however, no STXM or XANES study has been reported on the hydration of C₂S.

In this work, the hydration products of C₂S polymorphs (β - and α' _H-) were studied by STXM at the Ca *L*_{2,3}- and Si *K*-edges. The coordination of Ca of anhydrous C₂S and C-S-H was also analyzed. Silicate polymerization of the Op and Ip and their C₂S interfaces at two different ages were locally probed. Ptychographic imaging was used to provide the interface morphology between the Ip and Op and between water and the Op with a spatial resolution of 10 nm.

MATERIALS AND METHODS

Preparation of β - and α' _H-C₂S. Chemical analytical grade CaCO₃, SiO₂, and K₂CO₃ were mixed according to the stoichiometric composition of 1.80CaO-0.10K₂O-SiO₂ to prepare monoclinic β -C₂S. The mixed powder was calcined at 1500 °C for 3 hours and then cooled in air⁴⁶. Chemical analytical grade Ca₂SiO₄ and Ca₃(PO₄)₂ were stoichiometrically mixed as 1.946CaO-0.892SiO₂-0.054P₂O₅ to prepare α' _H-C₂S. The mixed powder was sintered at 1450 °C for 6 hours, followed by air cooling⁴⁷. Note that, to ensure the fast formation of single phase (high purity) of β - and α' _H-C₂S, the calcination temperatures of this laboratory synthesis were higher than typical calcination temperature of belite-rich cement (e.g., 1250 °C). The C₂S pellets were then grounded into powders. The particle size distribution D-values, D10, D50, and D90 of anhydrous β -C₂S were 1.19 μ m, 6.74 μ m, and 18.48 μ m, respectively. The D10, D50, and D90 of anhydrous α' _H-C₂S were 1.45 μ m, 7.05 μ m, and 19.08 μ m, respectively.

Sample preparation for STXM. Anhydrous C_2S powders were mixed with deionized water with a water-to-solid ratio (w/s) of 10 so that the particles were easily isolated by drop-casting to satisfy the transmission observation in the STXM. The suspensions were stored in polyethylene tubes filled with N_2 gas at 25 ± 1 °C. At early and late curing ages (10 days and 40 days for α' - C_2S ; 17 days and 51 days for β - C_2S), the suspension of 0.5 μ L was dropped onto a Si wafer frame (5 mm $\times$ 5 mm, 100 nm thick), where a 100-nm-thick Si_3N_4 membrane window (1 mm $\times$ 1 mm, 100 nm thick) is in the center. The liquid was quickly and gently absorbed with a tip of KimWipes^{TM} from the edge of the Si frame. The liquid removal process was monitored under an optical microscope to ensure that most of the solids remain on the membrane window. The anhydrous powders were dry-dusted on the Si_3N_4 membrane windows directly. These windows were then placed on the STXM sample stage inside a vacuum chamber.

Scanning Transmission X-ray Microscopy. The XANES spectra and images at Si K -edge (1830–1880 eV) and Ca $L_{2,3}$ -edge (342–360 eV) were obtained at beamlines 5.3.2.1 and 5.3.2.2, respectively, at the Advanced Light Source of the Lawrence Berkeley National Laboratory (LBNL). Comprehensive descriptions of the STXM beamlines are given in ^{36 48}.

The optical density (OD) at a specific energy of all pixels is affected by composition, density, and sample thickness ⁴⁰. Element mappings were obtained by differential measurements of the OD at pre- and on- edge at a spatial resolution up to 25 nm. Image stacks were collected by scanning the region of interest (ROI) at a series of beam energies, which yielded a XANES spectrum of each pixel on the ROI. RGB overlay maps, which visualize multiple phases with

various compositions, were generated using singular value decomposition with reference spectra. All data processing was conducted using *aXis2000* software⁴⁸. At each age, at least two RGB maps were taken to obtain statistically reliable results, and at least ten spectroscopic measurements were taken from different particles on each Si₃N₄ membrane.

Ptychographic images were collected at 800 eV at beamline 5.3.2.1. Full details of the imaging technique are given in⁴⁴. The spatial resolution of these transmission images is ~10 nm. The images were reconstructed by *Nanosurveyor* package⁴⁹. The width of C-S-H fibers of hydrated samples in the ptychographic images was quantified using *ImageJ* with *F3D* plugin developed at LBNL⁵⁰.

RESULTS AND DISCUSSION

Ca coordination of anhydrous β -C₂S and hydrated β -C₂S for 17 days. The Ca $L_{2,3}$ -edge XANES spectra (Figure 2) consist of two major peaks, L_3 2P_{3/2} (a_2) and L_2 2P_{1/2} (b_2), which are due to the loss of degeneracy of 2p orbitals by spin-orbital interactions⁵¹, along with a number of minor leading peaks, a_0 , a_1 , and b_1 , in order of increasing energy. The peak energy difference of a_2 - a_1 and b_2 - b_1 (ΔL_3 and ΔL_2 , termed as splitting energy) and the intensity of the minor peaks are relevant to the coordination symmetry of Ca in the first shell and its ordering^{52 53 54 55}.

Figure 2. Hydrated β -C₂S at 17 days: (A) Transmission image of the ROI taken at 349 eV; (B) selected regions in the Ca element map for the XANES spectra; (C) Ca $L_{2,3}$ -edge XANES spectra extracted from different regions specified in (B).

The Ca $L_{2,3}$ -edge XANES spectrum (Figure 2C) of anhydrous β -C₂S (monoclinic) exhibits a cubic-like symmetry with peak a_{10} located between a_1 and a_2 , and the peak energy differences of $a_2 - a_1$ and $b_2 - b_1$ are 1.54 and 1.2 eV, respectively. β -C₂S contains seven-fold and eight-fold coordinated Ca, denoted as Ca1 and Ca2 (Supporting Information, Figure S1). The equatorial plane of Ca1 is parallel to $(10\bar{1})$ with Ca-O bond lengths for Ca1 ranging from 2.273 to 2.892 Å with an average of 2.528 Å⁵⁶. The five equatorial O atoms are not exactly coplanar. The Ca2 is

coordinated by eight O atoms with a distorted symmetry for the cube, where the two trapezoids formed of the top four and bottom four O atoms are misaligned along each other's diagonal direction by 55 °. The Ca-O bond lengths for Ca2 range from 2.400 to 2.676 Å with an average of 2.503 Å. The complex coordination of Ca1 and Ca2 in β -C₂S produces weak cubic-like crystal field splitting effects.

To avoid X-ray absorption saturation at low energy, only particles with size of ~1 μ m (Figure 2A and 1B) were measured at Ca $L_{2,3}$ -edge. The 17-day hydrated β -C₂S grains at the Ca $L_{2,3}$ -edge show mostly identical peak positions and an equivalent splitting energy in each grain, indicating that the Ca in each grain exhibits a similar environment. Peaks a₂ and b₂ in the selected areas are 0.1 eV lower than anhydrous β -C₂S, suggesting a lower bond strength of Ca-O. The splitting energies in the selected areas are 1.1 eV, suggesting a distorted octahedral-like symmetry for Ca⁵². The X-ray absorption features (i.e., splitting energy and peak positions) are similar to 14Å tobermorite (calcium silicate hydrate mineral, [Ca₄Si₆O₁₆(OH)₂ · 2H₂O] (Ca 5H₂O))^{57 58}, suggesting the C-S-H formed in this hydration system is structurally analogous to tobermorite. The relative intensity ratios of peak a₁-to-a₂ (I(a₁)/I(a₂)) and b₁-to-b₂ (I(b₁)/I(b₂)) of these selected areas are 0.021-0.041 and 0.050-0.077, respectively, which are lower than hydrothermally synthetic C-S-H at 25 °C (0.05-0.15 for I(a₁)/I(a₂) and 0.07-0.15 for I(b₁)/I(b₂))³⁸. The details in the calculation of relative intensity of these peaks are shown in Figure S2 (Supporting information). Synthetic C-S-H has a longer range order than C-S-H formed in the β -C₂S hydration along the *c*-axis⁵⁹. This suggests a shorter range order for Ca in this hydration system since the Ca/Si molar ratio of C-S-H in hydrated β -C₂S ranges from 1.2 to 2.1⁶⁰. Moreover, no contribution by portlandite (a non-strength-giving phase in hydrated C₂S) was observed in the spectra, suggesting that C-S-H does not intermix with portlandite at the 25 nm-scale in this ROI,

and the interlayer six-fold coordinated Ca is also distorted. Thus, the Ca of C-S-H in hydrated β -C₂S is short-range-ordered and tobermorite-like. Portlandite crystallites were observed elsewhere in these dilute systems (Supporting information, Figure S3).

Hydrated C₃S at 17 days also exhibited comparable peak positions, splitting energies, and intensity ratios in XANES at the Ca $L_{2,3}$ -edge ⁶¹, indicating that the Ca environment of hydrated C₃S is similar to hydrated β -C₂S. The extended X-ray absorption fine structure study showed that the Ca-O environment of hydrated β -C₂S is similar to 11 Å tobermorite, but the coordination number and Ca-O bond length of C-S-H could not be determined due to the presence of portlandite ⁶². An ¹⁷O NMR study demonstrated that Ca-OH sites are present in C-S-H of hydrated β -C₂S ¹⁷. The C-S-H structure of hydrated β -C₂S proposed by Richardson ¹² contains six- and seven-fold coordinated Ca in the interlayer and intralayer, respectively. The model proposed by Gartner ⁶³ suggests that the interlayer Ca of C-S-H from hydration of C₃S and β -C₂S is six-fold coordinated. In the present work, the distorted six-fold Ca in the interlayer of hydrated β -C₂S fits both models.

Ca coordination of anhydrous α' _H-C₂S and α' _H-C₂S hydrated for 10 days. The Ca $L_{2,3}$ -edge XANES spectra of α' _H-C₂S (orthorhombic) also exhibits a cubic-like symmetry with peak energy differences of a_2 - a_1 of 1.57 eV and b_2 - b_1 of 1.25 eV in Figure 3. This indicates a slightly stronger crystal field of Ca for α' _H-C₂S. α' _H-C₂S contains nine- and eight-fold coordinated Ca at two sites (denoted as Ca1 and Ca2, see Figure S1 in Supporting information) with Ca-O bond lengths for Ca1 ranging from 2.214 to 3.175 Å with an average of 2.708 Å, and those for Ca2 ranging from 2.292 to 2.927 Å with an average of 2.545 Å ⁵⁶. The superposition of symmetries and complex

coordination leads to the cubic-like crystal field splitting of $\alpha'_H\text{-C}_2\text{S}$. The energy difference in $\alpha'_H\text{-C}_2\text{S}$ is slightly larger compared to $\beta\text{-C}_2\text{S}$ (monoclinic), suggesting that Ca-O complexes in $\alpha'_H\text{-C}_2\text{S}$ are more similar to cubic-like symmetry (less distorted) than in $\beta\text{-C}_2\text{S}$. For Ca1 in $\beta\text{-C}_2\text{S}$, its coordination number is seven, which is incapable of providing an ideal cubic symmetry.

Figure 3. Hydrated $\alpha'_H\text{-C}_2\text{S}$ at 10 days: (A) Transmission image of the ROI taken at 349 eV; (b) selected regions in the Ca element map for the XANES spectra; (c) Ca $L_{2,3}$ -edge XANES spectra extracted from different regions specified in (b).

Portlandite was not observed in this region for $\alpha'_H\text{-C}_2\text{S}$ hydrated for 10 days. Mostly identical peak positions and peak intensities were observed in each grain. Peaks a₂ and b₂ in the selected areas are ~ 0.1 eV lower than for $\alpha'_H\text{-C}_2\text{S}$, and the peak positions are 0.05 eV higher than for

hydrated β -C₂S. The splitting energies in the compounds are ~0.1 eV lower than for α' _H-C₂S but ~0.05 eV higher than for hydrated β -C₂S. This suggests that the bond strength of Ca-O of hydrated α' _H-C₂S is slightly higher than for hydrated β -C₂S; namely, more six-fold coordinated Ca is present in the α' _H-C₂S hydration system. The intensity ratios of hydrated α' _H-C₂S are 0.018-0.038 and 0.037-0.067, which are also lower than for anhydrous but comparable to or slightly lower than hydrated β -C₂S. These absorption features indicate that the coordination symmetry of Ca in hydrated α' _H-C₂S is also tobermorite-like, but the ordering of Ca is slightly lower than for hydrated β -C₂S.

Si environment of anhydrous β -C₂S and β -C₂S hydrated for 17 days. The major peak of a_1 at the Si *K*-edge of β -C₂S (Figure 4C) is assigned to the electronic excitation from 1s to the antibonding 3p-like state orbital (t_2) of tetrahedral Si^{64 65}. Pre-edge peak a_0 is attributed to the dipole-forbidden transition of 1s electrons to the antibonding 3s-like states⁶⁶. This forbidden peak appears due to the mixing of s- and p- states when the SiO₄ tetrahedra coordination is highly distorted. Thus, the intense a_0 peak of β -C₂S suggests a strong distortion of silicate tetrahedron. The minor peak of a_2 is assigned to the multiple-scattering effect from more distant atom shells through a photoelectron interaction; its energy is governed by the interatomic distance and structural complexity⁶⁷.

The interface between the β -C₂S core and the hydrous layer C-S-H is well distinguished (Figure 4), indicating changes in the phase density. The OD of the hydration product layer slightly decreases with increasing distance from the interface, which is associated with several small brighter regions. Compared to C₃S hydration system⁶¹, the C-S-H of hydrated β -C₂S is more

dispersed, and fibrils are not present at this age and at this resolution (Figure 4A).

Figure 4. Hydrated β -C₂S at 17 days: (A) Transmission image of the ROI taken at 1849 eV; (B)

selected regions in the Si element map from the XANES spectra; (C) Si *K*-edge XANES spectra extracted from different regions specified in (B); (D) RGB overlay map using XANES spectra obtained from the C-S-H (Area 4, green) marked in (B) and reference spectrum of anhydrous β -C₂S (red). More RGB over maps can be found in Figure S4 (Supporting information).

Peak a_1 is not shown at ~ 1851.1 eV in areas 3, 4, 6 but a single a_1 peak is at 1848.8 eV in these areas (Figure 4C), suggesting that C-S-H is the only silicate phase in these areas. The absorption features of C-S-H in hydrated β -C₂S resemble those of C-S-H in C₃S hydration systems^{68 61 43}. The Si *K*-edge (a_1 peak) at 1848.8 eV of C-S-H is 2.2 eV lower than that of β -C₂S due to the longer Si-O bond of the C-S-H relative to β -C₂S^{69 56}. Li⁶⁴ concluded that although there is considerable overlapping for silicate minerals with different polymerization types, the Si *K*-edge generally shifts to higher energy with increased silicate polymerizations. Thus, in this case, the Si-O bond length, rather than the polymerization degree, dominates the Si *K*-edge shift.

The energy difference between a_1 and a_2 , $\Delta a_2 - a_1$, can be used to evaluate the degree of silicate polymerization^{38, 43, 61, 68}. The values of $\Delta a_2 - a_1$ for areas 3 and 4 are equivalent, suggesting that the degree of polymerization of the C-S-H here is comparable. The energy positions of multiple scattering peaks (e.g., a_2) are affected by the Si interatomic distances, while the intensity and number of resonances are heavily dependent on the bond angle, site symmetry, and number of nearest neighboring oxygen atoms (Si in most cement phases are 4-fold coordinated, except thaumasite, where Si is 6-fold coordinated)⁷⁰. Two a_2 peaks are distinguished in the spectra in areas 2 and 5. In these areas, a peak at 1848.8 eV and a broad shoulder/hump at ~ 1851.1 eV were observed, the peak is assigned to the a_1 peak of C-S-H, and the shoulder/hump is the contribution of a_1 peak (at 1851.0 eV) of anhydrous β -C₂S. These absorption features suggest that areas 2 and 5 are mixtures of C-S-H and anhydrous β -C₂S, and the hydration here is incomplete. Similarly,

areas 7 and 8 are mixes of C-S-H and anhydrous β -C₂S, implying that small β -C₂S particles exist in these areas. This fact is consistent with the original granulometry result of β -C₂S, ~10% of β -C₂S was below 1 μ m. Note that a weak contribution of C-S-H to the spectrum at ~1848.8 eV is observed in area 1 since C-S-H surrounds the entire grain. Δa_2-a_1 of area 6 is 0.9 eV lower than those of areas 3 and 4 (~15.7 eV), suggesting a lower degree of polymerization of C-S-H in area. The difference in local polymerization degree can be explained by the different dissolution rates on the crystal faces and by different numbers of surface defects of β -C₂S⁷¹; multiple crystal faces with low hydraulic reactivity occur in area 6. Note that, hydraulic reactivity of all faces of pure β -Ca₂SiO₄ is similar; the dopant changes the local reactivity of β -C₂S crystals⁷². Similarly, the value of Δa_2-a_1 for C-S-H in area 9 is 0.7 eV lower than for C-S-H in the unconstrained space. The RGB overlay map (Figure 4d) shows that the C-S-H surrounds the unreacted core, which is consistent with the analysis above. The values of Δa_2-a_1 for C-S-H among different grains (Areas A- D) are 15.6-16.1 eV, indicating a distinction in silicate polymerization due to the interference of other grains and the hydration rate. In addition, the contribution of cross-linking sites to the spectra is not observed in the typical range at 1853-1854 eV⁷³ since the basal layers of C-S-H are separated by [Ca(H₂O)₆]²⁺ or [Ca(OH)(H₂O)₅]⁺⁶³. ²⁹Si NMR studies showed that the mean silicate chain lengths of C-S-H of 7-12 months hydrated β -C₂S are still lower than 3.5^{12 74}. This suggests that the proportion of long silicate chains (octamer or longer) in this C-S-H is relatively low. Therefore, the C-S-H at 17 days is mainly a mixture of dimer and pentamer C-S-Hs.

It is well known that the degree of silicate polymerization of synthetic C-S-H increases as Ca/Si decreases^{27 26}. Although the degree of polymerization of hydrated β -C₂S progressively increases over time^{17 75}, there is no significant variation in the mean Ca/Si of Op (excluding intermixed

portlandite) with age³⁷. Thus, it is difficult to estimate the local degree of polymerization based on Ca/Si ratio. STXM is a more reliable technique to locally probe the variation in silicate polymerization of the C-S-H without considering intermixed microcrystalline portlandite in the hydrous regions¹² and unreacted β -C₂S.

Si environment of hydrated β -C₂S for 51 days. Two distinct optical densities were observed at 51 days (Figure 5A). Double a_1 peaks are not observed in Figure 5B, and only a single a_1 peak at 1848.9-1849.1 eV occurs. Peak a_0 at 1847.9 eV was not observed, suggesting a fully hydrated grain (see Supporting information, Figure S5). The peak difference of Δa_2-a_1 for areas 5, 6, 7, 8, 9, and B is 16.7-17.0 eV, and 15.8-16.2 eV for areas 1, 2, 3, and 4; two distinct ranges of Δa_2-a_1 were observed in Figure 5C. Thus, the two distinct ODs indicate the existence of Ip (dark region) and Op (light region) in Figure 5A. Areas 5, 6, 7, 8, and 9 are Ip dominant, while the areas 1, 2, 3, and 4 are Op dominant. The Si K -edge (a_1) and Δa_2-a_1 of Ip are both lower compared to those of Op, indicating a lower silicate polymerization and a slightly longer Si-O bond for Ip. The Δa_2-a_1 and Si K -edge for Op at 51 days are slightly higher than at 17 days, revealing that the Op polymerizes over time. The lower Δa_2-a_1 for areas 10 and A may be explained by impingement from adjacent grains. Similarly, contribution of cross-linking sites to the spectra was also not observed due to the abundant interlayer Ca between basal layers of C-S-H⁶³. Thus, both Op and Ip are likely mixtures of dimer and pentamer C-S-Hs with very small amounts of octamer and longer chains. The values of Δa_2-a_1 for Op and Ip are larger compared to those of synthetic C-S-H with a bulk Ca/Si molar ratio of 1.4³⁸, suggesting that the electron shielding on Si from cations in hydration product C-S-Hs is weaker. This can be explained by the highly distorted Ca of $[\text{Ca}(\text{OH})(\text{H}_2\text{O})_5]^+$ in the interlayer of C-S-Hs; and the partial replacement of divalent Ca by

monovalent K from the dopant ⁷⁶. Future study will focus the coordination environment of K in this system and the electron density around these atoms.

Figure 5. Hydrated β -C₂S at 51 days: (A) Transmission image of the ROI at 1849 eV; (B) selected regions in the Si element map for the XANES spectra; (C) Si K-edge XANES spectra

extracted from different regions specified in (C); (D) ptychographic image of another area at the same age. Op is indicated by blue arrows, Ip is indicated by red arrows, and portlandite is indicated by yellow arrows.

The ptychographic image (Figure 5d) shows the fibrillar Op of another hydrated β -C₂S particle at 51 days; the width of fibers has a distribution of 11-25 nm, which is smaller than the Op of C₃S⁷⁷. The Ip of β -C₂S exhibits a dense aggregated structure, and the Ip of C₃S with the same w/s exhibits a less dense structure with aggregates of globules⁷⁷. The morphological difference between the two Ips can be explained by the lower reactivity of β -C₂S. Geng⁶⁸ reported that the Ip and Op of hydrated C₃S exhibits an identical Si *K*-edge with a higher energy for the *a*₂ peaks of Op, showing that Ip has a lower degree of silicate polymerization. Portlandite microcrystallites intermixed with Op is observed, which is consistent with TEM study of Richardson¹¹.

Si environment of anhydrous and hydrated α' _H-C₂S for 10 days. Similar to β -C₂S, pre-edge peak *a*₀ was also observed in α' _H-C₂S (Figure 6c), suggesting a slight distortion of the silicate tetrahedron of α' _H-C₂S. The Si *K*-edge of α' _H-C₂S is 0.2 eV higher than for β -C₂S, suggesting a slightly shorter Si-O bond for α' _H-C₂S compared with β -C₂S, which is consistent with XRD refinement⁵⁶.

Figure 6. Hydrated $\alpha'_H\text{-C}_2\text{S}$ at 10 days: (A) Transmission image of the ROI taken at 1849 eV; (B) selected regions in the Si element map for the XANES spectra; (C) Si K-edge XANES spectra extracted from different regions specified in (B); (D) RGB overlay map using XANES spectra obtained from the C-S-H (area 7, green) marked in (B) and reference spectrum of

anhydrous $\alpha'_H\text{-C}_2\text{S}$ (red).

Similar to $\beta\text{-C}_2\text{S}$ hydration, the interface between non-fibrillar Op and $\alpha'_H\text{-C}_2\text{S}$ was observed at 10 days (Figure 6). The Si *K*-edge and $\Delta a_2\text{-}a_1$ of hydrated $\alpha'_H\text{-C}_2\text{S}$ at 10 days are equivalent to or 0.2-0.3 eV larger than for hydrated $\beta\text{-C}_2\text{S}$ at 17 days. Thus, the chemical environment of Si in hydrated $\alpha'_H\text{-C}_2\text{S}$ is similar to that in $\beta\text{-C}_2\text{S}$ hydration at 17 days with a comparable degree of polymerization at an earlier age. The polymerization degree of the Op is more homogeneous since the $\Delta a_2\text{-}a_1$ values of all C-S-Hs here are ~ 15.9 eV. Again, Op cross-linking sites are not present, suggesting that the Op is still mainly a mixture of dimer and pentamer units¹⁸. Thus, $\alpha'_H\text{-C}_2\text{S}$ exhibits a higher reactivity relative to $\beta\text{-C}_2\text{S}$. This work is consistent with experimental and simulation studies on the reactivity^{32 47 78} but provides new details on the rate of polymerization of $\alpha'_H\text{-C}_2\text{S}$ hydration.

Si environment of hydrated $\alpha'_H\text{-C}_2\text{S}$ for 40 days. The C-S-H of $\alpha'_H\text{-C}_2\text{S}$ at 40 days is fibrillar in Figure 7. There was no Ip/Op interface in the fully hydrated grain (see Supporting information, Figure S6) observed. The values of $\Delta a_2\text{-}a_1$ for all the areas range from 16.7 to 17.0 eV, suggesting a relatively homogenous polymerization. This is a primary difference compared to $\beta\text{-C}_2\text{S}$. The Si *K*-edge (a_1) of all areas is comparable, suggesting similar Si coordination in these areas. The comparable degree of polymerization of the interfaces between different grains suggests that the polymerization is not obviously interfered by adjacent grains. Additionally, the C-S-Hs are mainly mixtures of dimer and pentamer units, and a cross-linking effect was not observed on the spectra. Compared to the Op of $\beta\text{-C}_2\text{S}$ at 51 days, hydrated $\alpha'_H\text{-C}_2\text{S}$ at 40 days

exhibited a comparable polymerization degree at an earlier age. This confirms the higher reactivity of $\alpha'_H\text{-C}_2\text{S}$ compared with $\beta\text{-C}_2\text{S}$.

Figure 7. Hydrated $\alpha'_H\text{-C}_2\text{S}$ at 40 days: (A) Transmission image of the ROI taken at 1849 eV; (B) selected regions in the Si element map for the XANES spectra; (C) Si K-edge XANES spectra extracted from different regions specified in (B); (D) ptychographic image.

The ptychographic image (Figure 7D) shows the fibrillar C-S-H with a width of 15-30 nm, which

is larger than hydrated β -C₂S but smaller than hydrated C₃S (41-59 nm)⁷⁷, and the inner C-S-H exhibits a looser aggregated structure with ~17 nm voids compared to the Ip of hydrated β -C₂S. The Ips of hydrated β -C₂S, C₃S, and PC with a practical w/s (i.e., <0.6) appear to be small and globular⁷⁹. The larger void of the Ip relative to the Ip of hydrated C₃S⁷⁹ could be induced by the w/s of 10 used in this study, which provides sufficient space for nanocrystallite growth during the fast hydration. The microstructure of hydrated α' _H-C₂S is similar to hydrated C₃S with the same w/s⁷⁷ instead of the hydrated β -C₂S mentioned above. Thus, the morphological difference among the silicates in these diluted systems may be relevant to their hydration reactivity. More ptychographic images can be found in Figure S7 (Supporting information).

CONCLUSIONS

The coordination environments of Ca and Si in anhydrous β -C₂S, α' _H-C₂S, and their hydration products were studied using STXM; the morphology of C-S-Hs was imaged by ptychography.

The key conclusions are:

- (1) Ca in both anhydrous phases are in a distorted cubic symmetric coordination. The Ca coordination of C-S-H in both hydration systems is highly distorted and is similar to 14Å tobermorite but have a shorter-range order. More six-fold coordinated Ca occur in hydrated α' _H-C₂S than in hydrated β -C₂S.
- (2) The Si of both anhydrous phases have asymmetric tetrahedral coordination. The silicate chain of the Op in both hydration systems polymerizes over time. The hydration products in the α' _H-C₂S system polymerize faster than in β -C₂S. The hydraulic reactivity of α' _H-C₂S is higher.

- (3) Ip has a lower degree of silicate polymerization than Op in fully hydrated β -C₂S, which is accompanied with a slightly longer Si-O bond due to the space constraint for contacting water. Compared with hydrated β -C₂S, the silicate polymerization in hydrated α' _H-C₂S is more homogenous.
- (4) The C-S-H of hydrated β -C₂S exhibits fine fibrils that intermix with portlandite, and Ip appears to be dense aggregated structure. The morphology of fully hydrated α' _H-C₂S is more homogenous, and its inner region is slightly more porous with nano-size voids. Ip and Op are not distinguished in fully hydrated α' _H-C₂S

Therefore, this study provides insights into advanced applications of the hydration behaviors of C₂S to C₂S rich cements and the controllability of the performance of these materials in service. The lower calcination temperature and CO₂ emission of α' _H-C₂S during manufacturing can reduce the environmental impact of cement manufacturing. Due to its high reactivity, α' _H-C₂S can be a practical alternative to C₃S and β -C₂S in Portland cement or BCSA cement. Therefore, this work is an important step towards the development of hydration mechanism of C₂S-rich cement, which will provide new insight into the performance of these sustainable cements (lower CO₂ emission and energy use) in service.

ASSOCIATED CONTENT

Supporting Information

Coordination environment of Ca in two C₂S polymorphs; an example of fitting of a XANES spectrum at Ca *L*_{2,3}-edge; transmission images at 349 eV of samples at 10 and 17 days; RGB

overlay maps of samples at 10, 17, 40, and 51 days; ptychographic images of samples at 40 and 51 days.

AUTHOR INFORMATION

Author Contributions

J.L., G.G., and P.J.M. conceived and designed the experiments. J.L. conducted the experiments. Y.-S.Y. and D.A.S. supported the imaging experiments. J.L., G.G., and W.Z. analyzed the results. J.L. and G.G. wrote the manuscript. All authors reviewed the manuscript.

ACKNOWLEDGEMENTS

This research was founded by the Republic of Singapore's National Research Foundation through a grant to the Berkeley Education Alliance for Research in Singapore (BEARS) for the Singapore-Berkeley Building Efficiency and Sustainability in the Tropics (SinBerBEST) Program. The Advanced Light Source is supported by the Director, Office of Science, and Office of Basic Energy Sciences of the U.S. Department of Energy under Contract No. DE-AC02-05CH11231. G. Geng also wants to acknowledge European Union's Horizon 2020 research and innovation programme under the Marie Skłodowska-Curie grant agreement No 701647. We thank Matthew Marcus for insightful discussions on fitting and interpretation of Ca $L_{2,3}$ -edge XANES spectra. We thank Ellis Gartner for the personal communication and help on the study of dicalcium silicates.

REFERENCES

1. Myers, R. J.; Geng, G.; Li, J.; Rodriguez, E. D.; Ha, J. Y.; Kidkhunthod, P.; Sposito, G.; Lammers, L. N.; Kirchheim, A. P.; Monteiro, P. J. M., Role of adsorption phenomena in cubic tricalcium aluminate dissolution. *Langmuir* **2017**, *33* (1), 45-55, DOI 10.1021/acs.langmuir.6b03474.
2. Mehta, P. K., Reducing the environmental impact of concrete. *Concrete international* **2001**, *23* (10), 61-66.
3. Lee, B. Y.; Kurtis, K. E., Proposed acceleratory effect of TiO₂ nanoparticles on belite hydration: Preliminary results. *J Am Ceram Soc* **2012**, *95* (1), 365-368, DOI 10.1111/j.1551-2916.2011.04937.x.
4. Chen, I. A.; Hargis, C. W.; Juenger, M. C. G., Understanding expansion in calcium sulfoaluminate-belite cements. *Cement and Concrete Research* **2012**, *42* (1), 51-60, DOI 10.1016/j.cemconres.2011.07.010.
5. Quillin, K., Performance of belite-sulfoaluminate cements. *Cement and Concrete Research* **2001**, *31* (9), 1341-1349, DOI 10.1016/j.cemconres.2011.07.010.
6. Zhou, Y.; Hou, D.; Jiang, J.; She, W.; Li, J., Molecular dynamics study on the solvated aniline (AN) and ethylene glycol (EG) monomers confined in calcium silicate nanometer channel: A case study of tobermorite. *Phys Chem Chem Phys* **2017**, DOI 10.1039/C7CP02928D.
7. Hou, D. S.; Zhang, J. R.; Li, Z. J.; Zhu, Y., Uniaxial tension study of calcium silicate hydrate (C-S-H): Structure, dynamics and mechanical properties. *Materials and Structures* **2015**, *48* (11), 3811-3824, DOI 10.1617/s11527-014-0441-1.
8. Merlino, S.; Bonaccorsi, E.; Kampf, A. R., Tobermorite 14 angstrom: Crystal structure and od character. *Applied Mineralogy, Vols 1 and 2* **2000**, 859-861, DOI 10.2138/am-1999-1015
9. Geng, G.; Myers, R. J.; Li, J.; Maboudian, R.; Carraro, C.; Shapiro, D. A.; Monteiro, P. J., Aluminum-induced dreierketten chain cross-links increase the mechanical properties of nanocrystalline calcium aluminosilicate hydrate. *Scientific Reports* **2017**, *7*, 44032, DOI 10.1038/srep44032.
10. Guo, P.; Wang, B.; Bauchy, M.; Sant, G., Misfit stresses caused by atomic size mismatch: The origin of doping-induced destabilization of dicalcium silicate. *Crystal Growth & Design* **2016**, *16* (6), 3124-3132, DOI 10.1021/acs.cgd.5b01740.
11. Richardson, I. G., The nature of C-S-H in hardened cements. *Cement and Concrete Research* **1999**, *29* (8), 1131-1147, DOI 10.1016/s0008-8846(99)00168-4.
12. Richardson, I. G., Tobermorite/jennite- and tobermorite/calcium hydroxide-based models for the structure of C-S-H: Applicability to hardened pastes of tricalcium silicate, beta-dicalcium silicate, portland cement, and blends of portland cement with blast-fumace slag, metakaolin, or silica fume. *Cement and Concrete Research* **2004**, *34* (9), 1733-1777, DOI 10.1016/j.cemconres.2004.05.034.
13. Taylor, H. F. W., Cement chemistry. *Thomas Telford* **1997**.

14. Chen, J. H.; Wang, Y. Y.; Wan, C. C.; Liou, D. C., MAS NMR-studies of the hydration process of beta-C₂S in the presence of chromium. *Cement and Concrete Research* **1994**, 24 (2), 319-324, DOI 10.1016/0008-8846(94)90058-2.
15. Tong, Y. Y.; Du, H.; Fei, L., Hydration process of beta-dicalcium silicate followed by MAS and CP/MAS nuclear-magnetic-resonance. *Cement and Concrete Research* **1991**, 21 (2-3), 355-358, DOI 10.1016/0008-8846(91)90016-b.
16. Tong, Y. Y.; Du, H.; Fei, L., CP-MAS NMR-studies of the initial hydration processes of activated and ordinary beta-dicalcium silicates. *Cement and Concrete Research* **1990**, 20 (6), 986-991, DOI 10.1016/0008-8846(90)90062-3.
17. Cong, X.; Kirkpatrick, R. J., 17O and 29Si MAS NMR study of β -C₂S hydration and the structure of calcium-silicate hydrates. *Cement and concrete research* **1993**, 23 (5), 1065-1077, DOI 10.1016/0008-8846(93)90166-7.
18. Richardson, I. G., The nature of the hydration products in hardened cement pastes. *Cement Concrete Comp* **2000**, 22 (2), 97-113, DOI 10.1016/S0958-9465(99)00036-0.
19. Doval, M.; Palou, M.; Mojumdar, S. C., Hydration behavior of C₂S and C₂AS nanomaterials, synthesized by sol-gel method. *J Therm Anal Calorim* **2006**, 86 (3), 595-599, DOI 10.1007/s10973-006-7713-0.
20. Lawrence, F. V.; Reid, D. A.; Decarval, A., Transmission electron-microscopy of hydrated dicalcium silicate thin-films. *J Am Ceram Soc* **1974**, 57 (3), 144-148, DOI 10.1111/j.1151-2916.1974.tb10838.x
21. Ibanez, J.; Artus, L.; Cusco, R.; Lopez, A.; Menendez, E.; Andrade, M. C., Hydration and carbonation of monoclinic C₂S and C₃S studied by raman spectroscopy. *J Raman Spectrosc* **2007**, 38 (1), 61-67, DOI 10.1002/jrs.1599.
22. Delgado, A. H.; Paroli, R. M.; Beaudoin, J. J., Comparison of IR techniques for the characterization of construction cement minerals and hydrated products. *Appl Spectrosc* **1996**, 50 (8), 970-976, DOI 10.1366/0003702963905312.
23. Rheinheimer, V.; Casanova, I., An X-ray photoelectron spectroscopy study of the hydration of C₂S thin films. *Cement and Concrete Research* **2014**, 60, 83-90, DOI 10.1016/j.cemconres.2014.03.005.
24. Black, L.; Stumm, A.; Garbev, K.; Stemmermann, P.; Hallam, K. R.; Allen, G. C., X-ray photoelectron spectroscopy of the cement clinker phases tricalcium silicate and beta-dicalcium silicate. *Cement and Concrete Research* **2003**, 33 (10), 1561-1565, DOI 10.1016/S0008-8846(03)00097-8.
25. Ortoboy, S.; Li, J.; Geng, G.; Myers, R. J.; Monteiro, P. J.; Maboudian, R.; Carraro, C., Effects of CO₂ and temperature on the structure and chemistry of C-(A-) S-H investigated by raman spectroscopy. *RSC Advances* **2017**, 7 (77), 48925-48933, DOI 10.1039/C7RA07266J.
26. Yu, P.; Kirkpatrick, R. J.; Poe, B.; McMillan, P. F.; Cong, X. D., Structure of calcium silicate hydrate (C-S-H): Near-, mid-, and far-Infrared spectroscopy. *J Am Ceram Soc* **1999**, 82 (3), 742-748, DOI 10.1111/j.1151-2916.1999.tb01826.x.

27. Cong, X. D.; Kirkpatrick, R. J., Si-29 MAS NMR study of the structure of calcium silicate hydrate. *Adv Cem Based Mater* **1996**, 3 (3-4), 144-156, DOI 10.1016/1065-7355(96)00023-5.
28. Zhou, Y.; She, W.; Hou, D.; Yin, B.; Chang, H.; Jiang, J.; Li, J., Modification of incorporation and in-situ polymerization of aniline on the nano-structure and meso-structure of calcium silicate hydrates. *Construction and Building Materials* **2018**, 182, 459-468, DOI 10.1016/j.conbuildmat.2018.06.141.
29. Gallucci, E.; Mathur, P.; Scrivener, K., Microstructural development of early age hydration shells around cement grains. *Cement and Concrete Research* **2010**, 40 (1), 4-13, DOI 10.1016/j.cemconres.2009.09.015.
30. Collier, N. C.; Sharp, J. H.; Milestone, N. B.; Hill, J.; Godfrey, I. H., The influence of water removal techniques on the composition and microstructure of hardened cement pastes. *Cement and Concrete Research* **2008**, 38 (6), 737-744, DOI 10.1016/j.cemconres.2008.02.012.
31. Galle, C., Effect of drying on cement-based materials pore structure as identified by mercury intrusion porosimetry - a comparative study between oven-, vacuum-, and freeze-drying. *Cement and Concrete Research* **2001**, 31 (10), 1467-1477, DOI 10.1016/S0008-8846(01)00594-4.
32. Cuesta, A.; Losilla, E. R.; Aranda, M. A.; Sanz, J.; Ángeles, G., Reactive belite stabilization mechanisms by boron-bearing dopants. *Cement and Concrete Research* **2012**, 42 (4), 598-606, DOI 10.1016/j.cemconres.2012.01.006.
33. Ghose, A.; Chopra, S.; Young, J. F., Microstructural characterization of doped dicalcium silicate polymorphs. *J Mater Sci* **1983**, 18 (10), 2905-2914, DOI 10.1007/bf00700771.
34. Yano, J.; Yachandra, V. K., X-ray absorption spectroscopy. *Photosynth Res* **2009**, 102 (2-3), 241-254, DOI 10.1007/s11120-009-9473-8.
35. Chae, S. R., et al. , Advanced nanoscale characterization of cement based materials using x-ray synchrotron radiation: A review. *International Journal of Concrete Structures and Materials* **2013**, 7 (2), 95-110. DOI 10.1007/s40069-013-0036-1.
36. Kilcoyne, D., et al., A new scanning transmission X-ray microscope at the ALS for operation up to 2500 eV. *AIP Conference Proceedings* **2010**, 465, DOI 10.1063/1.3463241.
37. Richardson, I. G.; Groves, G. W., Microstructure and microanalysis of hardened ordinary portland-cement pastes. *J Mater Sci* **1993**, 28 (1), 265-277.
38. Li, J.; Geng, G.; Myers, R. J.; Yu, Y.-S. S., David A; Carraro, Carlo; Maboudian, Roya; Monteiro, Paulo J.M. , The chemistry and structure of calcium (alumino) silicate hydrate: A study by xanes, ptychographic imaging, and wide- and small- angle scattering. *Cement and Concrete Research* **2019**, 115, 367-378, DOI 10.1016/j.cemconres.2018.09.008.
39. Wieland, E.; Dahn, R.; Vespa, M.; Lothenbach, B., Micro-spectroscopic investigation of Al and S speciation in hardened cement paste. *Cement and Concrete Research* **2010**, 40 (6), 885-891, DOI 10.1016/j.cemconres.2010.02.001.

40. Ha, J.; Chae, S.; Chou, K. W.; Tyliczszak, T.; Monteiro, P. J. M., Effect of polymers on the nanostructure and on the carbonation of calcium silicate hydrates: A scanning transmission X-ray microscopy study. *J Mater Sci* **2012**, *47* (2), 976-989, DOI 10.1007/s10853-011-5877-x.
41. Ha, J.; Chae, S.; Chou, K. W.; Tyliczszak, T.; Monteiro, P. J. M., Scanning transmission X-ray microscopic study of carbonated calcium silicate hydrate. *Transport Res Rec* **2010**, (2142), 83-88, DOI 10.3141/2142-12.
42. Hernandez-Cruz, D.; Hargis, C. W.; Bae, S.; Itty, P. A.; Meral, C.; Dominowski, J.; Radler, M. J.; Kilcoyne, D. A.; Monteiro, P. J. M., Multiscale characterization of chemical-mechanical interactions between polymer fibers and cementitious matrix. *Cement Concrete Comp* **2014**, *48*, 9-18, DOI 10.1016/j.cemconcomp.2014.01.001.
43. Li, Q.; Ge, Y.; Geng, G.; Bae, S.; Monteiro, P. J. M., CaCl₂-accelerated hydration of tricalcium silicate: A stxm study combined with ²⁹Si MAS NMR. *Journal of Nanomaterials* **2015**, *2015*, 1-10, DOI 10.1155/2015/215371.
44. Geng, G.; Myers, R. J.; Yu, Y. S.; Shapiro, D. A.; Winarski, R.; Levitz, P. E.; Kilcoyne, D. A. L.; Monteiro, P. J. M., Synchrotron X-ray nanotomographic and spectromicroscopic study of the tricalcium aluminate hydration in the presence of gypsum. *Cement and Concrete Research* **2018**, *111*, 130-137, DOI 10.1016/j.cemconres.2018.06.002.
45. Geng, G.; Myers, R. J.; Kilcoyne, A. L.; Ha, J.; Monteiro, P. J., Ca L_{2,3}-edge near edge X-ray absorption fine structure of tricalcium aluminate, gypsum, and calcium (sulfo) aluminate hydrates. *Am Mineral* **2017**, *102* (4), 900-908, DOI 10.2138/am-2017-5670.
46. Lai, G. C.; Nojiri, T.; Nakano, K., Studies of the stability of beta-Ca₂SiO₄ doped by minor ions. *Cement and Concrete Research* **1992**, *22* (5), 743-754, DOI 10.1016/0008-8846(92)90097-f.
47. Müller, R.; Neubauer, J.; Götz-Neunhoeffler, F., Effects of phosphate rich raw materials on the crystallographic and hydraulic properties of dicalcium silicate. *Proceedings of the 11th Int. Cong. On the Chem. of Cement, Durban, South Africa* **2003**, 1045-1053.
48. Kilcoyne, A. L. D.; Tyliczszak, T.; Steele, W. F.; Fakra, S.; Hitchcock, P.; Franck, K.; Anderson, E.; Harteneck, B.; Rightor, E. G.; Mitchell, G. E.; Hitchcock, A. P.; Yang, L.; Warwick, T.; Ade, H., Interferometer-controlled scanning transmission x-ray microscopes at the advanced light source. *J Synchrotron Radiat* **2003**, *10*, 125-136, DOI 10.1107/S0909049502017739
49. Shapiro, D. A.; Yu, Y.-S.; Tyliczszak, T.; Cabana, J.; Celestre, R.; Chao, W.; Kaznatcheev, K.; Kilcoyne, A. D.; Maia, F.; Marchesini, S., Chemical composition mapping with nanometre resolution by soft X-ray microscopy. *Nature Photonics* **2014**, *8* (10), 765-769, DOI 10.1038/nphoton.2014.207.
50. Ushizima, D. M.; Bale, H. A.; Bethel, E. W.; Ercius, P.; Helms, B. A.; Krishnan, H.; Grinberg, L. T.; Haranczyk, M.; Macdowell, A. A.; Odziomek, K.; Parkinson, D. Y.; Percian, T.; Ritchie, R. O.; Yang, C., Ideal: Images across domains, experiments, algorithms and learning. *Jom-Us* **2016**, *68* (11), 2963-2972, DOI 10.1007/s11837-016-2098-4.

51. De Groot, F. M. F.; Fuggle, J. C.; Thole, B. T.; Sawatzky, G. A., 2p X-ray absorption of 3d transition-metal compounds - an atomic multiplet description including the crystal-field. *Phys Rev B* **1990**, *42* (9), 5459-5468, DOI 10.1103/physrevb.42.5459.
52. Naftel, S. J.; Sham, T. K.; Yiu, Y. M.; Yates, B. W., Calcium l-edge xanes study of some calcium compounds. *J Synchrotron Radiat* **2001**, *8* (2), 255-257, DOI 10.1107/s0909049500019555.
53. Fleet, M. E.; Liu, X. Y., Calcium L_{2,3}-edge XANES of carbonates, carbonate apatite, and oldhamite (CAS). *Am Mineral* **2009**, *94* (8-9), 1235-1241, DOI 10.2138/am.2009.3228.
54. Ko, J. P., X-ray absorption near-edge structure (xanes) of calcium L_{3,2} edges of various calcium compounds and X-ray excited optical luminescence (xeol) studies of luminescent calcium compounds. *X-Ray Absorption Fine Structure--XAFS* **2007**, *13* (882), 538-540, DOI 10.1063/1.2644585.
55. Geng, G.; Li, J.; Yu, Y.-S.; Shapiro, D. A.; Kilcoyne, D. A.; Monteiro, P. J., Nanometer-resolved spectroscopic study reveals the conversion mechanism of CaO· Al₂O₃· 10H₂O to 2CaO· Al₂O₃· 8H₂O and 3CaO· Al₂O₃· 6H₂O at an elevated temperature. *Crystal Growth & Design* **2017**, *17* (8), 4246-4253, DOI 10.1021/acs.cgd.7b00553.
56. Mumme, W.; Hill, R.; Bushnell-Wye, G.; Segnit, E., Rietveld crystal structure refinements, crystal chemistry and calculated powder diffraction data for the polymorphs of dicalcium silicate and related phases. **1995**, *169* (1), 35-68 .
57. Merlino, S.; Bonaccorsi, E.; Armbruster, T., The real structure of tobermorite 11 angstrom: Normal and anomalous forms, od character and polytypic modifications. *Eur J Mineral* **2001**, *13* (3), 577-590, DOI 10.1127/0935-1221/2001/0013-0577.
58. Biagioni, C.; Merlino, S.; Bonaccorsi, E., The tobermorite supergroup: A new nomenclature. *Mineral Mag* **2015**, *79* (2), 485-495, DOI 10.1180/minmag.2015.079.2.22.
59. Skinner, L. B.; Chae, S. R.; Benmore, C. J.; Wenk, H. R.; Monteiro, P. J. M., Nanostructure of calcium silicate hydrates in cements. *Phys Rev Lett* **2010**, *104* (19), DOI 10.1103/physrevlett.104.195502.
60. Taylor, H. F. W.; Newbury, D. E., Calcium hydroxide distribution and calcium silicate hydrate composition in tricalcium silicate and beta-dicalcium silicate pastes. *Cement and Concrete Research* **1984**, *14* (1), 93-98, DOI 10.1016/0008-8846(84)90084-x.
61. Bae, S.; Taylor, R.; Hernandez-Cruz, D.; Yoon, S.; Kilcoyne, D.; Monteiro, P. J. M., Soft X-ray spectromicroscopic investigation of synthetic C-S-H and C₃S hydration products. *J Am Ceram Soc* **2015**, *98* (9), 2914-2920, DOI 10.1111/jace.13709.
62. Kirkpatrick, R. J.; Brown, G. E.; Xu, N.; Cong, X. D., Ca X-ray absorption spectroscopy of C-S-H and some model compounds. *Adv Cem Res* **1997**, *9* (33), 31-36, DOI 10.1680/adcr.1997.9.33.31.
63. Gartner, E.; Maruyama, I.; Chen, J., A new model for the csh phase formed during the hydration of portland cements. *Cement and Concrete Research* **2017**, *97*, 95-106, DOI 10.1016/j.cemconres.2017.03.001.

64. Li, D.; Bancroft, G. M.; Fleet, M. E.; Feng, X. H., Silicon k-edge xanes spectra of silicate minerals. *Phys Chem Miner* **1995**, 22 (2), 115-122, DOI 10.1007/bf00202471.
65. Fleet, M. E.; Muthupari, S.; Kasrai, M.; Prabakar, S., Sixfold coordinated si in alkali and alkali-CaO silicophosphate glasses by Si K-edge xanes spectroscopy. *J Non-Cryst Solids* **1997**, 220 (1), 85-92, DOI 10.1016/s0022-3093(97)00222-6.
66. Li, D.; Bancroft, G. M.; Kasrai, M.; Fleet, M. E.; Secco, R. A.; Feng, X. H.; Tan, K. H.; Yang, B. X., X-ray-absorption spectroscopy of silicon dioxide (SiO₂) polymorphs - the structural characterization of opal. *Am Mineral* **1994**, 79 (7-8), 622-632.
67. Cabaret, D.; Le Grand, M.; Ramos, A.; Flank, A. M.; Rossano, S.; Galois, L.; Calas, G.; Ghaleb, D., Medium range structure of borosilicate glasses from Si K-edge xanes: A combined approach based on multiple scattering and molecular dynamics calculations. *J Non-Cryst Solids* **2001**, 289 (1-3), 1-8, DOI 10.1016/s0022-3093(01)00733-5.
68. Geng, G.; Taylor, R.; Bae, S.; Hernandez-Cruz, D.; Kilcoyne, D. A.; Emwas, A. H.; Monteiro, P. J. M., Atomic and nano-scale characterization of a 50-year-old hydrated C₃S paste. *Cement and Concrete Research* **2015**, 77, 36-46, DOI 10.1016/j.cemconres.2015.06.010.
69. Soyer-Uzun, S.; Chae, S. R.; Benmore, C. J.; Wenk, H. R.; Monteiro, P. J. M., Compositional evolution of calcium silicate hydrate (C-S-H) structures by total x-ray scattering. *J Am Ceram Soc* **2012**, 95 (2), 793-798, DOI 10.1111/j.1551-2916.2011.04989.x.
70. Calas, G.; Brown, G. E.; Waychunas, G. A.; Petiau, J., X-ray absorption spectroscopic studies of silicate-glasses and minerals. *Phys Chem Miner* **1987**, 15 (1), 19-29, DOI 10.1007/bf00307604.
71. Nicoleau, L.; Bertolim, M. A., Analytical model for the alite (C₃S) dissolution topography. *J Am Ceram Soc* **2016**, 99 (3), 773-786, DOI 10.1111/jace.13647.
72. Durgun, E.; Manzano, H.; Pellenq, R. J. M.; Grossman, J. C., Understanding and controlling the reactivity of the calcium silicate phases from first principles. *Chemistry of Materials* **2012**, 24 (7), 1262-1267, DOI 10.1021/cm203127m.
73. Henderson, G. S., A Si K-edge EXAFS/XANES study of sodium-silicate glasses. *J Non-Cryst Solids* **1995**, 183 (1-2), 43-50, DOI 10.1016/0022-3093(94)00651-2.
74. Gursel, A. P.; Maryman, H.; Ostertag, C., A life-cycle approach to environmental, mechanical, and durability properties of "green" concrete mixes with rice husk ash. *J Clean Prod* **2016**, 112, 823-836, DOI 10.1016/j.jclepro.2015.06.029.
75. Ishida, H.; Okada, Y.; Mitsuda, T., Highly reactive β -dicalcium silicate: II, hydration behavior at 25 °C followed by ²⁹Si nuclear magnetic resonance. *J Am Ceram Soc* **1992**, 75 (2), 359-363, DOI 10.1111/j.1151-2916.1992.tb08187.x.
76. L'Hopital, E.; Lothenbach, B.; Scrivener, K.; Kulik, D. A., Alkali uptake in calcium alumina silicate hydrate (C-A-S-H) *Cement and Concrete Research* **2016**, 85, 122-136, DOI 10.1016/j.cemconres.2016.03.009.
77. Bae, S.; Taylor, R.; Shapiro, D.; Denes, P.; Joseph, J.; Celestre, R.; Marchesini, S.; Padmore, H.; Tyliczszak, T.; Warwick, T., Soft X-ray ptychographic imaging and

morphological quantification of calcium silicate hydrates (C-S-H). *J Am Ceram Soc* **2015**, 98 (12), 4090-4095, DOI 10.1111/jace.13808.

78. Ludwig, H.-M.; Zhang, W., Research review of cement clinker chemistry. *Cement and Concrete Research* **2015**, 78, 24-37, DOI 10.1016/j.cemconres.2015.05.018.

79. Richardson, I. G., The calcium silicate hydrates. *Cement and Concrete Research* **2008**, 38 (2), 137-158, DOI 10.1016/j.cemconres.2007.11.005.

SYNOPSIS

The atomic-scale and nano-scale structure of hydrated dicalcium silicate are studied, which may inspire the manufacture of cement with significantly lower CO₂ emission.

For Table of Contents Use Only