Direct Observation of Charge Transfer and Magnetism in Fe₄Co₄ Cyanide Bridged Molecular Cubes

Niéli Daffé,^{§,*} Juan-Ramón Jiménez,[¥] Michał Studniarek,[§] Amina Benchohra,[¥] Marie-Anne Arrio,[£] Rodrigue Lescouëzec,[¥] and Jan Dreiser^{§,*}

[§] Paul Scherrer Institut, CH-5232 Villigen PSI, Switzerland

[¥] Institut Parisien de Chimie Moléculaire, CNRS UMR 8232, Sorbonne Université, FR-75252 Paris cedex 05, France

[£] CNRS, Sorbonne Université/IRD/MNHN, UMR 7590, Institut de Minéralogie, de Physique des Matériaux et de Cosmochimie, IMPMC, 75252 Paris, France

Corresponding authors:

*Email addresses: nieli.daffe@psi.ch, jan.dreiser@psi.ch

This document is the accepted manuscript version of the following article:

Daffé, N., Jiménez, J. R., Studniarek, M., Benchohra, A., Arrio, M. A., Lescouëzec, R., & Dreiser, J. (2019). Direct observation of charge transfer and magnetism in Fe₄Co₄cyanide-bridged molecular cubes. *Journal of Physical Chemistry Letters*, 10(8), 1799–1804.
<https://doi.org/10.1021/acs.jpclett.8b03839>

ABSTRACT

We have studied the zero-dimensional cubane molecular correspondent of a Prussian blue analogue Cs-Fe₄Co₄ at low temperature and high magnetic field by means of L-edge X-ray absorption spectroscopy and X-ray magnetic circular dichroism. We probe the magnetic and electronic structures of Fe and Co separately upon light irradiation, which allows us to observe directly the electron transfer coupled to a spin transition (ETCST) phenomenon within the molecular cubes and to investigate the nature of the metastable photoexcited state. The magnetic moments in the photoexcited state are found to be $M = 1.3 \mu_B$ ($M_{\text{spin}} = 0.58 \mu_B$ with large orbital moment, $M_{\text{orbit}} = 0.74 \mu_B$) for low spin Fe^{III} and $M = 1.5 \mu_B$ ($M_{\text{spin}} = 1.07 \mu_B$ with orbital moment, $M_{\text{orbit}} = 0.41 \mu_B$) for high spin Co^{II} at 2 K and 6.8 T. From our results, we evidence that a strong magnetic coupling between the metal ions can be ruled out.

TOC GRAPHICS.

The photocontrol of the magnetic and optical properties of switchable compounds is of great interest in view of possible implementations as sensors, optical switches or memories in organic electronics devices.^{1–7} FeCo Prussian Blue Analogues⁸ (PBAs) are excellent candidate materials exhibiting a photoinduced metastable state as reported for the first time in the inorganic PBA polymer $\text{K}_{0.2}\text{Co}_{1.4}[\text{Fe}(\text{CN})_6] \cdot 6.9\text{H}_2\text{O}$.⁹ At the origin of the substantial changes of the magnetic properties in these three-dimensional networks of metallic ions connected by cyanide ligands, there is a metal-to-metal electron transfer within the Fe-CN-Co pairs associated with a spin transition of the Co ions, known as the electron transfer coupled to spin transition (ETCST) phenomenon.^{10,11} The ground state is formed from pairs of Co and Fe ions both in the t_{2g}^6 configuration. After the ETCST, in the excited state the formerly diamagnetic ($\text{Co}^{\text{III}}, t_{2g}^6, S = 0$) – ($\text{Fe}^{\text{II}}, t_{2g}^6, S = 0$) pairs are converted to the paramagnetic ($\text{Co}^{\text{II}}, t_{2g}^5 e_g^2, S = 3/2$) – ($\text{Fe}^{\text{III}}, t_{2g}^5, S = 1/2$) ones. A schematic representation of the ETCST process in FeCo 3D-PBA is depicted **Figure 1a**.

Lately, cyanide-bridged FeCo systems have attracted a renewed attention when the light-induced magnetic properties of PBAs were successfully transferred to discrete molecular FeCo models. First demonstrations include the report of thermally-induced ETCST in a Fe_2Co_3 pentanuclear complex¹² and the photomagnetic effect in a zero-dimensional molecular cube of Fe_4Co_4 was reported for the first time a decade ago.¹³ Since then, the many advantages of transferring the photomagnetic properties to zero-dimensional molecular systems were corroborated.^{14–20} These include less structural complexity than in 3D-PBAs facilitating rationalization and optimization of their magnetic properties, the availability of single crystals and good solubility. Similar to 3D-PBA, the light-induced properties of the molecular systems are also attributed to the mechanism of ETCST.

The characterizations of the metal-to-metal electron transfer processes are typically performed indirectly using magnetometry or X-ray structural analysis. In this respect, X-ray absorption spectroscopy (XAS) is a very powerful technique able to clarify the electronic structure of transition metals, including valence and spin states and crystal-field splitting by a direct observation of the $2p \rightarrow 3d$ dipole allowed transitions at the $L_{2,3}$ edges. The technique has been indeed successfully applied to examine the light-induced excited spin state trapping (LIESST) in spin-crossover complexes and PBA.^{21–24} The direct observation of ETCST in photomagnetic molecular complexes was reported by Sekine *et al.* who have investigated the thermal and X-ray induced conversion in Fe_2Co_2 cyanide bridge molecular squares using K-edge XAS.²⁵ Very recently, Jafri *et al.* have evidenced the occurrence of the thermal and light-induced electron transfer in a FeCo dinuclear complex using L-edge XAS and X-ray Magnetic Circular Dichroism (XMCD).²⁶ Another important unknown is the nature of the Fe-Co magnetic coupling in the photoinduced paramagnetic state of the molecular systems. While in 3D-PBA an antiferromagnetic coupling between the Co_{HS}^{II} and the Fe_{LS}^{III} was reported,²⁷ calculations on paramagnetic 1D FeCo chains²⁸ and on 0D FeCo square complexes²⁹ have demonstrated that intramolecular ferromagnetic exchange pathways may dominate in the lower dimensional systems.

In this study, we employ L-edge XAS and XMCD to examine the photomagnetic process in the discrete molecular heterocubane $Cs \subset \{[Fe^{II}(Tp)(CN)_3]_4 [Co^{III}(^{pz}Tp)]_3 [Co^{II}(^{pz}Tp)]\} \cdot 12CH_3CN$ cluster³⁰ (Tp = hydrotris(pyrazol-1-yl)borate; ^{pz}Tp = tetra(pyrazol-1-yl)borate), from here on referred to as $Cs-Fe_4Co_4$. This complex encapsulating an inserted alkali ion is the true representation of the elementary unit of the cubic Cs-FeCo 3D-PBA. Besides, the remarkable stability of these cubic molecules in solution allows to envision different solution processes for the surface deposition of these materials, which is of extreme importance for applications in molecular

electronics or spintronics devices. Taking advantage of the elemental selectivity of XAS, we follow the changes of the electronic structures of Fe and Co upon photoexcitation proving the concurrent electron transfer between these ions as well as the Co spin state change. Furthermore, we resolve the exact compositions of the ground state and of the metastable excited state with the support of ligand-field multiplet (LFM) calculations. To the best of our knowledge, we report for the first time a XAS and XMCD study of the photoinduced excited state in a Fe_4Co_4 cubane system. We exploit the magnetic sensitivity of XMCD as a local probe of the magnetic moments of the Fe and Co ions and to obtain insight into the possible magnetic coupling between the metallic centers in $\text{Cs-Fe}_4\text{Co}_4$.

Figure 1. (a) Schematic representation of the ETCST process in FeCo 3D-PBA. (b) Scheme of the XAS and XMCD experimental geometry (c) Ball-and-stick representation of $\text{Cs-Fe}_4\text{Co}_4$. Hydrogen atoms, solvent molecules, and Cs bonds are omitted for clarity. Color code: iron: orange, cobalt: blue, cesium: purple, nitrogen: light blue, carbon: grey, boron: pink. The scale bar has a length of 1 nm.

The neutral cyanide-bridged Fe_4Co_4 cage encapsulating a Cs^+ ion is depicted in **Figure 1b**. Details about the synthesis, magnetic and structural characterization of $\text{Cs-Fe}_4\text{Co}_4$ can be found in ref. 30. A solution of $\text{Cs-Fe}_4\text{Co}_4$ in dichloromethane ($c \sim 1 \text{ mM}$) was sprayed onto a gold-coated silicon substrate to obtain a homogeneous and clearly visible film of molecular deposit after the

evaporation of the solvent indicating a film thickness much larger than the probing depth of the total electron yield (TEY) detection of a few nanometers. No additional capping was used and a comparison of the XAS recorded on a polycrystalline sample revealed that the molecules are fully intact in the film (Supporting Information **Figure S1**). This finding is consistent with the stability of the molecules in solution as demonstrated in ref. 30. XAS and XMCD spectra were recorded at the X-Treme beamline of the Swiss Light Source.³¹ The sample was positioned so that the X-ray beam was incident at an angle of 30° from the sample surface as depicted in **Figure 1c**. XAS measurements were performed in total electron yield (TEY) mode with the magnetic field applied parallel to the beam propagation direction. A large spot size ($0.5 \times 2.5 \text{ mm}^2$) and a low photon flux were chosen to avoid radiation damage. The spectra were normalized to the maxima of the Fe or Co L_3 edges after subtraction of the background using a step function to allow a direct comparison with the simulations. A laser ($\lambda = 650 \text{ nm}$) with moderate intensity of $\sim 1 \text{ mW/mm}^2$ was used to photoexcite the molecules for a total of 3 hours. The sample was not exposed to X-rays before the laser irradiation at low temperature in order to minimize the X-ray induced conversion.²⁵

Fe and Co XAS recorded at 300 K before the irradiation and at 2 K after the laser irradiation are shown in **Figure 2**. Initially, the Fe L_3 edge exhibits a double-peak shape. After laser irradiation at 2 K, additional features appear including a broad shoulder at around 710.9 eV and a sharp peak at the lower energy of 705.8 eV. The Co L_3 edge displays one main peak at 779.7 eV and smaller contributions at 775.5 eV, 776.9 eV and 778.3 eV before laser irradiation. In contrast, after irradiation the contributions of features at lower energies prevail, while the peak at 779.7 eV is significantly reduced. Upon heating the sample to 300 K after the laser irradiation at low temperature the molecules relax to the ground state, since the molecules are trapped in the photoexcited state only up to a few tens of Kelvin. The ground state of $\text{Cs-Fe}_4\text{Co}_4$ is fully recovered

as shown by the overlap of the spectra acquired after warming up the sample and the ones recorded before irradiation at room temperature in **Figure 2**. The thermal reversibility which we evidenced by XAS is in good agreement with previous SQUID measurements described in ref. 30. Furthermore, it testifies to the absence of damage of the sample by the laser and X-ray irradiation. To deliberately check for the X-ray induced conversion we have measured in another experiment the X-ray spectra before laser irradiation at 2 K. This revealed the same spectral modifications due to photo-excitation by laser, but indicating a much slower conversion induced by X-ray induced conversion rate (*cf.* Supporting Information **Figure S2**).

Figure 2. Experimental XAS of the ground and excited states measured at the Fe $L_{2,3}$ edges (700 eV – 740 eV) and Co $L_{2,3}$ edges (770 eV- 805 eV) of $\text{Cs-Fe}_4\text{Co}_4$ and calculated best-fit curves. All fits exhibit a high coefficient of determination $0.86 \leq R^2 \leq 0.98$.

A more precise analysis and understanding of the X-ray spectra of the ground and excited states is obtained by comparison with theoretical spectra of multiplet features of $\text{Fe}_{\text{LS}}^{\text{III}}$, $\text{Fe}_{\text{LS}}^{\text{II}}$, $\text{Co}_{\text{LS}}^{\text{III}}$ and $\text{Co}_{\text{HS}}^{\text{II}}$ (LS: low spin and HS: high spin). Spectra were calculated using LFM theory as implemented in the QUANTY/CRISPY software package.^{32,33} In the molecular $\text{Cs-Fe}_4\text{Co}_4$ cubes, all metal ions

experience a slightly distorted octahedral coordination sphere with a pseudo C_3 axis along the boron-metal direction. In order to approximate this distorted octahedral (O_h) environment, the calculations are performed using a C_{3v} point symmetry, and the strength of the crystal field potential is therefore defined using three independent parameters Dq , $D\sigma$ and $D\tau$. Details on the parameters used are given in the Supporting Information (SI). The simulations of the Fe L-edge spectra were performed in order to match the ones of the mononuclear reference complexes $K_2[Fe^{II}(Tp)(CN)_3]$ and $NBu_4[Fe^{III}(Tp)(CN)_3]$ (see Supporting Information **Figures S3**) possessing well-known oxidation numbers. To reproduce the spectral shape of Fe_{LS}^{III} , the same parameters reported for the precursor $[TpFe^{III}CN_3]$ by Jafri and co-workers are used ($10Dq = 2.8$ eV; $D\sigma = 0.07$ eV, $D\tau = 0.12$ eV). The best simulation of $K_2[Fe^{II}(Tp)(CN)_3]$ is obtained by matching the same crystal field parameters than Fe^{III} modeled spectra for Fe^{II} ions with relatively strong cubic crystal field of 2.8 eV consistent with a LS state. The Fe L-edge spectrum measured on $Cs-Fe_4Co_4$ at 300 K before photoexcitation plotted in **Figure 2** is similar to the simulations obtained for Fe_{LS}^{II} . In contrast, the peak at 705.2 eV is the signature of Fe_{LS}^{III} , which is observed in the excited state of $Cs-Fe_4Co_4$. This peak is known to originate from the $2p^6t_{2g}^5 \rightarrow 2p^5t_{2g}^6$ transitions that are absent in the Fe_{LS}^{II} configuration.¹¹

Concerning the Co spectra, the peaks centered at 775.8 eV, 776.8 eV and 778.2 eV are fingerprints of Co^{II} in a sixfold coordination environment, while the signature of Co^{III} is characterized by peaks at 779.7 eV and 783.1 eV. The features corresponding to Co^{III} are shifted toward higher energies due to the shortening of the Co-ligand bonds as compared to Co^{II} . This well-defined separation in energy allows the comparison of the respective spectral features. The results obtained on the mononuclear reference compounds for Co^{II} and Co^{III} are presented and discussed in the SI **Figure S4**. The contributions of the Co^{II} ions are well modeled using the C_{3v}

symmetry, which takes into account the deviation from the octahedral (O_h) symmetry in the Cs-Fe₄Co₄ cubes. The $10Dq$, $D\sigma$ and $D\tau$ crystal field parameters were chosen according to the axial distortion factor ($\Delta = -922 \text{ cm}^{-1}$) previously reported and leading to the splitting of $^4T_{1g}$ ground state in O_h symmetry into the 4E_g and $^4A_{2g}$ states, separated by Δ (4E_g being the ground state). A value of $10Dq = 1.1 \text{ eV}$ is found for the Co^{II} ions in good agreement with the HS state. In contrast, the best simulation in the case of the Co^{III} ions corresponds to the higher $10Dq$ value of 3.0 eV consistent with to a LS state.

The straightforward comparison of typical spectral features of both Fe and Co ions in Cs-Fe₄Co₄ as visible in **Figure 2**, along with the LFM calculations described in the above, yields clear evidence of the occurrence of the light-induced excited state at 2 K. The spectra obtained after irradiation with the laser show an increase of the signatures of Co^{II}_{HS} and Fe^{III}_{LS} compared to the ground state at room temperature, which mainly includes Co^{III}_{LS} and Fe^{II}_{LS}. The signatures of Co^{III}_{LS} and Fe^{II}_{LS} in the excited state do not disappear completely, which indicates that the conversion is not complete for both Fe and Co ions. This is expected because of the initial presence of Co^{II} ions in the ground state which implies the presence of Fe^{II} ions in the excited state.

In order to extract quantitative information about the relative amount of Co^{II}/Co^{III} and Fe^{II}/Fe^{III}, linear combinations of the modeled spectra presented in **Figure 2** are used to visually fit the measurements obtained for Cs-Fe₄Co₄. We find 100% of Fe^{II}_{LS} and a mix of $16 \pm 1\%$ of Co^{II}_{HS} and $84 \pm 1\%$ of Co^{III}_{LS} in the ground state. The amount of Co^{II} in the ground state is lower than the 25% that were previously reported.³⁰ Due to the probing depth of TEY of a few nanometers, this result can be interpreted in terms of surface oxidation of part of the cubes. The excited state is composed of $52 \pm 1\%$ Fe^{II}_{LS} + $48 \pm 1\%$ Fe^{III}_{LS} on the one hand and $64 \pm 1\%$ of Co^{II}_{HS} + $36 \pm 1\%$ of Co^{III}_{LS}

on the other hand. As an additional confirmation, linear combinations of the reference compounds for Fe and Co ions can be found **Figures S5 and S6** in the SI and show very consistent results compared to the compositions obtained by multiplet calculations. From the compositions of the ground and excited states we conclude that 48 ± 1 % of $\text{Co}_{\text{LS}}^{\text{III}}$ are transformed into $\text{Co}_{\text{HS}}^{\text{II}}$ while 48 ± 1 % of the initial $\text{Fe}_{\text{LS}}^{\text{II}}$ ions in the ground state are oxidized toward $\text{Fe}_{\text{LS}}^{\text{III}}$ during the three hours of laser irradiation. These findings are perfectly consistent, and they demonstrate the concomitance of the Fe oxidation with the Co reduction. This is further supported by the observation of the XAS changes during the irradiation process. **Figure S7** in the SI shows the comparison of the variation of Co^{II} and Fe^{III} in time during laser irradiation, revealing similar time constants for Co and Fe extracted from monoexponential fits. Altogether, these results confirm the ETCST mechanism in the $\text{Cs-Fe}_4\text{Co}_4$ cubes to be at the origin of the simultaneous transformation of the Fe and Co oxidation states and the Co spin transition. As supported by **Figure S7**, the conversion is not complete after 3 hours of irradiation. This may be due to the 650 nm wavelength deviating from 800 nm for which a full conversion was reported in these compounds,¹⁸ and/or the presence of Co^{II} in the ground state preventing the electron-transfer of 16% of the Co-CN-Fe pairs.

Figure 3. Experimental and calculated XMCD spectra measured after laser excitation at 2 K (a) at the Fe $L_{2,3}$ edges and (b) at the Co $L_{2,3}$ edges in a magnetic field of 6.8 T and at 2 K. Symbols and solid lines denote experimental data and calculations, respectively. (c) Experimental, element specific and normalized $M(H)$ curves extracted from XMCD are plotted as symbols.

Beyond the averaged properties provided by SQUID magnetometry, XMCD helps to determine the local magnetic moments of the ions in the Cs-Fe₄Co₄ cages. XMCD spectra were recorded on the Cs-Fe₄Co₄ ground state at 200 K, well above the relaxation temperature of the system of ~ 66 K (see **Figure S8**). No XMCD signal is detected at 200 K at the Fe L_{2,3} edges. This is consistent with the above conclusion that the ground state contains solely LS Fe^{II}. In contrast, at the Co L_{2,3} edges, a clear dichroic signal of the order of 0.7% with respect to the main edge jump is detected, confirming that the ground state contains a minor contribution of Co^{II}_{HS} in line with the XAS analysis of the ground state. After laser irradiation at 2 K, the magnetic state of Cs-Fe₄Co₄ is considerably modified as shown by the XMCD signals reported in **Figure 3a-b**. Indeed, a significant XMCD signal is detected from Fe^{III}_{LS} together with a strong XMCD contribution of Co^{II}_{HS}, leading to 21% and 50% of signal normalized to the main edge jump, respectively. The XMCD is well reproduced by the calculations performed in C_{3v} point symmetry for Fe^{III} and Co^{II} (note that we obtained a zero XMCD signal in the calculations performed for Fe^{II} and Co^{III} in good agreement with the expected low spin state). From the LFM calculations, we extract the orbital and spin momentum expectation values for Fe (respectively for Co), which yields in the angular spherical average for a fully disordered sample $\langle L_z \rangle / \hbar = -0.741$ (resp. -0.410), $\langle S_z \rangle / \hbar = -0.293$ (resp. -0.538) and a magnetic dipole strength of $\langle T_z \rangle / \hbar = -0.069$ (resp. -0.008). These values give rise to the spin and orbital magnetic moments in the photoexcited state of $M_{\text{spin}} = 0.59 \mu_B$ and a large orbital moment of $M_{\text{orbit}} = 0.74 \mu_B$ for Fe^{III}_{LS}, and $M_{\text{spin}} = 1.08 \mu_B$ with the orbital moment of $M_{\text{orbit}} = 0.41 \mu_B$ for Co^{II}_{HS} at 2 K and 6.8 T. From the comparison of the experimental XMCD signals (mainly negative) with the calculated ones with the magnetic field set along the C_{3v} axis one finds that the observed Co and Fe magnetic moments are both oriented parallel to the external magnetic field at 6.8 T. In order to investigate further the magnetic coupling between the ions, we have

obtained the field dependent magnetization for both Fe and Co from XMCD, as shown in **Figure 3c** in the paramagnetic excited state. **Figure 3c** shows a superposition of the element-specific magnetization curves $M(H)$ which do not saturate at 6.8 T. This clearly demonstrates the absence of a significant antiferromagnetic coupling between the metal ions in the paramagnetic excited state. This result contrasts with the previous studies, which have demonstrated a strong antiferromagnetic coupling between Co and Fe in PBA 3D networks. Recently reported XMCD measurements of the dinuclear FeCo complex have led to similar conclusions.²⁶ A ferromagnetic coupling cannot be excluded,^{28,35,36} however, from the current set of data it is not possible to discriminate between a ferromagnetic Fe-Co exchange interaction and a paramagnetic behavior of the ions with their spins aligned along the direction of the magnetic field applied. The competition between the local anisotropy observed through the large orbital moments carried by the Fe^{III} and Co^{II} ions and the weak antiferromagnetic coupling make the determination of the coupling tricky. As a rough approximation, considering the Heisenberg-Dirac Hamiltonian $\hat{H}^{spin} = -J \cdot \vec{S}_{Fe} \cdot \vec{S}_{Co}$ and by comparison with the temperature in the experiment we estimate a lower bound for the Fe-Co superexchange coupling of $J \gtrsim -0.5 \text{ cm}^{-1}$. This can be interpreted in that a very weak antiferromagnetic coupling, no coupling or a ferromagnetic coupling are consistent with our observations. A strong antiferromagnetic coupling can be ruled out with certainty.

In summary, using L-edge XAS as an element-specific probe of the valence and spin states of Fe and Co ions in Cs-Fe₄Co₄ discrete molecular cubes we have observed directly the concurrent electronic and magnetic changes of both types of ions upon light irradiation. These results demonstrate beyond the shadow of doubt the existence of the light-induced ETCST process and its thermal relaxation in the molecular cages. The XMCD measurements directly reveal a parallel arrangement of the Fe and Co spins in the photoexcited state at 2 K for all applied magnetic field

values. Furthermore, XMCD rules out the possibility of a strong antiferromagnetic coupling. Our study paves the way toward the integration of the present Cs-Fe₄Co₄ cages, featuring excellent photomagnetic properties and a high solubility, into organic electronics devices.

ASSOCIATED CONTENT

Supporting Information: Crystal field multiplet calculations; best-fit parameters of the LFM calculations; expectation values of orbital and spin angular momentum and magnetic dipole operators; coefficient of determination; spectra of Fe and Co for the polycrystalline and the drop-cast samples; X-ray induced conversion effect at 2 K; reference spectra of Fe and best fits; reference spectra of Co and best fits; linear combinations of the reference spectra of Fe; linear combinations of the reference spectra of Co; time dependence of Fe^{III} and Co^{II} spectral features during laser irradiation; XMCD of Fe and Co measured at 200 K.

ACKNOWLEDGMENTS

The authors thank Stefan Zeugin for his technical support during the experiments. Furthermore, the authors thank Marius Retegan for his help with the CRISPY software. Funding from the European Union's Horizon 2020 research and innovation programme under the Marie Skłodowska-Curie grant agreement No 701647 (M.S.) and from the Swiss National Science Foundation (grant nos. 200021_165774/1 and 200020_182599/1, M.S., N.D. and J.D.) and from the Centre National de la Recherche Scientifique (CNRS, France) (M.-A.A.) are acknowledged.

REFERENCES

- (1) Sato, O.; Tao, J.; Zhang, Y.-Z. Control of Magnetic Properties through External Stimuli. *Angew. Chem. Int. Ed.* **2007**, 46 (13), 2152–2187.

- (2) Li J.; Qiu J.-D.; Xu J.-J.; Chen H.-Y.; Xia X.-H. The Synergistic Effect of Prussian-Blue-Grafted Carbon Nanotube/Poly(4-vinylpyridine) Composites for Amperometric Sensing. *Adv. Funct. Mater.* **2007**, *17* (9), 1574–1580.
- (3) Létard, J.-F.; Guionneau, P.; Goux-Capes, L. Towards Spin Crossover Applications. In *Spin Crossover in Transition Metal Compounds III*; Gülich, P., Goodwin, H. A., Eds.; Topics in Current Chemistry; Springer Berlin Heidelberg: Berlin, Heidelberg, 2004; pp 221–249.
- (4) Ricci, F.; Palleschi, G. Sensor and Biosensor Preparation, Optimisation and Applications of Prussian Blue Modified Electrodes. *Biosens. Bioelectron.* **2005**, *21* (3), 389–407.
- (5) Karyakin, A. A.; Puganova, E. A.; Budashov, I. A.; Kurochkin, I. N.; Karyakina, E. E.; Levchenko, V. A.; Matveyenko, V. N.; Varfolomeyev, S. D. Prussian Blue Based Nanoelectrode Arrays for H₂O₂ Detection. *Anal. Chem.* **2004**, *76* (2), 474–478.
- (6) Kahn, O.; Kröber, J.; Jay, C. Spin Transition Molecular Materials for Displays and Data Recording. *Adv. Mater.* **1992**, *4* (11), 718–728.
- (7) Kahn, O.; Martinez, C. J. Spin-Transition Polymers: From Molecular Materials Toward Memory Devices. *Science* **1998**, *279* (5347), 44–48.
- (8) Keggin, J. F.; Miles, F. D. Structures and Formulæ of the Prussian Blues and Related Compounds. *Nature* **1936**, *137* (3466), 577–578.
- (9) Sato, O.; Iyoda, T.; Fujishima, A.; Hashimoto, K. Photoinduced Magnetization of a Cobalt-Iron Cyanide. *Science* **1996**, *272* (5262), 704.
- (10) Tokoro, H.; Ohkoshi, S. Novel Magnetic Functionalities of Prussian Blue Analogs. *Dalton Trans.* **2011**, *40* (26), 6825.
- (11) Bleuzen, A.; Lomenech, C.; Escax, V.; Villain, F.; Varret, F.; Cartier dit Moulin, C.; Verdaguer, M. Photoinduced Ferrimagnetic Systems in Prussian Blue Analogues Cl_xCo₄[Fe(CN)₆]_y (Cl = Alkali Cation). 1. Conditions to Observe the Phenomenon. *J. Am. Chem. Soc.* **2000**, *122* (28), 6648–6652.
- (12) Berlinguette, C. P.; Dragulescu-Andrasi, A.; Sieber, A.; Galán-Mascarós, J. R.; Güdel, H.-U.; Achim, C.; Dunbar, K. R. A Charge-Transfer-Induced Spin Transition in the Discrete Cyanide-Bridged Complex {[Co(Tmphen)₂]₃[Fe(CN)₆]₂}. *J. Am. Chem. Soc.* **2004**, *126* (20), 6222–6223.
- (13) Li, D.; Clérac, R.; Roubeau, O.; Harté, E.; Mathonière, C.; Le Bris, R.; Holmes, S. M. Magnetic and Optical Bistability Driven by Thermally and Photoinduced Intramolecular Electron Transfer in a Molecular Cobalt–Iron Prussian Blue Analogue. *J. Am. Chem. Soc.* **2008**, *130* (1), 252–258.
- (14) Koumoussi, E. S.; Jeon, I.-R.; Gao, Q.; Dechambenoit, P.; Woodruff, D. N.; Merzeau, P.; Buisson, L.; Jia, X.; Li, D.; Volatron, F.; et al. Metal-to-Metal Electron Transfer in Co/Fe Prussian Blue Molecular Analogues: The Ultimate Miniaturization. *J. Am. Chem. Soc.* **2014**, *136* (44), 15461–15464.
- (15) Garnier, D.; Jiménez, J.-R.; Li, Y.; Bardeleben, J. von; Journaux, Y.; Augenstein, T.; B. Moos, E. M.; T. Gamer, M.; Breher, F.; Lescouëzec, R. K⁺ {[Fe^{II}(Tp)(CN)₃]₄ [Co^{III}(PzTp)]₃[Co^{II}(PzTp)]}: A Neutral Soluble Model Complex of Photomagnetic Prussian Blue Analogues. *Chem. Sci.* **2016**, *7* (8), 4825–4831.
- (16) Li, D.; Parkin, S.; Wang, G.; Yee, G. T.; Clérac, R.; Wernsdorfer, W.; Holmes, S. M. An *S* = 6 Cyanide-Bridged Octanuclear Fe^{III}₄Ni^{II}₄ Complex That Exhibits Slow Relaxation of the Magnetization. *J. Am. Chem. Soc.* **2006**, *128* (13), 4214–4215.

- (17) Zhang Yuanzhu; Li Dongfeng; Clérac Rodolphe; Kalisz Marguerite; Mathonière Corine; Holmes Stephen M. Reversible Thermally and Photoinduced Electron Transfer in a Cyano-Bridged $\{\text{Fe}_2\text{Co}_2\}$ Square Complex. *Angew. Chem.* **2010**, *122* (22), 3840–3844.
- (18) Mondal, A.; Li, Y.; Seuleiman, M.; Julve, M.; Toupet, L.; Buron-Le Cointe, M.; Lescouëzec, R. On/Off Photoswitching in a Cyanide-Bridged $\{\text{Fe}_2\text{Co}_2\}$ Magnetic Molecular Square. *J. Am. Chem. Soc.* **2013**, *135* (5), 1653–1656.
- (19) Shiga, T.; Tetsuka, T.; Sakai, K.; Sekine, Y.; Nihei, M.; Newton, G. N.; Oshio, H. Cyanide-Bridged Decanuclear Cobalt–Iron Cage. *Inorg. Chem.* **2014**, *53* (12), 5899–5901.
- (20) Nihei, M.; Ui, M.; Hoshino, N.; Oshio, H. Cyanide-Bridged Iron(II,III) Cube with Multisteped Redox Behavior. *Inorg. Chem.* **2008**, *47* (14), 6106–6108.
- (21) Cartier dit Moulin, C.; Villain, F.; Bleuzen, A.; Arrio, M.-A.; Saintavit, P.; Lomenech, C.; Escax, V.; Baudalet, F.; Dartyge, E.; Gallet, J.-J.; et al. Photoinduced Ferrimagnetic Systems in Prussian Blue Analogues $\text{Cl}_x\text{Co}_4[\text{Fe}(\text{CN})_6]_y$ (Cl = Alkali Cation). 2. X-Ray Absorption Spectroscopy of the Metastable State. *J. Am. Chem. Soc.* **2000**, *122* (28), 6653–6658.
- (22) Bleuzen, A.; Lomenech, C.; Dolbecq, A.; Villain, F.; Goujon, A.; Roubeau, O.; Nogues, M.; Varret, F.; Baudalet, F.; Dartyge, E.; et al. Photo-Induced Electron Transfer and Magnetic Switching in CoFe Cyanides: Study of the Metastable State. *Mol. Cryst. Liq. Cryst. Sci. Technol. Sect. Mol. Cryst. Liq. Cryst.* **1999**, *335* (1), 253–262.
- (23) Lee, J.-J.; Sheu, H.; Lee, C.-R.; Chen, J.-M.; Lee, J.-F.; Wang, C.-C.; Huang, C.-H.; Wang, Y. X-Ray Absorption Spectroscopic Studies on Light-Induced Excited Spin State Trapping of an Fe(II) Complex. *J. Am. Chem. Soc.* **2000**, *122* (24), 5742–5747.
- (24) Jesús Luque, F.; Agnieszka Kowalik, I.; Pablo Prieto-Ruiz, J.; Ángel Niño, M.; Prima-García, H.; Manuel Romero, F.; Arvanitis, D.; Coronado, E.; Miranda, R.; Miguel, J. J. de. Magnetic Ordering in an $(\text{Fe}_{0.2}\text{Cr}_{0.8})_{1.5}[\text{Cr}(\text{CN})_6]$ Prussian Blue Analogue Studied with Synchrotron Radiation Based Spectroscopies. *J. Mater. Chem. C* **2018**, *6* (30), 8171–8186.
- (25) Sekine, Y.; Nihei, M.; Kumai, R.; Nakao, H.; Murakami, Y.; Oshio, H. X-Ray-Induced Phase Transitions by Selective Excitation of Heterometal Ions in a Cyanide-Bridged Fe–Co Molecular Square. *Chem. Commun.* **2014**, *50* (31), 4050–4052.
- (26) Jafri, S. F.; Koumoussi, E. S.; Arrio, M.-A.; Juhin, A.; Mitcov, D.; Rouzières, M.; Dechambenoit, P.; Li, D.; Otero, E.; Wilhelm, F.; et al. Atomic Scale Evidence of the Switching Mechanism in a Photomagnetic CoFe Dinuclear Prussian Blue Analogue. *J. Am. Chem. Soc.* **2019**, *141* (8), 3470–3479.
- (27) Champion, G.; Escax, V.; Cartier dit Moulin, C.; Bleuzen, A.; Villain, F.; Baudalet, F.; Dartyge, E.; Verdaguer, M. Photoinduced Ferrimagnetic Systems in Prussian Blue Analogues $\text{C}^I_x\text{Co}_4[\text{Fe}(\text{CN})_6]_y$ (C^I = Alkali Cation). 4. Characterization of the Ferrimagnetism of the Photoinduced Metastable State in $\text{Rb}_{1.8}\text{Co}_4[\text{Fe}(\text{CN})_6]_{3.3} \cdot 13\text{H}_2\text{O}$ by K Edges X-Ray Magnetic Circular Dichroism. *J. Am. Chem. Soc.* **2001**, *123* (50), 12544–12546.
- (28) Lescouëzec, R.; Vaissermann, J.; Ruiz-Pérez, C.; Lloret, F.; Carrasco, R.; Julve, M.; Verdaguer, M.; Dromzee, Y.; Gatteschi, D.; Wernsdorfer, W. Cyanide-Bridged Iron(III)–Cobalt(II) Double Zigzag Ferromagnetic Chains: Two New Molecular Magnetic Nanowires. *Angew. Chem. Int. Ed.* **2003**, *42* (13), 1483–1486.
- (29) Pardo, E.; Verdaguer, M.; Herson, P.; Rousselière, H.; Cano, J.; Julve, M.; Lloret, F.; Lescouëzec, R. Synthesis, Crystal Structures, and Magnetic Properties of a New Family of Heterometallic Cyanide-Bridged $\text{Fe}^{\text{III}}_2\text{M}^{\text{II}}_2$ (M = Mn, Ni, and Co) Square Complexes. *Inorg. Chem.* **2011**, *50* (13), 6250–6262.

- (30) Jiménez, J.-R.; Tricoire, M.; Garnier, D.; Chamoreau, L.-M.; Bardeleben, J. von; Journaux, Y.; Li, Y.; Lescouëzec, R. A New $\{\text{Fe}_4\text{Co}_4\}$ Soluble Switchable Nanomagnet Encapsulating Cs^+ : Enhancing the Stability and Redox Flexibility and Tuning the Photomagnetic Effect. *Dalton Trans.* **2017**, 46 (44), 15549–15557.
- (31) Piamonteze, C.; Flechsig, U.; Rusponi, S.; Dreiser, J.; Heidler, J.; Schmidt, M.; Wetter, R.; Calvi, M.; Schmidt, T.; Pruchova, H.; et al. X-Treme Beamline at SLS: X-Ray Magnetic Circular and Linear Dichroism at High Field and Low Temperature. *J. Synchrotron Radiat.* **2012**, 19 (5), 661–674.
- (32) Retegan, M. Crispy <https://zenodo.org/badge/latestdoi/53660512> (accessed Mar 14, 2019).
- (33) Haverkort, M. W.; Zwierzycki, M.; Andersen, O. K. Multiplet Ligand-Field Theory Using Wannier Orbitals. *Phys. Rev. B* **2012**, 85 (16), 165113.
- (34) Hocking, R. K.; Wasinger, E. C.; de Groot, F. M. F.; Hodgson, K. O.; Hedman, B.; Solomon, E. I. Fe L-Edge XAS Studies of $\text{K}_4[\text{Fe}(\text{CN})_6]$ and $\text{K}_3[\text{Fe}(\text{CN})_6]$: A Direct Probe of Back-Bonding. *J. Am. Chem. Soc.* **2006**, 128 (32), 10442–10451.
- (35) Jafri, S. F.; Arrio, M.-A.; Bordage, A.; Moulin, R.; Juhin, A.; Cartier dit Moulin, C.; Otero, E.; Ohresser, P.; Bleuzen, A.; Saintavit, P. Weak Ferromagnetic Interaction at the Surface of the Ferrimagnetic $\text{Rb}_2\text{Co}_4[\text{Fe}(\text{CN})_6]_{3.3} \cdot 11\text{H}_2\text{O}$ Photoexcited State. *Inorg. Chem.* **2018**, 57 (13), 7610–7619.
- (36) Marilena Toma, L.; Lescouëzec, R.; Lloret, F.; Julve, M.; Vaissermann, J.; Verdaguer, M. Cyanide-Bridged Fe(III)–Co(II) Bis Double Zigzag Chains with a Slow Relaxation of the Magnetisation. *Chem. Commun.* **2003**, 0 (15), 1850–1851.