Negative-vector-chirality 120° spin structure in the defect- and distortion-free quantum kagome antiferromagnet $\text{YCu}_3(\text{OH})_6\text{Cl}_3$

A. Zorko^{1,*}, M. Pregelj¹, M. Gomilšek^{1,2}, M. Klanjšek¹, O. Zaharko³, W. Sun⁴, and J.-X. Mi⁴¹Jožef Stefan Institute, Jamova c. 39, SI-1000 Ljubljana, Slovenia²Centre for Materials Physics, Durham University, South Road, Durham DH1 3LE, United Kingdom³Laboratory for Neutron Scattering, Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland⁴Fujian Provincial Key Laboratory of Advanced Materials, Department of Materials Science and Engineering, College of Materials, Xiamen University, Xiamen 361005, Fujian Province, People's Republic of China

(Received 12 July 2019; revised manuscript received 6 September 2019; published 14 October 2019)

The magnetic ground state of the ideal quantum kagome antiferromagnet (QKA) has been a long-standing puzzle, mainly because perturbations to the nearest-neighbor isotropic Heisenberg Hamiltonian can lead to various fundamentally different ground states. Here we investigate a recently synthesized QKA representative, $\text{YCu}_3(\text{OH})_6\text{Cl}_3$, in which perturbations commonly present in real materials, like lattice distortion and intersite ion mixing, are absent. Nevertheless, this compound enters a long-range magnetically ordered state below $T_N = 15$ K. Our powder neutron diffraction experiment reveals that its magnetic structure corresponds to a coplanar 120° state with negative vector spin chirality. The ordered magnetic moments are suppressed to $0.42(2)\mu_B$, which is consistent with the previously detected spin dynamics persisting to the lowest experimentally accessible temperatures. This indicates either a coexistence of magnetic order and disorder or the presence of strong quantum fluctuations in the ground state of $\text{YCu}_3(\text{OH})_6\text{Cl}_3$. The origin of the magnetic order is sought in terms of Dzyaloshinskii-Moriya magnetic anisotropy and further-neighbor isotropic exchange interactions.

DOI: [10.1103/PhysRevB.100.144420](https://doi.org/10.1103/PhysRevB.100.144420)

I. INTRODUCTION

The two-dimensional quantum kagome antiferromagnet (QKA) is a paradigm of geometrical frustration. It has been intensively studied in the last two decades, mainly because the properties of its predicted spin-liquid ground state turned out to be extremely puzzling [1–3]. Due to the lack of proper approximations it remains unclear, even in theory, whether this state should be gapped or gapless [4–9]. Moreover, various perturbations to the nearest-neighbor isotropic Heisenberg Hamiltonian, like structural distortion and disorder-induced randomness [10–12], interlayer [13] and further-neighbor [14–21] exchange interaction, and magnetic anisotropy [12,20–29], may all play an important role in stabilizing very different ground states, from spin liquids and valence-bond solids to magnetically ordered states. Experimentally, these perturbations usually cannot be controlled in a given material and are rather poorly determined [30]. Therefore, experimental realizations of the QKA model, where such perturbations are minimized and limited in number, are of paramount importance.

The recently synthesized $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ compound [31] features a perfect-symmetry kagome lattice of Cu^{2+} ($S = 1/2$) ions (Fig. 1). This avoids the issue of reduced symmetry present in some QKA representatives, including the paradigmatic herbertsmithite [30], where a subtle lattice distortion was found at low temperatures [32]. Most QKA representatives, including herbertsmithite, also suffer from strong

intersite ion disorder, leading to the famous QKA impurity problem [30,33]. Due to the very large size of the Y^{3+} ions there is no detectable intersite ion disorder present in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ [31]. Hence, because of its much lower level of perturbations compared to the ideal isotropic Heisenberg Hamiltonian, $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ was initially expected to provide novel insight into the pressing issue of the spin-liquid ground state of the QKA model. Indeed, after the first bulk magnetic characterizations this system was suggested as a new promising spin-liquid candidate since no strong anomalies were detected in either its magnetization [31] or its heat capacity [34] down to the lowest accessible temperatures despite its sizable Weiss temperature of -99 K [31].

However, more sensitive local-probe muon spin relaxation (μSR) measurements have recently disclosed static internal magnetic fields that develop in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ below $T_N = 15$ K [35,36]. The magnetic ordering at T_N is, in fact, also witnessed in an increase of the bulk magnetization below T_N and in heat capacity as a broad maximum at T_N [35]. However, the order appears to be rather unconventional, as it progressively sets in and is fully established over the whole sample only for $T \lesssim T_N/3$ [35]. Moreover, persistent spin dynamics was detected by μSR at temperatures as low as $T/T_N = 1/300$ [35]. This might have various origins, including emergent spin excitations of correlated spin-loop structures [37] and fragmentation of magnetic moments into an ordered and a fluctuating part, e.g., as proposed for some partially ordered magnetic states on the kagome lattice [26] and for incommensurate ordered states [38].

The fundamental question of why $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ has a magnetically ordered ground state instead of a spin liquid

*andrej.zorko@ijs.si

FIG. 1. A perfect kagome lattice (lines) of Cu^{2+} spin-1/2 ions (orange) is established in the ab plane of the $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ compound. The Y^{3+} , O^{2-} , H^+ , and Cl^- ions are shown in gray, red, turquoise, and green, respectively. A coplanar magnetic structure (arrows) with negative vector spin chirality corresponding to the magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$ and an average magnetic moment of $\mu = 0.42(2)\mu_B$ per Cu^{2+} site is established below $T_N = 15$ K.

needs to be addressed, even more so because the number of relevant perturbations to the isotropic nearest-neighbor Heisenberg Hamiltonian is substantially reduced in this compound, making it closer to the ideal QKA than most of the known spin-liquid QKA representatives. In order to be able to address this important question, a proper characterization of the magnetic order is required, which calls for complementary experiments, like neutron diffraction. We note that an earlier neutron diffraction experiment failed to detect any magnetic Bragg peaks [36]. It needs to be stressed, though, that the experiment was focused on structural refinement and was therefore quite coarse in resolution. Here we report the results of a neutron diffraction study with much better resolution and statistics, which provides clear evidence for the appearance of magnetic Bragg peaks below T_N . These are assigned to a uniform 120° magnetic order with negative vector spin chirality (Fig. 1), magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$, and an average ordered magnetic moment of $\mu = 0.42(2)\mu_B$ at 1.5 K. The origin of this magnetic order is discussed in terms of magnetic anisotropy and exchange interactions beyond the nearest-neighbor Heisenberg exchange.

II. EXPERIMENTAL DETAILS

Powder neutron diffraction was performed on the DMC powder diffractometer at the Paul Scherrer Institute, Villigen, Switzerland; 2.3 g of sample were put in an Al sample can measuring 6 mm in diameter. The measurements were performed at 1.5 and 20 K at a fixed incoming-neutron energy corresponding to a wavelength of $\lambda = 4.506$ Å. The high

FIG. 2. (a) The neutron diffraction pattern of $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ taken at 20 K. The calculation is based on the $P\bar{3}m1$ space group with trigonal symmetry that accounts well for the crystal structure. The difference between the observed and the calculated diffraction patterns is displaced vertically for clarity. (b) The additional (magnetic) Bragg peaks that appear below $T_N = 15$ K are marked by arrows in the data set taken at 1.5 K. Here the data set taken at 20 K is translated vertically for clarity.

background in the neutron diffraction patterns is due to strong incoherent scattering from the hydrogen nuclei present in the sample. In order to detect weak magnetic Bragg reflections, high-statistics runs were collected, with a measurement time of 60 h at each temperature. All measurements were performed on a sample from the same batch as the one used in our previous μSR investigation [35].

III. RESULTS

The neutron diffraction pattern above T_N (at 20 K) can be perfectly reproduced using the trigonal crystal-structure model with $P\bar{3}m1$ symmetry (space group No. 164) initially found by Sun *et al.* using x-ray diffraction (XRD) [31]. Due to the high sensitivity of neutrons to light nuclei, the position of the hydrogen atoms is better determined here than in the previous XRD study. The good agreement between the model and our measurements shown in Fig. 2(a) confirms the high quality of our sample. The refined parameters of the crystal structure are summarized in Table I. They are consistent with the previously published XRD results at higher temperature [31] and the recently published neutron diffraction results

TABLE I. Fractional atomic coordinates and lattice parameters of $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ measured at 20 K within the space group $P\bar{3}m1$ (No. 164). The refinement was performed using the FULLPROF SUITE [39]. Lattice constants are $a = 6.7474(1) \text{ \AA}$, $c = 5.5905(1) \text{ \AA}$, $\alpha = \beta = 90^\circ$ $\gamma = 120^\circ$.

Atom	Wyckoff	Site	x	y	z	Occupancy
Y11	1b	$\bar{3}m.$	0.0000	0.0000	0.5000	0.95(5)
Y12	2c	$3m.$	0.0000	0.0000	0.378 (fixed)	0.05(5)
Cu	3f	$.2/m.$	0.5000	0.5000	0.5000	1
Cl1	2d	$3m.$	0.3333	0.6667	0.8668(5)	1
Cl2	1a	$\bar{3}m.$	0.0000	0.0000	0.0000	1
O	6i	$.m.$	0.1899(9)	0.3899(18)	0.3624(3)	1
H	6i	$.m.$	0.2058(8)	0.4118(16)	0.1920(6)	1

obtained at 1.6 K [36]. The precision of some of the derived crystal-structure parameters is not very high, as the focus of our study was on the magnetic order, which is why a large wavelength of the incoming neutrons was chosen. This allowed for better sensitivity at low q , where weak magnetic reflections were expected to appear. As a result, the occupancy of sites Y11 and Y12 have significant uncertainties. In fact, refinement with a single Y site at Wyckoff position 1b yields only a slightly worse R_F factor of 0.79 compared to the value of 0.76 obtained for two sites. This is consistent with recent neutron diffraction experiment that suggested the presence of a single Y site [36].

The diffraction pattern below T_N (at 1.5 K) reveals the emergence of additional weak Bragg reflections, highlighted by arrows in Fig. 2(b), while the dominant reflections already present above T_N are unchanged. As there is no structural transition in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ at least down to 1.6 K [36], these new reflections are a fingerprint of long-range magnetic order appearing below T_N . The positions of the magnetic reflections correspond to the magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$, signifying a ($q = 0$)-type magnetic structure [14] within the ab kagome planes and the antiferromagnetic nature of the magnetic order between neighboring kagome planes. The comparable width of the magnetic and the structural

Bragg reflections reveals that the correlation length of the magnetic order is very large.

We tackle the problem of determining the magnetic structure in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ within the framework of representation analysis [40], using the FULLPROF SUITE [39]. This analysis reveals that the little group for the propagation vector $\mathbf{k} = (0, 0, 0.5)$ has six irreducible representations (irreps) Γ_i . From these only three occur at the Cu^{2+} crystallographic site (Wyckoff position 3f), where the magnetic representation Γ is decomposed as

$$\Gamma = 0\Gamma_1 + 2\Gamma_2 + 0\Gamma_3 + 1\Gamma_4 + 3\Gamma_5 + 0\Gamma_6. \quad (1)$$

According to Landau's theory of second-order phase transition, the magnetic structure can correspond to only one of the three nonzero irreps [40]: either the one-dimensional Γ_2 or Γ_4 or the two-dimensional Γ_5 . The normalized basis vectors ψ_i^j for these representations are given in Table II. Here the index i corresponds to a specific irrep, while the index j counts its $d_i \cdot n_i$ basis vectors, where d_i is the dimensionality of Γ_i and n_i is its multiplicity in the decomposition given by Eq. (1). The corresponding spin structures are shown in Fig. 3. For Γ_5 where the basis vectors are complex and three pairs related by complex conjugation can be formed, we

TABLE II. The basis vectors ψ_i^j of the irreducible representations (irreps) Γ_2 , Γ_4 , and Γ_5 of the space group $P\bar{3}m1$ for the magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$ occurring in the magnetic representation at the magnetic site $(1/2, 1/2, 1/2)$ of atom 1 and its two crystallographically equivalent sites. The representation analysis was performed using the BASIREPS program incorporated in the FULLPROF SUITE [39]. The listed basis vectors are scaled to yield normalized magnetic moments in the complex plane.

irrep	Basis vector	Atom 1			Atom 2			Atom 3		
		m_a	m_b	m_c	m_a	m_b	m_c	m_a	m_b	m_c
Γ_2	ψ_2^1	$\frac{1}{\sqrt{3}}$	$-\frac{1}{\sqrt{3}}$	0	$\frac{1}{\sqrt{3}}$	$\frac{2}{\sqrt{3}}$	0	$-\frac{2}{\sqrt{3}}$	$-\frac{1}{\sqrt{3}}$	0
	ψ_2^2	0	0	1	0	0	1	0	0	1
Γ_4	ψ_4^1	1	1	0	-1	0	0	0	-1	0
Γ_5	ψ_5^1	1	0	0	0	$-\frac{1}{2} - i\frac{\sqrt{3}}{2}$	0	$\frac{1}{2} - i\frac{\sqrt{3}}{2}$	$\frac{1}{2} - i\frac{\sqrt{3}}{2}$	0
	ψ_5^2	0	1	0	$\frac{1}{2} + i\frac{\sqrt{3}}{2}$	$\frac{1}{2} + i\frac{\sqrt{3}}{2}$	0	$-\frac{1}{2} + i\frac{\sqrt{3}}{2}$	0	0
	ψ_5^3	0	0	1	0	0	$-\frac{1}{2} - i\frac{\sqrt{3}}{2}$	0	0	$-\frac{1}{2} + i\frac{\sqrt{3}}{2}$
	ψ_5^4	0	-1	0	$-\frac{1}{2} + i\frac{\sqrt{3}}{2}$	$-\frac{1}{2} + i\frac{\sqrt{3}}{2}$	0	$\frac{1}{2} + i\frac{\sqrt{3}}{2}$	0	0
	ψ_5^5	-1	0	0	0	$\frac{1}{2} - i\frac{\sqrt{3}}{2}$	0	$-\frac{1}{2} - i\frac{\sqrt{3}}{2}$	$-\frac{1}{2} - i\frac{\sqrt{3}}{2}$	0
	ψ_5^6	0	0	1	0	0	$-\frac{1}{2} + i\frac{\sqrt{3}}{2}$	0	0	$-\frac{1}{2} - i\frac{\sqrt{3}}{2}$

FIG. 3. The spin structures corresponding to the basis vectors of the irreducible representations Γ_i for the magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$ occurring at the magnetic Cu^{2+} site in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$. For Γ_2 and Γ_4 the basis vectors are given in Table II, while the six presented spin structures of Γ_5 correspond to the linear combinations $\tilde{\psi}_5^1 = iA\psi_5^1 + B_{++}\psi_5^2 + B_{-+}\psi_5^4 + iA\psi_5^5$, $\tilde{\psi}_5^2 = B_{--}\psi_5^1 - iA\psi_5^2 - iA\psi_5^4 + B_{+-}\psi_5^5$, $\tilde{\psi}_5^3 = C_+\psi_5^3 + C_-\psi_5^6$, $\tilde{\psi}_5^4 = A\psi_5^1 + iB_{--}\psi_5^2 + iB_{-+}\psi_5^4 - A\psi_5^5$, $\tilde{\psi}_5^5 = iB_{++}\psi_5^1 - A\psi_5^2 + A\psi_5^4 + iB_{+-}\psi_5^5$, and $\tilde{\psi}_5^6 = D_+\psi_5^3 + D_-\psi_5^6$, where $A = 1/\sqrt{3}$, $B_{\pm\pm} = (\pm 1 \pm i/\sqrt{3})/2$, $C_{\pm} = (-\sqrt{3} \pm i)/4$, and $D_{\pm} = (1 \pm i/\sqrt{3})/\sqrt{8}$, which represent a real basis of Γ_5 [26]. The chosen assignment of the three magnetically nonequivalent sites in Eq. (2) is shown for ψ_2^1 . The spin structures ψ_2^1 and ψ_4^1 have positive vector chirality +1 [see Eq. (2)] for each triangle when projected onto the c axis, while this projection is -1 for the $\tilde{\psi}_5^2$ and $\tilde{\psi}_5^5$ states. These chirality vectors are perpendicular to the kagome planes and are denoted by $\pm$ signs inside the triangles. The vector chirality of all other structures is zero as they are collinear.

rather show their six linear combinations $\tilde{\psi}_5^j = \sum_k a_k \psi_5^k$ that constitute an equivalent real basis of this irrep [26]. The spins on each site are normalized for all basis vectors, except for the antiferromagnetic vectors $\tilde{\psi}_5^3$ and $\tilde{\psi}_5^6$, because it is impossible to form a net-zero-magnetization state for three normalized collinear spins. The basis vectors ψ_2^1 , ψ_4^1 , and $\tilde{\psi}_5^2$, $\tilde{\psi}_5^5$ correspond to noncollinear structures within the kagome plane, the so-called 120° states, which satisfy the condition $\sum_i \mathbf{S}_i = 0$ on each spin triangle. The other basis vectors describe either ferro-, ferri-, or antiferromagnetic collinear structures. The coplanar 120° structures can be further distinguished based on their vector chirality

$$\kappa = \frac{2}{3\sqrt{3}S^2} (\mathbf{S}_1 \times \mathbf{S}_2 + \mathbf{S}_2 \times \mathbf{S}_3 + \mathbf{S}_3 \times \mathbf{S}_1). \quad (2)$$

The projection of the vector chirality on the c axis is $+1$ for ψ_2^1 and ψ_4^1 , while it is -1 for $\tilde{\psi}_5^2$ and $\tilde{\psi}_5^5$. The sign of these projections is determined by the counterclockwise site assignment shown in Fig. 3. Although the two positive chirality structures are related by a global 90° rotation of spins, the representations Γ_2 and Γ_4 differ in that an out-of-plane ferromagnetic component can be added within the former but not within the latter representation. This gives rise to the so-called umbrella structure for Γ_2 [40].

The refinement of the magnetic structure model to the magnetic diffraction pattern, i.e., to the difference between the diffraction pattern recorded at 1.5 K and the one at 20 K, is shown in Fig. 4 for all relevant irreps. The corresponding

parameters are summarized in Table III. First, we note that our powder neutron diffraction experiment does not distinguish between spin structures $\tilde{\psi}_5^1$ and $\tilde{\psi}_5^4$, $\tilde{\psi}_5^2$ and $\tilde{\psi}_5^5$, and $\tilde{\psi}_5^3$ and $\tilde{\psi}_5^6$. Therefore, we can focus on one of them for each pair when considering the irrep Γ_5 . For the irrep Γ_2 the agreement is worse than for the other two allowed irreps, giving by far the largest reduced χ^2 value after refinement [Fig. 4(a)]. In this solution only the in-plane component ψ_2^1 is included because the ferromagnetic out-of-plane component ψ_2^2 gives a strong reflection at 105° , which is not experimentally observed. For the other one-dimensional irrep Γ_4 , also yielding a coplanar spin structure with positive vector chirality, the agreement with experiment is somewhat better, although it severely underestimates the intensity of the Bragg peak at 88° [Fig. 4(b)]. A much better agreement is obtained for the coplanar spin structure with negative vector chirality $\tilde{\psi}_5^5$ from the two-dimensional Γ_5 [Fig. 4(c)]. On the other hand, for this irrep, the in-plane ferromagnetic spin structure $\tilde{\psi}_5^4$ does not fit the experiment well, as it yields a strong reflection at 23° , which is absent in experiment. However, the collinear out-of-plane spin structure $\tilde{\psi}_5^6$ is consistent with the observed magnetic Bragg peaks [Fig. 4(d)], even though it gives a somewhat worse agreement with experiment than the $\tilde{\psi}_5^5$ spin structure. We note that a marginally better agreement than for the pure coplanar spin structure $\tilde{\psi}_5^5$ is obtained for a linear combination of the basis vectors $0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6$. Within this best-fit model, the relative uncertainty of the two mixing coefficients is, however, quite big (15%). Consequently, the uncertainty of the ordered moments within this model is also

FIG. 4. Simulations of the experimental magnetic diffraction pattern obtained by subtracting the data set taken at 20 K from the data set taken at 1.5 K, which conform to models based on different irreducible representations Γ_i of the little group corresponding to the magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$. The positions of all the predicted magnetic reflections for this $\mathbf{k}$ are marked by green ticks. The intensities of the reflections at 23°, 74°, and 105° are nonzero only for ferromagnetic spin structures. The quality of the fit for each model is reflected in the reduced χ^2 values, which are summarized in Table III together with the corresponding average magnetic moments.

increased compared to the pure $\tilde{\psi}_5^5$ model (see Table III). Independent of the model, we find that the magnitude of the ordered moments is significantly reduced from the full value of $1\mu_B$ – $1.2\mu_B$ expected for Cu^{2+} .

IV. DISCUSSION

Our refinements yield two candidate magnetic structures that are almost indistinguishable regarding the quality of

TABLE III. The in-plane (μ_{ab}) and out-of-plane (μ_c) components of the ordered magnetic moment μ for the different spin structures corresponding to the allowed irreducible representations (irreps). The quality of the refinement for each structure is given by the reduced χ^2 value.

irrep	Vector	Atom	μ_{ab}/μ_B	μ_c/μ_B	μ/μ_B	χ^2
Γ_2	ψ_2^1	1–3	0.48(2)	0	0.48(2)	2.57
Γ_4	ψ_4^1	1–3	0.33(2)	0	0.33(2)	1.61
Γ_5	$\tilde{\psi}_5^5$	1–3	0.42(2)	0	0.42(2)	1.23
	$\tilde{\psi}_5^6$	1, 2	0	0.26(1)	0.26(1)	1.40
		3	0	−0.52(2)	0.52(2)	
	$0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6$	1, 2	0.36(4)	0.14(4)	0.39(5)	1.22
		3	0.36(4)	−0.27(7)	0.46(6)	

the fit (Fig. 4): the in-plane coplanar 120° spin structure with negative vector chirality given by the basis vector $\tilde{\psi}_5^5$ and the spin structure represented by a linear combination of two basis vectors from Γ_5 , $0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6$, where the collinear out-of-plane component $\tilde{\psi}_5^6$ is added to the same in-plane coplanar component. These two spin structures can, however, be distinguished based on their energy. The isotropic Heisenberg exchange model with dominant antiferromagnetic interactions prefers either coplanar or more complex spin structures with larger magnetic unit cells in the kagome plane, the latter if interactions beyond the nearest neighbors are considered [14,16–18]. In $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ the in-plane component of the magnetic propagation vector is zero; therefore, the basic triangular unit is representative for energy considerations.

The distinction between the coplanar structures with positive and negative vector chiralities is made by magnetic anisotropy. The antisymmetric Dzyaloshinskii-Moriya (DM) anisotropy $\mathbf{D} \cdot \mathbf{S}_i \times \mathbf{S}_j$, where $\mathbf{D}$ is the DM vector, directly couples to the vector spin chirality of Eq. (2). The out-of-plane DM component D_z therefore acts as an easy plane [22] and selects either the state with positive vector chirality for $D_z < 0$ or the state with negative vector chirality for $D_z > 0$, the latter apparently being the situation in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$. For the former state, the in-plane DM component D_p causes out-of-plane canting of the spin structure, i.e., an admixture of the ψ_2^2 state, leading to the umbrella structure, while the state with negative chirality remains coplanar even for finite D_p [22]. To explain the possible admixture of the antiferromagnetic collinear state within Γ_5 , as suggested by our experiment, symmetric exchange anisotropy $\Delta S_i^z S_j^z$ with $\Delta > 0$ needs to be included [26] since it acts as an easy-axis anisotropy perpendicular to the kagome plane. Therefore, we consider the Hamiltonian

$$\mathcal{H} = \sum_{\Delta} (J_1 \mathbf{S}_i \mathbf{S}_j + \mathbf{D}_{ij} \cdot \mathbf{S}_i \times \mathbf{S}_j + \Delta S_i^z S_j^z), \quad (3)$$

where J_1 is the nearest-neighbor isotropic exchange interaction and the sum runs over the three spins in the basic triangular unit. For an ordered magnetic moment $\mu = g\mu_B \langle S \rangle$ in the coplanar $\tilde{\psi}_5^5$ spin structure, where g and μ_B are the g factor and the Bohr magneton, respectively, while $\langle S \rangle$ denotes the expectation value of the spin operator, this Hamiltonian

yields the classical energy per spin site of $E(\tilde{\psi}_5^5) = -\frac{1}{2}(J_1 + \sqrt{3}D_z)(\mu/g\mu_B)^2$. In the antiferromagnetic spin structure $\tilde{\psi}_5^6$ the ordered magnetic moment μ on one of the sites in the triangle is accompanied by two moments $\mu/2$ on the other two sites (see Fig. 3), and the classical energy is $E(\tilde{\psi}_5^6) = -\frac{1}{4}(J_1 + \Delta)(\mu/g\mu_B)^2$. Taking into account the magnitude of the in-plane and out-of-plane magnetic moment components for the solutions $\tilde{\psi}_5^5$ and $0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6$ (Table III), we obtain the corresponding energies $E(\tilde{\psi}_5^5) = -0.088\frac{J_1}{g^2} - 0.153\frac{D_z}{g^2}$ and $E(0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6) = -0.083\frac{J_1}{g^2} - 0.112\frac{D_z}{g^2} - 0.020\frac{\Delta}{g^2}$. Comparing these values, we find that the composite spin structure $0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6$ is energetically favorable only if the condition $\Delta > 0.25J_1 + 2.0D_z$ is satisfied.

Both types of exchange anisotropies are spin-orbit-coupling-induced relativistic corrections to the isotropic Heisenberg Hamiltonian. Their expected values are of the order of $D/J_1 \approx \Delta/g$ and $\Delta/J_1 \approx (\Delta/g)^2$ [41]. For the Cu^{2+} ions the g -factor anisotropy is of the order of $\Delta/g \approx 0.15$ [42]. The DM anisotropy is therefore usually dominant for Cu-based kagome lattices [43,44]. We thus conclude that the required Δ/J_1 ratio for the composite spin structure $0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6$ to be stable is at least an order of magnitude larger than can be reasonably expected. The pure coplanar spin structure with negative vector chirality $\tilde{\psi}_5^5$ is therefore the most likely ground state of $\text{YCu}_3(\text{OH})_6\text{Cl}_3$. We note that since the powder neutron diffraction experiment does not distinguish between this state and the other negative vector chirality state $\tilde{\psi}_5^2$ from the same irrep, any linear combination of the two states is possible. Only the experiment on a single-crystal sample could exactly determine the spin structure.

The observed spin structure of $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ corresponds to the so-called $q = 0$ magnetic order in a given kagome plane, which is one of the regular magnetic orders of this lattice [14]. In the case of classical spins this state with negative vector spin chirality can be stabilized by an infinitesimal DM interaction $D_z > 0$ [21,22]. However, in the case of quantum spins, the DM interaction needs to surpass a threshold value for the ordered state to replace a spin-liquid ground state if only the nearest-neighbor isotropic exchange interaction is considered. The majority of theoretical studies suggest that the quantum critical point between a spin-liquid and the $q = 0$ ordered state should occur around $D_z \sim 0.1J_1$ [12,21,23,29]. We note, though, that a much lower critical value of $D_z \sim 0.012(2)J_1$ was recently suggested by a theoretical approach that favors a gapless $\text{U}(1)$ spin liquid as the ground state in the absence of the DM interaction [27].

As an alternative to the DM component D_z being responsible for stabilizing the ordered state in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$, the same state could also be stabilized by exchange interactions beyond nearest neighbors. A finite next-nearest-neighbor interaction J_2 , for example, decreases the above-mentioned quantum critical point and stabilizes the $q = 0$ ordered state above $J_2/J_1 \approx 0.15$ [29]. Indeed, the $q = 0$ ordered state is stable even in the absence of the DM interaction in the parameter range $0.15 - 0.5 \lesssim J_2/J_1 \lesssim 1.7$ [16,18,21]. A finite DM component D_z further shifts these boundaries in favor of the ordered state [21] and is needed to select the chirality of the spin structure. The shift of the phase boundaries towards lower

J_2/J_1 values is due to the fact that the isotropic Heisenberg antiferromagnetic interaction on the basic triangular unit is more frustrated than the DM interaction; for example, in the energy calculation of the coplanar state $\tilde{\psi}_5^5$ presented above, the DM contribution is effectively multiplied by a factor of $\sqrt{3}$ when compared to the J_1 contribution. The DM component D_z , therefore, tends to reduce quantum fluctuation in favor of magnetic ordering. The same is true for the in-plane DM component D_p , which also disfavors some spin structures from the ground-state manifold of the classical isotropic Hamiltonian and should be even more efficient than the D_z component in suppressing quantum fluctuations [44].

The Heisenberg interactions with even more distant neighbors further complicate the theoretically predicted phase diagram [14,15,17–21]. Although these interactions are negligible in the paradigmatic QKA representative herbertsmithite [45], they turn out to be relevant in some other QKA representatives. For instance, in kapellasite, where the Zn^{2+} ions occupy the centers of hexagons instead of the interlayer sites occupied in herbertsmithite, the diagonal exchange interaction across the kagome hexagon in fact dominates over the nearest-neighbor interaction [17,46]. There, a gapless spin-liquid ground state that hosts unusual noncoplanar dynamical short-range correlations of a so-called cuboc2 regular magnetic order from the classical spin picture was observed [47], which might also be influenced by a severe site-mixing problem on the kagome planes of that material [48]. Moreover, for vesignieite it was recently argued that a complex triple- $\mathbf{k}$ octahedral spin structure is stabilized by a dominant antiferromagnetic third-nearest-neighbor exchange [49]. On the other hand, the $q = 0$ ordered state found in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ is generally stable in the region of the phase diagram where J_1 and J_2 interactions dominate [15,18,19]. Therefore, we do not expect exchange interactions beyond the second neighbors to play any significant role in this compound. Lastly, we note that magnetic ordering in kagome materials can also be induced by the interlayer exchange coupling [13]. However, the required value of the interlayer exchange is very high, $J_\perp/J_1 \gtrsim 0.15$, which is unlikely to be satisfied in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$, where the neighboring kagome layers are separated by Cl^- ions and the interlayer distance is as large as 5.6 Å.

Finally, our refinement yields an ordered magnetic moment of $\mu = 0.42(2)\mu_B$ per Cu^{2+} site, which is significantly smaller than the full value of $1\mu_B - 1.2\mu_B$ expected for this ion. The origin of this strong reduction may be twofold. First, it can be due to strong quantum renormalization effects, as theoretical predictions suggest that the ordered magnetic moments should be strongly reduced close to the quantum critical point at $D_z/J_1 \sim 0.1$ [18,23]. Alternatively, the observed reduction of the average ordered magnetic moment can occur even for classical spins because some of the order parameters described by the irreps of the kagome lattice correspond to configurations in which spins are not of unit length [26]. Consequently, there exist extended regions in parameter space where either multiple types of order have to coexist or partial order that coexists with a magnetically disordered phase is established. In the latter scenario, magnetic fluctuations arising from an extensive fraction of disordered spin degrees of freedom would persist down to zero temperature. This is a possible explanation of the persistent spin dynamics

observed in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ by μSR experiments [35], while the alternative possibility of an incommensurate magnetic order being at the origin of the persistent spin dynamics is ruled out by the magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$ found in our experiment.

In summary, the neutron diffraction results on $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ are consistent with the $\tilde{\psi}_5^5$ coplanar $q = 0$ state with negative vector chirality and strongly reduced magnetic moments. The other ground-state candidate, $0.68\tilde{\psi}_5^5 + 0.32\tilde{\psi}_5^6$, would require unphysically large symmetric exchange anisotropy. Based on energy consideration, we conclude that the selection of this particular spin structure is due to the DM magnetic anisotropy. The origin of the magnetic ordering below T_N is either in the DM anisotropy or in further-neighbor isotropic exchange interactions.

V. CONCLUSIONS

Our powder neutron diffraction experiments on $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ have disclosed clear magnetic Bragg peaks that appear below $T_N = 15$ K. Their positions and intensities are consistent with a negative vector chirality 120° coplanar spin structure within the kagome planes with antiferromagnetic order between the neighboring planes, as described by the magnetic propagation vector $\mathbf{k} = (0, 0, 0.5)$. The detected magnetic order is partial in the sense that the ordered magnetic moment amounts to only $\mu = 0.42(2)\mu_B$ at 1.5 K. This strong moment reduction may arise either from strong quantum fluctuations due to the vicinity of a quantum critical point [23] or from the coexistence of

order and disorder, which could be ubiquitous even in classical kagome systems [26]. This explains the previously observed spin dynamics that persists down to extremely low temperatures [35]. Either Dzyaloshinskii-Moriya anisotropy or further-neighbor exchange interactions could be responsible for stabilizing the observed magnetically ordered state instead of a quantum-spin-liquid state. The selection of a negative vector chirality state out of the degenerate manifold of classical states of the isotropic Heisenberg Hamiltonian is attributed to the out-of-plane Dzyaloshinskii-Moriya anisotropy $D_z > 0$. Additional experiments, e.g., electron spin resonance, which is extremely sensitive to magnetic anisotropy [43,44,48,50], and theoretical calculations of the relevant exchange interactions, e.g., using *ab initio* [45,51] or exact-diagonalization approaches [52], are required to determine the precise microscopic Hamiltonian of $\text{YCu}_3(\text{OH})_6\text{Cl}_3$ and thus to address the origin of magnetic ordering in this material in detail.

The data that support the findings of this study are available in Durham University [53].

ACKNOWLEDGMENTS

We acknowledge the financial support from the Slovenian Research Agency under Program No. P1-0125. M.G. is grateful to EPSRC (UK) for financial support through Grant No. EP/N024028/1. This work is based on experiments performed at the Swiss spallation neutron source SINQ, Paul Scherrer Institute, Villigen, Switzerland.

-
- [1] L. Balents, Spin liquids in frustrated magnets, *Nature (London)* **464**, 199 (2010).
 - [2] L. Savary and L. Balents, Quantum spin liquids: A review, *Rep. Prog. Phys.* **80**, 016502 (2017).
 - [3] Y. Zhou, K. Kanoda, and T.-K. Ng, Quantum Spin Liquid States, *Rev. Mod. Phys.* **89**, 025003 (2017).
 - [4] S. Yan, D. A. Huse, and S. R. White, Spin-liquid ground state of the $S = 1/2$ kagome Heisenberg antiferromagnet, *Science* **332**, 1173 (2011).
 - [5] S. Depenbrock, I. P. McCulloch, and U. Schollwöck, Nature of the Spin-Liquid Ground State of the $S = 1/2$ Heisenberg Model on the Kagome Lattice, *Phys. Rev. Lett.* **109**, 067201 (2012).
 - [6] Y. Iqbal, F. Becca, S. Sorella, and D. Poilblanc, Gapless spin-liquid phase in the kagome spin-1/2 Heisenberg antiferromagnet, *Phys. Rev. B* **87**, 060405(R) (2013).
 - [7] Y.-C. He, M. P. Zaletel, M. Oshikawa, and F. Pollmann, Signatures of Dirac Cones in a DMRG Study of the Kagome Heisenberg Model, *Phys. Rev. X* **7**, 031020 (2017).
 - [8] H. J. Liao, Z. Y. Xie, J. Chen, Z. Y. Liu, H. D. Xie, R. Z. Huang, B. Normand, and T. Xiang, Gapless Spin-Liquid Ground State in the $S = 1/2$ Kagome Antiferromagnet, *Phys. Rev. Lett.* **118**, 137202 (2017).
 - [9] J.-W. Mei, J.-Y. Chen, H. He, and X.-G. Wen, Gapped spin liquid with $\mathbb{Z}_2$ topological order for the kagome Heisenberg model, *Phys. Rev. B* **95**, 235107 (2017).
 - [10] H. Kawamura, K. Watanabe, and T. Shimokawa, Quantum spin-liquid behavior in the spin- $\frac{1}{2}$ random-bond Heisenberg antiferromagnet on the kagome lattice, *J. Phys. Soc. Jpn.* **83**, 103704 (2014).
 - [11] T. Shimokawa, K. Watanabe, and H. Kawamura, Static and dynamical spin correlations of the $S = \frac{1}{2}$ random-bond antiferromagnetic Heisenberg model on the triangular and kagome lattices, *Phys. Rev. B* **92**, 134407 (2015).
 - [12] I. Rousochatzakis, S. R. Manmana, A. M. Läuchli, B. Normand, and F. Mila, Dzyaloshinskii-Moriya anisotropy and nonmagnetic impurities in the $s = 1/2$ kagome system $\text{ZnCu}_3(\text{OH})_6\text{Cl}_2$, *Phys. Rev. B* **79**, 214415 (2009).
 - [13] O. Götze and J. Richter, The route to magnetic order in the spin-1/2 kagome Heisenberg antiferromagnet: The role of interlayer coupling, *Europhys. Lett.* **114**, 67004 (2016).
 - [14] L. Messio, C. Lhuillier, and G. Misguich, Lattice symmetries and regular magnetic orders in classical frustrated antiferromagnets, *Phys. Rev. B* **83**, 184401 (2011).
 - [15] L. Messio, B. Bernu, and C. Lhuillier, Kagomé Antiferromagnet: A Chiral Topological Spin Liquid? *Phys. Rev. Lett.* **108**, 207204 (2012).
 - [16] R. Suttner, C. Platt, J. Reuther, and R. Thomale, Renormalization group analysis of competing quantum phases in the J_1 - J_2 Heisenberg model on the kagome lattice, *Phys. Rev. B* **89**, 020408(R) (2014).
 - [17] Y. Iqbal, H. O. Jeschke, J. Reuther, R. Valentí, I. I. Mazin, M. Greiter, and R. Thomale, Paramagnetism in the kagome compounds $(\text{Zn}, \text{Mg}, \text{Cd})\text{Cu}_3(\text{OH})_6\text{Cl}_2$, *Phys. Rev. B* **92**, 220404(R) (2015).

- [18] S.-S. Gong, W. Zhu, L. Balents, and D. N. Sheng, Global phase diagram of competing ordered and quantum spin-liquid phases on the kagome lattice, *Phys. Rev. B* **91**, 075112 (2015).
- [19] F. L. Buessen and S. Trebst, Competing magnetic orders and spin liquids in two- and three-dimensional kagome systems: Pseudofermion functional renormalization group perspective, *Phys. Rev. B* **94**, 235138 (2016).
- [20] Y.-C. He and Y. Chen, Distinct Spin Liquids and Their Transitions in Spin-1/2 XXZ Kagome Antiferromagnets, *Phys. Rev. Lett.* **114**, 037201 (2015).
- [21] M. Hering and J. Reuther, Functional renormalization group analysis of Dzyaloshinsky-Moriya and Heisenberg spin interactions on the kagome lattice, *Phys. Rev. B* **95**, 054418 (2017).
- [22] M. Elhajal, B. Canals, and C. Lacroix, Symmetry breaking due to Dzyaloshinsky-Moriya interactions in the kagomé lattice, *Phys. Rev. B* **66**, 014422 (2002).
- [23] O. Cepas, C. M. Fong, P. W. Leung, and C. Lhuillier, Quantum phase transition induced by Dzyaloshinskii-Moriya interactions in the kagome antiferromagnet, *Phys. Rev. B* **78**, 140405(R) (2008).
- [24] A. L. Chernyshev and M. E. Zhitomirsky, Quantum Selection of Order in an XXZ Antiferromagnet on a Kagome Lattice, *Phys. Rev. Lett.* **113**, 237202 (2014).
- [25] K. Essafi, O. Benton, and L. D. C. Jaubert, A kagome map of spin liquids from XXZ to Dzyaloshinskii-Moriya ferromagnet, *Nat. Commun.* **7**, 10297 (2016).
- [26] K. Essafi, O. Benton, and L. D. C. Jaubert, Generic nearest-neighbor kagome model: XYZ and Dzyaloshinskii-Moriya couplings with comparison to the pyrochlore-lattice case, *Phys. Rev. B* **96**, 205126 (2017).
- [27] C.-Y. Lee, B. Normand, and Y.-J. Kao, Gapless spin liquid in the kagome Heisenberg antiferromagnet with Dzyaloshinskii-Moriya interactions, *Phys. Rev. B* **98**, 224414 (2018).
- [28] H. J. Changlani, D. Kochkov, K. Kumar, B. K. Clark, and E. Fradkin, Macroscopically Degenerate Exactly Solvable Point in the Spin-1/2 Kagome Quantum Antiferromagnet, *Phys. Rev. Lett.* **120**, 117202 (2018).
- [29] W. Zhu, S.-S. Gong, and D. N. Sheng, Identifying spinon excitations from dynamic structure factor of spin-1/2 Heisenberg antiferromagnet on the kagome lattice, *Proc. Natl. Acad. Sci. USA* **116**, 5437 (2019).
- [30] M. R. Norman, Colloquium: Herbertsmithite and the search for the quantum spin liquid, *Rev. Mod. Phys.* **88**, 041002 (2016).
- [31] W. Sun, Y.-X. Huang, S. Nokhrin, Y. Pan, and J.-X. Mi, Perfect kagomé lattices in $\text{YCu}_3(\text{OH})_6\text{Cl}_3$: A new candidate for the quantum spin liquid state, *J. Mater. Chem. C* **4**, 8772 (2016).
- [32] A. Zorko, M. Herak, M. Gomilšek, J. van Tol, M. Velázquez, P. Khuntia, F. Bert, and P. Mendels, Symmetry Reduction in the Quantum Kagome Antiferromagnet Herbertsmithite, *Phys. Rev. Lett.* **118**, 017202 (2017).
- [33] M. Gomilšek, M. Klanjšek, M. Pregelj, H. Luetkens, Y. Li, Q. M. Zhang, and A. Zorko, μSR insight into the impurity problem in quantum kagome antiferromagnets, *Phys. Rev. B* **94**, 024438 (2016).
- [34] P. Puphal, M. Bolte, D. Sheptyakov, A. Pustogow, K. Kliemt, M. Dressel, M. Baenitz, and C. Krellner, Strong magnetic frustration in $\text{Y}_3\text{Cu}_9(\text{OH})_{19}\text{Cl}_8$: A distorted kagome antiferromagnet, *J. Mater. Chem. C* **5**, 2629 (2017).
- [35] A. Zorko, M. Pregelj, M. Klanjšek, M. Gomilšek, Z. Jagličić, J. S. Lord, J. A. T. Verezhak, T. Shang, W. Sun, and J.-X. Mi, Coexistence of magnetic order and persistent spin dynamics in a quantum kagome antiferromagnet with no intersite mixing, *Phys. Rev. B* **99**, 214441 (2019).
- [36] Q. Barthélemy, P. Puphal, K. M. Zoch, C. Krellner, H. Luetkens, C. Baines, D. Sheptyakov, E. Kermarrec, P. Mendels, and F. Bert, Local study of the insulating quantum kagome antiferromagnets $\text{YCu}_3(\text{OH})_6\text{O}_x\text{Cl}_{3-x}$ ($x = 0, 1/3$), *Phys. Rev. Mater.* **3**, 074401 (2019).
- [37] A. Yaouanc, P. Dalmas de Reotier, A. Bertin, C. Marin, E. Lhotel, A. Amato, and C. Baines, Evidence for unidimensional low-energy excitations as the origin of persistent spin dynamics in geometrically frustrated magnets, *Phys. Rev. B* **91**, 104427 (2015).
- [38] M. Pregelj, A. Zorko, O. Zaharko, D. Arčon, M. Komelj, A. D. Hillier, and H. Berger, Persistent Spin Dynamics Intrinsic to Amplitude-Modulated Long-Range Magnetic Order, *Phys. Rev. Lett.* **109**, 227202 (2012).
- [39] J. Rodríguez-Carvajal, Recent advances in magnetic structure determination by neutron powder diffraction, *Phys. B (Amsterdam, Neth.)* **192**, 55 (1993).
- [40] A. S. Wills, Long-range ordering and representational analysis of the jarosites, *Phys. Rev. B* **63**, 064430 (2001).
- [41] T. Moriya, Anisotropic superexchange interaction and weak ferromagnetism, *Phys. Rev.* **120**, 91 (1960).
- [42] A. Abragam and B. Bleaney, *Electron Paramagnetic Resonance of Transition Ions* (Clarendon, Oxford, 1970).
- [43] A. Zorko, S. Nellutla, J. van Tol, L. C. Brunel, F. Bert, F. Duc, J.-C. Trombe, M. A. de Vries, A. Harrison, and P. Mendels, Dzyaloshinsky-Moriya Anisotropy in the Spin-1/2 Kagome Compound $\text{ZnCu}_3(\text{OH})_6\text{Cl}_2$, *Phys. Rev. Lett.* **101**, 026405 (2008).
- [44] A. Zorko, F. Bert, A. Ozarowski, J. van Tol, D. Boldrin, A. S. Wills, and P. Mendels, Dzyaloshinsky-Moriya interaction in vesignieite: A route to freezing in a quantum kagome antiferromagnet, *Phys. Rev. B* **88**, 144419 (2013).
- [45] H. O. Jeschke, F. Salvat-Pujol, and R. Valentí, First-principles determination of Heisenberg Hamiltonian parameters for the spin-1/2 kagome antiferromagnet $\text{ZnCu}_3(\text{OH})_6\text{Cl}_2$, *Phys. Rev. B* **88**, 075106 (2013).
- [46] B. Bernu, C. Lhuillier, E. Kermarrec, F. Bert, P. Mendels, R. H. Colman, and A. S. Wills, Exchange energies of kapellasite from high-temperature series analysis of the kagome lattice J_1 - J_2 - J_d -Heisenberg model, *Phys. Rev. B* **87**, 155107 (2013).
- [47] B. Fåk, E. Kermarrec, L. Messio, B. Bernu, C. Lhuillier, F. Bert, P. Mendels, B. Koteswararao, F. Bouquet, J. Ollivier, A. D. Hillier, A. Amato, R. H. Colman, and A. S. Wills, Kapellasite: A Kagome Quantum Spin Liquid with Competing Interactions, *Phys. Rev. Lett.* **109**, 037208 (2012).
- [48] E. Kermarrec, A. Zorko, F. Bert, R. H. Colman, B. Koteswararao, F. Bouquet, P. Bonville, A. Hillier, A. Amato, J. van Tol, A. Ozarowski, A. S. Wills, and P. Mendels, Spin dynamics and disorder effects in the $S = 1/2$ kagome Heisenberg spin-liquid phase of kapellasite, *Phys. Rev. B* **90**, 205103 (2014).
- [49] D. Boldrin, B. Fåk, E. Canévet, J. Ollivier, H. C. Walker, P. Manuel, D. D. Khalyavin, and A. S. Wills, Vesignieite: An $S = 1/2$ Kagome Antiferromagnet with Dominant Third-Neighbor Exchange, *Phys. Rev. Lett.* **121**, 107203 (2018).

- [50] S. A. Zvyagin, D. Kamenskyi, M. Ozerov, J. Wosnitzer, M. Ikeda, T. Fujita, M. Hagiwara, A. I. Smirnov, T. A. Soldatov, A. Ya. Shapiro, J. Krzystek, R. Hu, H. Ryu, C. Petrovic, and M. E. Zhitomirsky, Direct Determination of Exchange Parameters in Cs_2CuBr_4 and Cs_2CuCl_4 : High-Field Electron-Spin-Resonance Studies, *Phys. Rev. Lett.* **112**, 077206 (2014).
- [51] K. Riedl, Y. Li, R. Valentí, and S. M. Winter, *Ab initio* approaches for low-energy spin Hamiltonians, *Phys. Status Solidi B* **256**, 1800684 (2019).
- [52] A. Zorko, J. Kokalj, M. Komelj, O. Adamopoulos, H. Luetkens, D. Arčon, and A. Lappas, Magnetic inhomogeneity on a triangular lattice: The magnetic-exchange versus the elastic energy and the role of disorder, *Sci. Rep.* **5**, 9272 (2015).
- [53] A. Zorko *et al.*, Negative-vector-chirality 120° spin structure in the defect- and distortion-free quantum kagome antiferromagnet $\text{YCu}_3(\text{OH})_6\text{Cl}_3$, doi: [10.15128/r2qr46r083v](https://doi.org/10.15128/r2qr46r083v) (2019).