Influence of disorder on the structural phase transition and magnetic interactions in $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$

Henrik Grundmann* and Andreas Schilling

Physik-Institut, Universität Zürich, Winterthurerstrasse 190, CH-8057 Zürich, Switzerland

Marisa Medarde

Laboratory for Development and Methods, Paul Scherrer Institut, 5232 Villigen PSI, Switzerland

Denis Sheptyakov

Laboratory for Neutron Scattering, Paul Scherrer Institut, 5232 Villigen PSI, Switzerland

(Received 22 April 2014; revised manuscript received 10 July 2014; published 1 August 2014)

The spin dimer system $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ is a solid solution of the triplon Bose-Einstein condensation candidates $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$. The magnetic intradimer interaction constant J_0 in this spin system can be tuned by varying the Sr content x . Very interestingly, this variation of J_0 with x is highly nonlinear. In the present study, we show that this peculiar behavior of J_0 can be only partly explained by the changes in the average crystal structure alone. We report on neutron powder diffraction experiments to probe the corresponding structural details. Performing extended Hückel tight-binding calculations based on those structural details obtained at liquid-helium temperatures, we found that the change of the magnetic interaction constant can be well reproduced by taking into account the presence of a structural transition due to the Jahn-Teller active Cr^{5+} ions. This transition, lifting the orbital degeneracy and thereby the magnetic frustration in the system, is heavily influenced by disorder in the system arising from partially exchanging Ba with Sr.

DOI: [10.1103/PhysRevB.90.075101](https://doi.org/10.1103/PhysRevB.90.075101)

PACS number(s): 71.27.+a, 71.70.Ej

I. INTRODUCTION

Bose-Einstein condensation (BEC) is one of the most fascinating aspects in modern physics. A decade ago, the field of spin dimer physics was closely linked to this topic by explaining several properties of certain spin dimer systems in terms of a BEC of magnetic quasiparticles (triplons) [1]. The triplons, formed by dimers of magnetic ions, condense at a low enough temperature T and above a critical magnetic field $H_c(T)$. Once the condensate is formed, the triplons should show macroscopic phase coherence, a defining property of every BEC. It has very recently been suggested that this phase coherence could be probed in a device of two coupled spin dimer materials with different critical fields [2], which would represent a direct analog to a Josephson junction showing the ac-Josephson effect. As in superconductors and atomic BECs [3,4], this effect is based on the existence of a phase-coherent macroscopic wave function. A successful detection of Josephson effects in spin dimer systems would therefore be direct proof of macroscopic phase coherence and allow us to classify the observed spin condensate as a true BEC.

As the above-sketched experiment requires two spin systems with a certain difference in the respective critical fields H_c , the fine-tuning of this parameter becomes necessary. The critical field largely depends on the intradimer magnetic interaction constant J_0 between the ions that form the spin dimers. J_0 is essentially determined by the specific (super)exchange path between those ions and therefore changes if the crystal structure is modified. The spin systems $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$, two candidates for a triplon BEC [5–7], represent such spin systems with a similar structure but strongly differing magnetic interactions. For the corresponding

mixed system $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$, J_0 has been reported to be tunable by changing the Sr content x [8]. It was found that J_0 changes in a peculiar, nonmonotonous way as a function of x , which contrasts with the almost linear changes of the lattice parameters. Up to now, this discrepancy has not been resolved.

The present work aims to give a satisfactory explanation based on a more detailed examination of changes in the crystal structure with x . It has been shown for $\text{Sr}_3\text{Cr}_2\text{O}_8$ that due to a Jahn-Teller-type temperature-induced structural phase transition involving certain oxygen positions (which is present for both $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$), J_0 is strongly enhanced at low temperatures [9]. Using neutron powder diffraction techniques, which are more sensitive to the oxygen positions than corresponding x-ray diffraction data in the presence of heavy elements such as Sr and Ba, we have investigated the crystal structure of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ (see Fig. 1) for several values of x at room temperature and at $T = 2$ K. Based on the obtained lattice parameters and atomic positions, we performed extended Hückel tight-binding (EHTB) calculations to estimate J_0 as a function of x .

II. EXPERIMENTAL DETAILS**A. Synthesis**

The polycrystalline samples were prepared by standard solid-state reaction schemes. Powders of BaCO_3 (99.98%, Sigma-Aldrich), SrCO_3 (99.9%, Sigma-Aldrich), and Cr_2O_3 (99.9%, Sigma-Aldrich) were mixed according to

and were ground and heated in flowing Ar at 1300°C . The heating was started with a linear ramp up to 1300°C over 5 h. The samples remained at this temperature for 12 h, followed by a linear cooling to room temperature for 8 h. The grinding

*grundmann@physik.uzh.ch

FIG. 1. (Color online) Crystal structure of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ at room temperature. The Cr-tetrahedron is shown in dimer configuration on the right, the Ba_1/Sr_1 dodecahedron is shown on the bottom and the Ba_2/Sr_2 -dodecahedron is shown on the top of the drawing. The angle $\beta^* = \beta - 90^\circ$ is marked to show how the monoclinic angle β was calculated for Fig. 6.

and heating were repeated twice. We prepared samples with $x \in \{0, \frac{1}{3}, \frac{2}{3}, 1, \frac{4}{3}, \frac{5}{3}, 2, \frac{7}{3}, \frac{8}{3}, 3\}$.

B. Neutron diffraction

The neutron powder diffraction experiments were carried out at the high-resolution powder diffractometer HRPT [10] at Paul Scherrer Institute (Villigen PSI) at room temperature and at $T = 2$ K, using $\lambda = 1.494 \text{ \AA}$ [Ge(533)]. Scans were performed with fixed primary Soller collimation ($40'$) and a secondary slit of $40'$. The powder samples (≈ 6 g) were loaded into cylindrical vanadium containers 8 mm in diameter (6 mm for $\text{Ba}_{\frac{8}{3}}\text{Sr}_{\frac{1}{3}}\text{Cr}_2\text{O}_8$). The low-temperature measurements were performed using a He cryostat, whose contribution to the total scattering was minimized using an oscillating radial collimator. The obtained diffractograms were analyzed using the RIETVELD package FULLPROF suite [11].

C. Tight-binding calculations

Based on these structure data, we calculated the antiferromagnetic interaction constant J_0 using the extended Hückel tight-binding method which was successfully used in the past to estimate the interaction constants in $\text{Ba}_3\text{Cr}_2\text{O}_8$ [12] and $\text{Sr}_3\text{Cr}_2\text{O}_8$ [9]. These calculations are based on determining the orbital splittings $\Delta e_{\mu\mu}$ of the occupied chromium orbitals. This splitting $\Delta e_{\mu\mu}$ of the μ th considered orbital occurs when two CrO_4^{3-} tetrahedra are brought together to form a dimer (see Fig. 2), and it can be calculated directly. Based on these splittings, J_0 can be estimated as $J_0 = \frac{\langle(\Delta e)^2\rangle}{U}$, where U is a repulsion potential and $\langle(\Delta e)^2\rangle = \frac{1}{n} \sum_{\mu} (\Delta e_{\mu\mu})^2$ is a sum over all n occupied orbitals. Due to the degeneracy of the $3z^2 - r^2$ and the $x^2 - y^2$ orbitals at room temperature, both orbitals have to be taken into account when calculating $\langle(\Delta e)^2\rangle$. At temperatures below the Jahn-Teller transition, however, only the $3z^2 - r^2$ orbital is occupied (see below), so that $\langle(\Delta e)^2\rangle = (\Delta e_{3z^2-r^2})^2$. A more detailed description of the general implementation of this procedure and its limitation

FIG. 2. (Color online) Sketch of the orbital splitting Δe that occurs when two CrO_4^{3-} tetrahedra form a dimer. The sketch refers to the undistorted room-temperature structure.

to antiferromagnetic interactions can be found in [13]. The EHTB calculations have been performed using the SAMOA suite [14].

The repulsion potential U depends on the chemical composition and should vary gradually with the Sr concentration x [15]. Assuming a linear behavior as a function of x , $U(x) = Ax + B$, we calculated $J_0(x)$ from $J_0 = \frac{\langle(\Delta e)^2\rangle}{Ax+B}$. Values for A and B were determined by comparing the published experimental values of J_0 (from inelastic neutron scattering) [16,17] with the calculated orbital splitting for the considered compounds in the low-temperature phase.

III. RESULTS AND DISCUSSION

A. Crystal structure at room temperature

In the neutron powder diffraction patterns obtained at room temperature, the observed Bragg reflections could be indexed using the space group $R\bar{3}m$ for all x . From the Rietveld refinement of the diffraction data we obtained an almost linear behavior of the lattice constants a and c as a function of the Sr

FIG. 3. (Color online) Lattice constants a and c of $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ at room temperature (space group $R\bar{3}m$). The lattice constants are shown as a function of the Sr content x as obtained from x-ray [8] and neutron powder diffraction experiments. The error bars for the values obtained from neutron diffraction are smaller than the size of the markers.

FIG. 4. (Color online) Heights and edge lengths of the oxygen polyhedra in $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ as functions of the Sr content x at room temperature. The sketches on the right show the definitions of the plotted parameters.

content, in accordance with recently reported x-ray diffraction experiments (see Fig. 3).

Along with this almost linear decrease of the lattice constants, the size of the oxygen polyhedra that surround the Ba/Sr ions decreases linearly as well. The Ba/Sr atoms are located at two different positions (sites Ba_1 and Ba_2). The respective Wyckoff positions are $3a$ and $6c$ for $R\bar{3}m$ ($4e$ and $8f$ for $C_{2/c}$). The atoms located in the Ba_2 position with point site symmetry $3m$ are tenfold coordinated. The height h_2 of the coordinating decatope changes linearly as a function of x (see Fig. 4). The planar oxygen hexagon surrounding the Ba_2 position is not evenly formed. Although the inner angle is always $\alpha = 120^\circ$, the edge M that is shared with the chromium tetrahedron is shorter than the edge N that is shared with the Ba_1 dodecatope. The value of N decreases with increasing x until M and N are equal for $x = 3$ (see Fig. 4).

The position Ba_1 is 12-fold coordinated with site symmetry $\bar{3}m$ (see Fig. 4). As stated above, the edge length N is shared with the Ba_2 decatope. Both edge lengths N and O as well as the dodecatope height h_1 decrease linearly as a function of x (see Fig. 4).

The oxygen tetrahedron around the Cr ion is only slightly affected by varying the stoichiometry. Neither the tetrahedron height h_3 nor the edge length M of the base triangle change significantly as a function of x (see Fig. 4). Without

any additional influences, this negligible change of the Cr tetrahedron should be reflected in a rather small, monotonous change of the interaction constant. This change of J_0 would be mostly given by the shrinking separation of the two tetrahedra forming a dimer as a function of x . Thus, the structural data at room temperature do not give a satisfactory explanation for the observed changes of J_0 with the stoichiometry.

B. Crystal structure at $T = 2$ K

Our analysis of the diffraction patterns obtained at $T = 2$ K shows that the lattice symmetry is lowered for some, but not all, values of x upon cooling. For chemical compositions close to the parent compounds, i.e., for $x \in \{0, 0.33, 2.33, 3\}$, the lattice is better described using space group $C_{2/c}$, which has been reported for $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$, with new diffraction peaks appearing (see Fig. 5). For the remaining samples, no superstructure peaks could be observed. The diffraction pattern at $T = 2$ K could be well described by the room-temperature space group $R\bar{3}m$, indicating a suppression of the structural phase transition for the samples with $0.33 < x < 2.33$.

Where detected, the symmetry breaking is due to a horizontal displacement δ_s of the apical oxygen in the tetrahedron surrounding the Cr^{5+} ions (O_1 in our notation; see Figs. 1 and 6). As shown in Fig. 6, this δ_s is smaller for intermediate

FIG. 5. (Color online) Additional peaks appearing in the low-temperature neutron diffractograms for $\text{Sr}_3\text{Cr}_2\text{O}_8$ and $\text{Ba}_{2/3}\text{Sr}_{7/3}\text{Cr}_2\text{O}_8$, indicating the occurrence of the structural phase transition.

x than for the parent compounds. By shifting O_1 along the $\text{O}_2\text{-O}_3$ edge, the site symmetry of the Cr ions ($3m$ at room temperature) is lost. This oxygen shift affects the electronic orbitals of the Cr ions. In the case of a perfect tetrahedron, the d orbitals are grouped into a lower-lying, twofold-degenerate e_g state and a higher-lying, threefold-degenerate t_g state. When the symmetry breaking occurs in $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$, the e_g state degeneracy is lifted, with a separation into a lower-lying $3z^2 - r^2$ orbital and a higher-lying $x^2 - y^2$ orbital. Therefore, both of the e_g states have to be considered when calculating $\langle \Delta e \rangle$ in the case of space group $R\bar{3}m$, whereas only the $3z^2 - r^2$ orbital has to be taken into account for $C_{2/c}$.

Apart from a shift of the apical oxygen atom, the structural distortion also affects the monoclinic angle β . Where the distortion could be detected, β deviates slightly by $\Delta\beta$ from the value that is expected from a conversion between the rhombohedral and the monoclinic space groups (see Fig. 1).

FIG. 6. (Color online) Distance δ_s of the apical oxygen atom from the dimer axis (crosses) and the angle distortion $\Delta\beta$ (circles) as a function of the Sr content x . The solid lines are guides to the eye. The distance in the corresponding sketches is exaggerated for visual clarity.

The value of $\Delta\beta$ was found to depend on x (see Fig. 6) and vanishes for stoichiometries where the Jahn-Teller transition is suppressed.

C. Calculating J_0 from the structural data

To quantitatively examine the effect of the oxygen shift on the interaction constant J_0 , we calculated the energy splitting $\langle \Delta e \rangle$ for the obtained crystal structures and estimated the repulsion potential U . Unfortunately, no experimental values for J_0 at room temperature have been reported. To obtain reasonable values for U , we therefore first carried out EHTB calculations based on the low-temperature structures for $x = 0$ and $x = 3$. For the occupied $3z^2 - r^2$, our calculations yielded orbital splitting energies $\Delta e(x = 0) = 5.6$ meV and $\Delta e(x = 0) = 3.9$ meV. From these values and the reported interaction constants $J_0^{\text{Ba}} = 2.38$ meV [16] and $J_0^{\text{Sr}} = 5.55$ meV [17], we obtained $A = -216$ meV and $B = 648$ meV. Based on these parameters, we could estimate the value of repulsion potential U for all examined values of x . As we assumed U to be temperature independent, the same values of $U(x)$ were used to calculate for J_0 at low temperature and at room temperature from the calculated splittings $\langle \Delta e \rangle$.

In Fig. 7, we have plotted the previously reported [8] values of J_0 as obtained from fitting magnetization data $M(T)$ together with the results of our calculations of J_0 at room temperature and at $T = 2$ K. The experimental values of J_0 are most sensitive to the low-temperature magnetization part of the $M(T)$ data used for the fitting procedure. Therefore, they are valid well below room temperature. Figure 7 demonstrates, as expected, that the experimental values can be well reproduced within the EHTB framework if the corresponding calculations are based on the low-temperature structure. By contrast, the calculated room temperature values of J_0 underestimate the experimental values for a wide range of x . On the other hand, the experimental values and the calculations for both the room-temperature and low-temperature structures almost coincide for a Sr content of $x \approx 1.33$. For this composition, our neutron diffraction experiments did not indicate any evidence

FIG. 7. (Color online) Intradimer interaction constant J_0 for $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ as a function of the Sr content x . The data points are experimentally obtained from superconducting quantum interference device measurements and estimated based on EHTB calculations for the crystal structure at room temperature and $T = 2$ K, respectively.

FIG. 8. (Color online) Obtained occupancy for the Ba atoms at sites 1 and 2 as a function of the Sr content x obtained at room temperature. The solid lines are guides to the eye; the filled areas mark the difference from the expected strictly linear decrease.

for the structural symmetry breaking that we observed for the other values of x at $T = 2$ K. Furthermore, combining the results of Figs. 6 and 7 suggests that a larger value of J_0 seems to be accompanied by a stronger symmetry breaking.

From these results, we conclude that the Jahn-Teller distortion, which induces an orbital ordering [9,12], increases the intradimer interaction constant J_0 for $0 < x < 3$, as reported for $\text{Sr}_3\text{Cr}_2\text{O}_8$. Without this orbital ordering, the splitting $\langle \Delta e \rangle$ for a given x remains almost constant for all temperatures. We predict that no (or just a minimal) distortion will be present for stoichiometries for which the experimental value of J_0 is close to the calculated room-temperature value.

D. Possible reasons for the suppressed Jahn-Teller distortion

To provide an explanation for the suppressed Jahn-Teller distortion, we analyzed the structural data obtained at room temperature in search for nonlinearities as a function of the Sr content x . A detailed analysis of the site occupancies revealed that the Ba/Sr distribution over the possible sites does not directly follow the stoichiometry (see Fig. 8). We found that the occupation probability for Ba at the Ba_1 site at intermediate stoichiometries is enhanced with respect to a completely random case and vice versa for the Ba_2 site. However, the occupation preferences are not very pronounced and do not fully coincide with the suppression of the Jahn-Teller distortion. In addition, such site preferences do not directly break the site symmetry of the Cr^{5+} ions, so that a Jahn-Teller distortion could still be energetically favorable. As all other quantities describing the average crystal structure change linearly as a function of the Sr content x [18], there seems to be no obvious structural reason for the suppression of this distortion.

However, as the prerequisite for such a distortion is a global degeneracy of electronic orbitals, it could also be suppressed by local changes in the crystal structure. While for pure $\text{Ba}_3\text{Cr}_2\text{O}_8$ and $\text{Sr}_3\text{Cr}_2\text{O}_8$, all Cr-O distances are well defined, we can expect strong local deviations from the average for intermediate values of x due to the very different ionic radii

FIG. 9. (Color online) Atomic displacements $\langle u^2 \rangle$ in $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ at room temperature as a function of the Sr content x .

of Ba^{2+} and Sr^{2+} . The different distributions of Sr/Ba ions inside the unit cell should thus lead to an increasing width of the distribution of Cr-O distances [19]. The symmetry at the Cr site would then be broken locally and would only be

FIG. 10. (Color online) (a) Estimated disorder contribution $\langle u_D^2 \rangle$ to the atomic displacements $\langle u^2 \rangle$ in $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ at room temperature as a function of the Sr content x . (b) Square root of the variance of atomic distances relevant to the electronic energies in the oxygen tetrahedron surrounding the Cr ions and for the interaction constant J_0 . The solid lines are guides to the eye.

preserved on average. Such a symmetry breaking then lifts the degeneracy of the e_g state by an energy difference $\Delta E(x)$. As $\Delta E(x)$ increases, the possible energy gain of the phase transition is lowered, and therefore this transition itself is gradually suppressed.

This scenario seems to be confirmed by the variation of the mean-square displacements $\langle u^2 \rangle$ as deduced from the structural refinement and shown in Fig. 9, which are found to be maximum for intermediate values of x . We attribute this behavior to an increase of the local disorder, which is common in solid solutions. To obtain an estimate for this disorder contribution, we have assumed that u is given by Gaussian distributions and comprises a thermal term and a disorder term, $u = u_T + u_D$, with no correlation between u_T and u_D . Therefore, the total mean displacement would be $\langle u^2 \rangle = \langle u_T^2 \rangle + \langle u_D^2 \rangle + 2\langle u_D u_T \rangle = \langle u_T^2 \rangle + \langle u_D^2 \rangle$. We have assumed the thermal part to be linear in x , $\langle u_T^2 \rangle(x) = \rho x + \tau$, and calculated the corresponding values for ρ and τ based on $\langle u^2 \rangle$ for $x = 0$ and $x = 3$. We subtracted this thermal part from the experimentally obtained displacements and plotted the resulting $\langle u_D^2 \rangle(x)$ in Fig. 10(b). Furthermore, as our argument mainly concerns variations of the distances between the oxygen and the chromium atoms, we have estimated the square root of the variance $\sqrt{\sigma_d}$ of the atomic distances d inside the tetrahedron. The value of $\sqrt{\sigma_d} = \sqrt{\langle (d - \langle d \rangle)^2 \rangle}$ is derived from the mean displacements and gives a more concrete picture of the influence of the chemical disorder on the distances which are important for the interaction constant and the orbital energies of the Cr atom that drive the Jahn-Teller distortion [see Fig. 10(a)]. All these disorder indicators peak where the structural transition is suppressed. We thus believe that this type of disorder is most likely at the origin of the suppression of the Jahn-Teller-induced structural phase transition.

IV. SUMMARY AND OUTLOOK

We have performed neutron powder diffraction experiments to obtain detailed structural information about $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ for various values of x at room temperature and $T = 2$ K. Based on these diffraction experiments, we have shown that the Jahn-Teller distortion reported for the parent compounds is present in $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ but seems to be gradually suppressed for intermediate values of x . We have given an explanation for this suppressed symmetry breaking at intermediate values of x based on an increasing disorder in the system. To test our hypothesis, experiments to directly probe the Cr states as a function of the Sr content x would be extremely helpful. Furthermore, density-functional-theory calculations of the total energy per unit cell for the two possible space groups, similar to those in [20], could clarify whether or not any symmetry breaking should be present in a disorder-free system with the respective equilibrium crystal structures for intermediate values of x . We have demonstrated that the interdimer interaction constant J_0 can be calculated within the EHTB framework. We furthermore showed that the reported peculiar change of J_0 can be explained based on the varying strength of this Jahn-Teller distortion. The tuning of J_0 with varying x as reported here should, along with a corresponding variation of the other relevant interaction constants, allow for a direct control of the critical fields H_c in the $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ system.

ACKNOWLEDGMENT

This work was supported by the Swiss National Science Foundation under Grants No. 21-126411 and No. 21-140465.

-
- [1] T. Nikuni, M. Oshikawa, A. Oosawa, and H. Tanaka, *Phys. Rev. Lett.* **84**, 5868 (2000).
 - [2] A. Schilling and H. Grundmann, *Ann. Phys. (NY)* **327**, 2301 (2012).
 - [3] M. Albiez, R. Gati, J. Fölling, S. Hunsmann, M. Cristiani, and M. K. Oberthaler, *Phys. Rev. Lett.* **95**, 010402 (2005).
 - [4] S. Levy, E. Lahoud, I. Shomroni, and J. Steinhauer, *Nature (London)* **449**, 579 (2007).
 - [5] A. A. Aczel, Y. Kohama, M. Jaime, K. Ninios, H. B. Chan, L. Balicas, H. A. Dabkowska, and G. M. Luke, *Phys. Rev. B* **79**, 100409 (2009).
 - [6] A. A. Aczel, Y. Kohama, C. Marcenat, F. Weickert, M. Jaime, O. E. Ayala-Valenzuela, R. D. McDonald, S. D. Selesnic, H. A. Dabkowska, and G. M. Luke, *Phys. Rev. Lett.* **103**, 207203 (2009).
 - [7] D. Kamenskyi, J. Wosnitza, J. Krzystek, A. Aczel, H. Dabkowska, A. Dabkowski, G. Luke, and S. Zvyagin, *J. Low Temp. Phys.* **170**, 231 (2013).
 - [8] H. Grundmann, A. Schilling, C. A. Marjerrison, H. A. Dabkowska, and B. D. Gaulin, *Mater. Res. Bull.* **48**, 3108 (2013).
 - [9] L. Chapon, C. Stock, P. G. Radaelli, and C. Martin, *arXiv:0807.0877*.
 - [10] P. Fischer, G. Frey, M. Koch, M. Könnecke, V. Pomjakushin, J. Schefer, R. Thut, N. Schlumpf, R. Bürge, U. Greuter, S. Bondt, and E. Berruyer, *Phys. B (Amsterdam, Neth.)* **276–278**, 146 (2000).
 - [11] FULLPROF is available free of charge at <http://www.ill.eu/sites/fullprof/>.
 - [12] K.-S. Lee and M.-H. Whangbo, *Inorg. Chem.* **45**, 10743 (2006).
 - [13] M.-H. Whangbo, H.-J. Koo, and D. Dai, *J. Solid State Chem.* **176**, 417 (2003).
 - [14] SAMOA is available free of charge at <http://www.primec.com/>.
 - [15] P. J. Hay, J. C. Thibeault, and R. Hoffmann, *J. Am. Chem. Soc.* **97**, 4884 (1975).
 - [16] M. Kofu, J.-H. Kim, S. Ji, S.-H. Lee, H. Ueda, Y. Qiu, H.-J. Kang, M. A. Green, and Y. Ueda, *Phys. Rev. Lett.* **102**, 037206 (2009).
 - [17] D. L. Quintero-Castro, B. Lake, E. M. Wheeler, A. T. M. N. Islam, T. Guidi, K. C. Rule, Z. Izaola, M. Russina, K. Kiefer, Y. Skourski, and T. Herrmannsdorfer, *Phys. Rev. B* **81**, 014415 (2010).
 - [18] See Supplemental Material at <http://link.aps.org/supplemental/10.1103/PhysRevB.90.075101> for detailed structural information on $\text{Ba}_{3-x}\text{Sr}_x\text{Cr}_2\text{O}_8$ obtained at room temperature and at $T = 2$ K.
 - [19] M. Medarde, J. F. Mitchell, J. E. Millburn, S. Short, and J. D. Jorgensen, *Phys. Rev. Lett.* **83**, 1223 (1999).
 - [20] G. Radtke, A. Saúl, H. A. Dabkowska, G. M. Luke, and G. A. Botton, *Phys. Rev. Lett.* **105**, 036401 (2010).